



3 April 2017

DRILLING OF NEW SOUTHEAST ZONE DISCOVERY EXTENDS STRIKE BY 700-METRES AT TRÊS ESTRADAS

Highlights:

- **Drilling along the newly discovered southeast zone has proven a strike-extension of at least 700 metres of shallow, additional mineralisation, with thicknesses and grades analogous to the current Três Estrada deposit:**
 - Hole TED-17-117 returned 42.00 meters grading 4.33% P₂O₅
 - Hole TED-17-112 returned 20.55 meters grading 3.67% P₂O₅
 - Hole TED-17-116 returned 47.73 meters grading 3.60% P₂O₅
- **Drilling of the strike extension to date has not cut off the mineralisation – strike length of NE extension remains open past 700 metres to the northeast**
- **Infill drill program continues to return better than expected results, confirming the homogeneous nature of mineralisation and continuity laterally and at depth**
- **Drilling strategy has been to focus on shallow mineralisation to add to current resource base – expected to reduce strip ratio and reduce mining costs**
- **13,022 meters of infill drilling has been completed and the program is anticipated to be wrapped up by the end of April**
- **Infill drilling within the main deposit continues to intercept mineralised zones thicker than anticipated in our original resource model:**
 - Hole TED-17-110 returned 96.97 meters grading 3.57% P₂O₅
- **Pilot plant flotation test at Eriez is currently underway running fresh carbonatite bulk sample – first commissioning work delivering expected results**

Brazilian fertiliser developer Aguia Resources Limited (ASX: AGR) (“Aguia” or “Company”) is pleased to update shareholders on the ongoing infill drilling program at its flagship Três Estradas Phosphate Project in southern Brazil. The program continues to return positive results that demonstrate the homogeneous and continuous nature of the deposit. Four diamond rigs continue to operate at site. To date a total of 13,022 metres have been drilled, which includes 8,807 metres of diamond drilling and 4,215 metres of reverse circulation drilling.

As announced on 16 February 2017, the Company has identified a new shallow zone of mineralisation along the southeast border of the proposed Três Estradas pit shell. Drilling has proven continuity of this zone **for at least 700 metres of strike with the NE extension remaining fully open**. Aguia took the decision to cease drilling at the 700 metre strike extension mark to focus on infill drilling.

Infill drilling along this 700 metres of strike continues with the objective of producing a measured and indicated category resource from surface to a depth of 100 metres. The technical team's strategy has been to target shallow mineralization that will be added to the current resource. It is expected that inclusion will not only improve the overall strip ratio of the proposed operation but will ultimately reduce mining costs. Initial results of this zone indicate that thicknesses and grades are in accordance with the bulk of the deposit as attested by results of hole TED-17-116 returning 47.73 metres of mineralisation grading 3.60% P₂O₅ and TED-17-117 returning 42.00 metres of mineralisation grading 4.33% P₂O₅.

Since the announcement of the infill drill program on 23 March 2017, the latest results continue to demonstrate the continuity of mineralisation both laterally and at depth. Modelling of these results has returned intersections that are thicker at depth than anticipated in the previous resource model, e.g. hole TED-17-110 that returned 96.97 metres grading 3.57% P₂O₅.

The pilot plant test of bulk fresh carbonatite sample is progressing well at the Flotation Division of Eriez in Pennsylvania. Initial results of this program should be available during April.

Technical Director Dr. Fernando Tallarico commented, "The outcome of the drilling along the new southeast zone and within the deposit continues to be very positive. We are not only able to prove continuity of mineralisation along strike and at depth, but we also have been able to define additional shallow resources that should positively impact our mining costs."

Managing Director Justin Reid added, "The success of our drilling program continues and we have made the decision to infill the new southeast limb. Our resource model is robust and expanding and it is important to convert the new discovery into Measured and Indicated resources in order to be included in our Bankable Feasibility Study. We will return to drilling the strike extension of this zone in the future. Our top priority is to define enough tonnes to drive a very robust mine model."

"Três Estradas continues to grow in terms of size and value, and together with surrounding projects that we have under option, we are methodically developing a phosphate project of significant scale that will be located in the heart of a Brazilian farming region that currently relies entirely on imported phosphate."

For further information, please contact:

Justin Reid, Managing Director

E: jreid@aguiaresources.com.au

T: +1 416-216-5446

Catherine Stretch, Chief Commercial Officer

E: cstretch@aguiaresources.com.au

T: +1 416-309-2695

Jan-Per Hole, Vice President Corporate Development Australia

E: jph@aguiaresources.com.au

T: +61 (0) 414 899 732

Released through: Ben Jarvis, Six Degrees Investor Relations: +61 413 150 448

Follow Aguia on Twitter: [@Aguia Resources](#)

About Aguia:

Agua Resources Limited, ("Agua") is an ASX listed company whose primary focus is on the exploration and development of phosphate projects in Brazil. Agua has an established and highly experienced in-country team based in Belo Horizonte, Brazil with corporate offices in Sydney, Australia. Agua's key projects are located in Rio Grande do Sul, a prime farming area which is 100% dependent on phosphate imports. The Rio Grande phosphate deposits exhibit high quality and low cost production characteristics, and are ideally located with proximity to road, rail, and port infrastructure. Agua's experienced management team has a proven track record of advancing high quality mining assets to production in Brazil.

The information in this announcement that relates to Exploration Targets, Exploration Results, Mineral Resources or Ore Reserves is based on information compiled by Dr Fernando Tallarico, who is a member of the Association of Professional Geoscientists of Ontario. Dr Tallarico is a full-time employee of the company. Dr Tallarico has sufficient experience that is relevant to the style of mineralisation and type of deposit under consideration and to the activity being undertaken to qualify as a Competent Person as defined in the 2012 Edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves'. Dr Tallarico consents to the inclusion in the report of the matters based on his information in the form and context in which it appears.




Figure 1: Geological map of the Três Estradas carbonatite draped over aerial photograph, highlighting the status of the ongoing drilling program.




Figure 2: Plan view of the PEA open pit model of Três Estradas, highlighting the new carbonatite zone discovered along the southeast border of the deposit. Inset on the right shows structural interpretation of the new zone along section 950NE.




Figure 3: Drilling section 950NE of the Três Estradas Deposit, showing the new southeast zone and one of the highlighted drill results of TED-17-116. Note that the bulk of the new carbonatite drilled in this section is beyond the previous pit model.




Figure 4: Drilling section 400NE of the Três Estradas Deposit, showing the thickening of the carbonatite at depth particularly in the intercept of hole TED-17-110.

Table 1 – Assay Results of the Drilling Campaign

(*Holes identifications initiated with TED are diamond holes and those initiated with TER are reverse circulation holes)

Hole_ID	From (m)	To (m)	Length (m)	P ₂ O ₅ %	CaO%	MgO%	Fe ₂ O ₃ %	SiO ₂ %	Al ₂ O ₃ %	
TED-17-109	188.00	274.55	86.55	3.97	36.08	7.37	9.29	8.61	1.45	
TED-17-110	150.00	246.97	96.97	3.57	32.04	9.68	8.80	11.48	2.13	
TED-17-112	33.71	54.26	20.55	3.67	34.70	7.57	6.86	15.21	2.28	
TED-17-116	109.70	157.43	47.73	3.60	33.70	9.43	7.32	10.76	2.03	
	159.00	201.00	42.00	4.33	28.42	8.72	8.75	19.40	4.40	
TED-17-117		Including	6.00	6.27	24.63	6.78	10.15	29.80	6.38	
		Including	7.00	5.13	29.89	14.54	5.91	9.99	1.15	
	0.00	15.00	15.00	15.29	20.16	1.57	19.88	28.18	3.91	
	15.00	80.00	65.00	6.65	35.00	6.72	8.71	11.27	1.58	
TER-17-229		Including	2.00	13.47	28.05	8.75	12.35	15.10	2.23	
		Including	7.00	11.17	29.68	8.59	11.95	12.61	1.57	
		Including	4.00	12.33	34.65	5.79	11.27	11.37	1.51	
TER-17-235					Not mineralized					
TER-17-236					Not mineralized					
TER-17-237	18.00	47.00	29.00	3.19	16.81	7.62	14.54	31.39	6.25	

Hole_ID	UTM_E	UTM_N	Elevation (m)	Length (m)	Status of coordinate	Datum	Azimuth	Dip
TED-17-109	767072	6576920	361	286.05	GPS	SAD-69 Z21S	150.00	-60.00
TED-17-110	766900	6576718	364	255.55	GPS	SAD-69 Z21S	150.00	-60.00
TED-17-112	767598	6576910	353	129.90	GPS	SAD-69 Z21S	330.00	-60.00
TED-17-116	767481	6576790	353	166.95	GPS	SAD-69 Z21S	330.00	-60.00
TED-17-117	767250	6576612	358	206.20	GPS	SAD-69 Z21S	330.00	-55.00
TER-17-229	766853	6576521	362	80.00	GPS	SAD-69 Z21S	0.00	-90.00
TER-17-235	767217	6576768	366	40.00	GPS	SAD-69 Z21S	0.00	-90.00
TER-17-236	767242	6576725	362	70.00	GPS	SAD-69 Z21S	0.00	-90.00
TER-17-237	767209	6576864	366	47.00	GPS	SAD-69 Z21S	0.00	-90.00

JORC Code, Table 1

Section 1 Sampling Techniques and Data

(Criteria in this section apply to all succeeding sections.)

Criteria	JORC Code explanation	Commentary
Sampling techniques	<ul style="list-style-type: none"> Nature and quality of sampling (eg cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling. 	<ul style="list-style-type: none"> Work is being carried out using RC and diamond drilling, with samples being analysed by laboratory analyses suitable for the carbonatite mineralisation being targetted Drill hole locations are detailed in a table in the text of this release, and shown graphically on a plan
	<ul style="list-style-type: none"> Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used. 	<ul style="list-style-type: none"> Hole locations are picked up using hand-held GPS. Sampling is carried out using comprehensive Agua protocols and QAQC procedures as per industry best practice
	<ul style="list-style-type: none"> Aspects of the determination of mineralisation that are Material to the Public Report. In cases where 'industry standard' work has been done this would be relatively simple (eg 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information. 	<ul style="list-style-type: none"> Mineralisation is generally visual RC samples are collected and assayed at 1m intervals, with a representative 2kg sample of all intervals being collected for XRF assay at the laboratory. Half core diamond drill samples in mineralized material are generally collected at 1m intervals and sent to the laboratory for assay; however lengths will vary to generally between 0.5 and 1.5m to honour geological boundaries where required. In all cases drilling samples are sent to SGS laboratories in Belo Horizonte and analysed using method XRF79C_10 – Lithium tetra borate fusion. Elements assayed for include SiO₂, Al₂O₃, Fe₂O₃, CaO, MgO, TiO₂, P₂O₅, Na₂O, K₂O, MnO and LOI, which is considered suitable for the type of mineralisation

Criteria	JORC Code explanation	Commentary
<i>Drilling techniques</i>	<ul style="list-style-type: none"> • <i>Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc).</i> 	<ul style="list-style-type: none"> • Reverse Circulation – Drilling utilized a face sampling Hard Formation Bit with Tungsten buttons and a diameter of 5 ½ inches. No downhole surveys were completed. • Core Drilling - Drilling utilized HQ equipment for weathered material and NQ for fresh rock. Downhole surveys are performed on 3-metre intervals using a Maxibore down-hole tool. No core orientation has been carried out.
<i>Drill sample recovery</i>	<ul style="list-style-type: none"> • <i>Method of recording and assessing core and chip sample recoveries and results assessed.</i> 	<ul style="list-style-type: none"> • RC – recoveries are monitored by samples weight. The minimum recovery is 85%. • Core Drilling - Recovery by sample and by drill run was recorded; core recovery generally exceeds 97%
	<ul style="list-style-type: none"> • <i>Measures taken to maximise sample recovery and ensure representative nature of the samples.</i> 	<ul style="list-style-type: none"> • Diamond Drilling - Due to the coherent nature of the fresh rock and homogenous nature of the mineralisation sample recovery is not an issue. In the saprolite recovery is maximised using short drill runs and best drilling practices. • RC – Dry samples are collected through a cyclone and riffle splitter ensuring homogenisation and representative sampling. Wet samples are dried, and then homogenised and sampled by hand.
	<ul style="list-style-type: none"> • <i>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</i> 	<ul style="list-style-type: none"> • Mineralisation is homogenous throughout the mineralized intervals, with no relationship between sample recovery and grade on any type of drilling.
<i>Logging</i>	<ul style="list-style-type: none"> • <i>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</i> 	<ul style="list-style-type: none"> • RC – logging is to a detail considered suitable for inclusion in resource estimations • Diamond – logging is considered suitable for inclusion in resource estimations, metallurgical studies and preliminary mining studies. The lack of orientated core and geotechnical logging prior to cutting precludes the use in detailed mining studies
	<ul style="list-style-type: none"> • <i>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography.</i> 	<ul style="list-style-type: none"> • RC logging includes lithology and weathering • Diamond logging includes rock type, alteration, structure and qualitative magnetism. No core orientation has been carried out, with structural measurements being limited to alpha angles only. All core is photographed dry before being cut
	<ul style="list-style-type: none"> • <i>The total length and percentage of the relevant intersections logged</i> 	<ul style="list-style-type: none"> • 100% of the relevant intersections of all drilling are logged
<i>Sub-sampling techniques and sample preparation</i>	<ul style="list-style-type: none"> • <i>If core, whether cut or sawn and whether quarter, half or all core taken.</i> 	<ul style="list-style-type: none"> • Solid core is sawn in half, with half being sent for assay and half being retained for reference. Friable core is split down the center line using a spatula or similar tool, with half being retained and half sent for assay.
	<ul style="list-style-type: none"> • <i>If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry.</i> 	<ul style="list-style-type: none"> • RC- One metre samples are collected from the cyclone, with moist samples being split using a

Criteria	JORC Code explanation	Commentary
		<p>plastic liner and metal cross-blade device, and dry samples being split through a riffle splitter. Saturated samples are dried before homogenization. Two representative samples of between 500g and 2kg are collected, with one for assay and a second for reference.</p> <ul style="list-style-type: none"> For all sampling and drilling, samples are dried and crushed, and then milled to 75% passing 80 mesh using LM mills at the laboratory.
	<ul style="list-style-type: none"> For all sample types, the nature, quality and appropriateness of the sample preparation technique. 	<ul style="list-style-type: none"> The sample preparation techniques are industry standard and are considered appropriate for the mineralisation being investigated
	<ul style="list-style-type: none"> Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples. 	<ul style="list-style-type: none"> Industry standard procedures are employed, including ensuring non-core samples are adequately homogenized before assay and archive samples are collected
	<ul style="list-style-type: none"> Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling. 	<ul style="list-style-type: none"> No field duplicate samples or second half sampling was done. The target mineralization is largely homogeneous.
	<ul style="list-style-type: none"> Whether sample sizes are appropriate to the grain size of the material being sampled. 	<ul style="list-style-type: none"> Sample sizes are considered appropriate to the grain size of the material being assayed
Quality of assay data and laboratory tests	<ul style="list-style-type: none"> The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total. 	<ul style="list-style-type: none"> The XRF method used is industry standard and considered appropriate for the analysis of apatite-hosted phosphate mineralisation. Sample preparation and analysis was completed at SGS's Belo Horizonte laboratory in Brazil using standard crushing and pulverization techniques. The prepared pulps are analysed by a lithium borate fusion XRF spectroscopy for major oxide elements (P₂O₅, Al₂O₃, CaO, Fe₂O₃, K₂O, MgO, MnO₂, SiO₂, TiO₂, Na₂O and LOI (Method code XRF79C and PHY01E). In specific cases, samples were also analysed for a suite of 31 elements using an aqua regia digestion and inductively coupled plasma - mass spectrometry (Method code ME-MS81). The preparation and analytical procedures are appropriate for the type of mineralization sampled and are reliable to deliver the total content of the analysed compounds.
	<ul style="list-style-type: none"> make and model, reading times, calibrations factors applied and their derivation, etc. 	<ul style="list-style-type: none"> Where utilised, hand held XRF is an Delta Analyser CS-4000 by Innov-X Systems
	<ul style="list-style-type: none"> For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument 	<ul style="list-style-type: none"> There is a calibration plate supplied by INOVV-X-Systems for the calibration of the Portable X Ray Fluorescence equipment.
	<ul style="list-style-type: none"> Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been 	<ul style="list-style-type: none"> Agua has prepared two certified phosphate reference materials (standards) from material collected from the Tres Estradas deposit – these comprise a mid and high grade standard and are

Criteria	JORC Code explanation	Commentary
	<i>established.</i>	<p>considered appropriate to the mineralisation being drilled</p> <ul style="list-style-type: none"> • This is in addition to fine and coarse blank standards prepared from barren quartz veins. • One each of the above company supplied standards is included in each batch of 48 samples, in addition to a pulp duplicate. • One batch of 48 samples is sent monthly for umpire laboratory testing. • Umpire testing is performed at At ALS Chemex in Lima, Peru, where they are analyzed for a suite of elements using method code XRF12pt/XRF24) • Additionally, Agua relies on the analytical quality control measured implemented by the ISO accredited laboratory used.
<i>Verification of sampling and assaying</i>	<ul style="list-style-type: none"> • <i>The verification of significant intersections by either independent or alternative company personnel.</i> 	<ul style="list-style-type: none"> • The AGR procedures consists an internal double check and, when required an independent verification during the independent audit process.
	<ul style="list-style-type: none"> • <i>The use of twinned holes.</i> 	<ul style="list-style-type: none"> • Given this is the initial programme at TE South no twin holes have been drilled
	<ul style="list-style-type: none"> • <i>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</i> 	<ul style="list-style-type: none"> • Data is manually entered onto logging sheets on site by Agua geologists. This data is then entered into a digital database consisting of Excel workbooks. Assay data from the laboratory is merged into the downhole sample sheets. All original logging sheets and digital data are stored. Digital data is regularly backed up. • Data is yet to be externally audited; external audits of previous drilling has confirmed the veracity of work carried out
	<ul style="list-style-type: none"> • <i>Discuss any adjustment to assay data.</i> 	<ul style="list-style-type: none"> • There is no adjustment to assay data
<i>Location of data points</i>	<ul style="list-style-type: none"> • <i>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</i> 	<ul style="list-style-type: none"> • All borehole collars were surveyed according to the local UTM coordinate system (South American Datum 1969 – SAD69, Zone 21S), using differential GPS equipment before drilling started, and once drilling had been completed.
	<ul style="list-style-type: none"> • <i>Specification of the grid system used.</i> 	<ul style="list-style-type: none"> • SAD 1969 UTM system, Zons 21S
	<ul style="list-style-type: none"> • <i>Quality and adequacy of topographic control.</i> 	<ul style="list-style-type: none"> • A topographic survey of the project area was completed using differential GPS technology. • The survey consisting of lines spaced 25 metres apart, and control lines spaced 100 metres apart. • The topographic survey generated contour lines at 1-metre intervals in the meta-carbonatite area. Contour lines at 5-metre intervals were obtained for the remaining area using shuttle radar topography mission (SRTM) and orthorectified Geoeye images with 0.5 metre resolution.

Criteria	JORC Code explanation	Commentary
<i>Data spacing and distribution</i>	<ul style="list-style-type: none"> <i>Data spacing for reporting of Exploration Results.</i> 	<ul style="list-style-type: none"> RC Drilling – RC holes, all vertical, at Tres Estrada South are being drilled on 50m spaced lines, with spacing along drill lines determined by carbonatite outcrop Diamond Drilling - Diamond holes (inclined) at Tres Estradas are being drilled on 100m spaced lines, with spacing along drill lines determined by carbonatite outcrop
	<ul style="list-style-type: none"> <i>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</i> 	<ul style="list-style-type: none"> The data spacing and distribution is considered suitable for the style of mineralisation being tested, and will be suitable for use in Mineral Resource and Reserve estimations
	<ul style="list-style-type: none"> <i>Whether sample compositing has been applied.</i> 	<ul style="list-style-type: none"> For the purposes of reporting of results no sample compositing has been applied
<i>Orientation of data in relation to geological structure</i>	<ul style="list-style-type: none"> <i>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</i> 	<ul style="list-style-type: none"> The bulk nature of the mineralisation indicates that sampling bias will not be introduced by changing drilling direction
	<ul style="list-style-type: none"> <i>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</i> 	<ul style="list-style-type: none"> Given the bulk and homogenous nature of the mineralisation it is considered that there is no sampling bias
<i>Sample security</i>	<ul style="list-style-type: none"> <i>The measures taken to ensure sample security.</i> 	<ul style="list-style-type: none"> Chain of custody is managed by Aguia. Samples are stored on site. Assay samples are sent by freight express to the relevant laboratories.
<i>Audits or reviews</i>	<ul style="list-style-type: none"> <i>The results of any audits or reviews of sampling techniques and data.</i> 	<ul style="list-style-type: none"> Tres Estradas – Audit by SRK Consulting in early 2013 and late 2014 indicated that techniques utilised by Aguia were in line with generally accepted industry best practices. The same audit found no issues with the data.

Section 2 Reporting of Exploration Results

(Criteria listed in the preceding section also apply to this section.)

Criteria	JORC Code explanation	Commentary
<i>Mineral tenement and land tenure status</i>	<ul style="list-style-type: none"> <i>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</i> <i>The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.</i> 	<ul style="list-style-type: none"> Tres Estradas <p>Permit 810.090/91, irrevocable right to 100% under an exercised option agreement with Companhia Brasileira de Cobre (CBC).</p> <p>On July 1, 2011, CBC and Aguia Metais Ltda., a subsidiary of Aguia in Brazil, executed an option agreement providing the irrevocable purchase option of these mineral rights by Aguia Metais (or its affiliate or subsidiaries). On May 30, 2012 Aguia Metais exercised the purchase option concerning these mineral rights by means of its affiliate Aguia Fertilizantes S/A (Agua Fertilizantes). On July 10, 2012, CBC and Agua Fertilizantes executed an irrevocable agreement providing the assignment of</p>

Criteria	JORC Code explanation	Commentary
		<p>these mineral rights to Agua Fertilizantes. On July 20, 2012 CBC filed a request before the DNPM applying for the transfer of these mineral rights to Agua Fertilizantes.</p> <p>The 2nd two-year term expired on August 16, 2012, with the Final Exploration Report now under review by the Government, approval of which will allow the Company a further year (from the date of approval) to submit an Economic Exploitation Plan.</p> <ul style="list-style-type: none"> • Tres Estradas South <p>Permit 810.325/12, irrevocable right to 100% under an exercised option agreement with Companhia Brasileira de Cobre.</p> <p>Granted April 29, 2013, initial 3 year term expiry April 29, 2016. The partial report with time extension request was filed February 23, 2016.</p>
<i>Exploration done by other parties</i>	<ul style="list-style-type: none"> • <i>Acknowledgment and appraisal of exploration by other parties.</i> 	<ul style="list-style-type: none"> • Tres Estradas and Tres Estrada South <p>Discoveries of phosphate rich rocks at TE were made by a joint exploration programme between Companhia Brasileira do Cobre and Santa Elina in 2007/2008 during a gold exploration programme. This involved an integrated geochemical/geological/geophysical and drilling programme. The gold results were disappointing, causing Santa Elina to withdraw from the JV, however +6% phosphate values were noted in assaying of soils and drill core.</p>
<i>Geology</i>	<ul style="list-style-type: none"> • <i>Deposit type, geological setting and style of mineralisation.</i> 	<ul style="list-style-type: none"> • Tres Estradas and Tres Estradas South <p>The mineralisation is a carbonatite hosted phosphate deposit, with apatite as the phosphate bearing mineral. The NE-SW trending carbonatite is probably Mid-Proterozoic in age, and has been affected by Neo-Proterozoic shearing and metamorphism. It is hosted in the Santa Maria Chico Granulite Complex, within the Taquarembo Domain of the Achaean to Proterozoic Sul-riograndense Shield.</p>
<i>Drill hole Information</i>	<ul style="list-style-type: none"> • <i>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes:</i> <ul style="list-style-type: none"> ○ <i>easting and northing of the drill hole collar</i> ○ <i>elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</i> ○ <i>dip and azimuth of the hole</i> 	<ul style="list-style-type: none"> • Drillhole information is listed in the appropriate tables in this document, and presented in maps and sections

Criteria	JORC Code explanation	Commentary
	<ul style="list-style-type: none"> ○ down hole length and interception depth ○ hole length. ● If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case. 	
Data aggregation methods	<ul style="list-style-type: none"> ● In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (eg cutting of high grades) and cut-off grades are usually Material and should be stated. 	<ul style="list-style-type: none"> ● Drill intersections are length weighted. A nominal 3% P₂O₅ lower cutoff is used, and there is no upper cut applied to intersections.
	<ul style="list-style-type: none"> ● Where aggregate intercepts incorporate short lengths of high grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail. 	<ul style="list-style-type: none"> ● Not applicable
	<ul style="list-style-type: none"> ● The assumptions used for any reporting of metal equivalent values should be clearly stated. 	<ul style="list-style-type: none"> ● Not applicable
Relationship between mineralisation widths and intercept lengths	<ul style="list-style-type: none"> ● These relationships are particularly important in the reporting of Exploration Results. 	<ul style="list-style-type: none"> ● RC drilling is targeting the flat lying upper oxide mineralisation – these holes may be terminated in mineralisation once fresh rock has been intersected ● Diamond drilling is targeted to intersect the full width of the interpreted steeply dipping carbonatite bodies
	<ul style="list-style-type: none"> ● If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. 	<ul style="list-style-type: none"> ● RC drilling is generally perpendicular to the flat-lying oxide blanket, and oxide intersection widths will reflect the true thickness of the oxide layer. ● Diamond holes are drilled at an acute angle to the steeply to vertically dipping carbonatite bodies, hence downhole widths will be greater than true widths. For drillholes drilled at -60°, true mineralisation widths will generally be in the order of 40-60% of downhole intersection lengths – this is shown in more detail on included cross sections.
	<ul style="list-style-type: none"> ● If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (eg 'down hole length, true width not known'). 	<ul style="list-style-type: none"> ● Down hole lengths are reported ● Relationships between true lengths and true thickness are shown in cross sections
Diagrams	<ul style="list-style-type: none"> ● Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views. 	<ul style="list-style-type: none"> ● Refer to maps and sections in release
Balanced reporting	<ul style="list-style-type: none"> ● Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high 	<ul style="list-style-type: none"> ● Results from all drillholes have been reported

Criteria	JORC Code explanation	Commentary
	<i>grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</i>	
<i>Other substantive exploration data</i>	<ul style="list-style-type: none"> <i>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</i> 	<ul style="list-style-type: none"> Geological mapping and interpretation is used as a base for included drill hole plans and sections
<i>Further work</i>	<ul style="list-style-type: none"> <i>The nature and scale of planned further work (eg tests for lateral extensions or depth extensions or large-scale step-out drilling).</i> 	<ul style="list-style-type: none"> As presented in the text of this report
	<ul style="list-style-type: none"> <i>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</i> 	<ul style="list-style-type: none"> As presented in the text of this report

Section 3 Estimation and Reporting of Mineral Resources

Not applicable to this release – this does not include mineral resource estimations

Section 4: Estimation and Reporting of Ore Reserves

Not applicable to this release

Section 5: Estimation and Reporting of Diamonds and Other Gemstones

Not applicable to this release