

3 NOV 2021

Assays Returned for Maiden Drill Campaign at Harden

Further high-grade gold intercepts and anomalous geochemistry provide encouragement for imminent diamond drill campaign

New Highlight Assay Results

Assay results received from the remaining reverse circulation (**RC**) holes at the Harden Gold Mine Prospect with significant results including:

Hole RC21HN011 6m at 2.0g/t Au from 128m, including

1m at 7.55g/t Au from 128m

Hole RC21HN010 1m at 0.7g/t Au from 113m
 Hole RC21HN009 6m at 0.36g/t Au from 118m
 Hole RC21HN008 1m at 1.16g/t Au from 51m

Hole RC21HN007 1m at 0.64g/t Au from 99m

Significant Re-assay Results

Hole RC21HN006 3m at 5.12g/t Au from 80m, within

6m at 3.60g/t Au from 79m

Previously Reported Assays

Hole RC21HN005 2m at 19.09g/t Au, including

1m at 32.80g/t Au from 111m, and

1m at 6.24g/t Au from 134m

Hole RC21HN006 3m at 4.62g/t Au from 79m, within

8m at 2.45g/t Au from 77m


Hole RC21HN003 9m at 0.56g/t Au from 120m, and

4m at 0.51g/t Au from 133m

Upcoming Diamond Drilling

Highly encouraging results from the maiden drill campaign at the Harden Gold Mine Prospect warrant priority testing of down-plunge targets to begin in early November:

- The diamond drill campaign is planned for 5 holes totalling ~1,200m
- Regulatory approval has been granted for this campaign and additional follow up campaigns



Management Comment

Legacy Minerals Managing Director, Christopher Byrne said:

"The latest assays from the Company's maiden drilling at the Harden Gold Mine Prospect have confirmed it is an exciting and rapidly developing high-grade gold discovery with significant potential. The grades seen to date across a strike of 400m demonstrate the size potential for the system.

We are keenly progressing further exploration and the diamond drilling planned for this month is a very exciting next step. It will allow us to test the continuity of the orebody at depth and we expect the drill campaign to run until mid-December."




Figure 1: Cross Section showing interpreted veins and mineralised halo (0.2g/t Au cut-off grade)






Figure 2: Cross Section showing interpreted veins and mineralised halo (0.2g/t Au cut-off grade)




Figure 3. Plan of Harden Gold Mine Prospect drill collars and hole traces

Results of initial Dipole-Dipole Induced Polarisation (DD-IP) target testing

Drill hole RC21HN010 tested the eastern high priority IP anomaly nearby the Harden Gold Mine Prospect. Drilling intersected sericite-pyrite alteration from 70m-78m and 87-99m coinciding with the location of the DD-IP chargeability anomaly. Initial interpretation is that the anomaly is due to disseminated sulphides. The best gold intercept of **1m at 0.7g/t Au** from 113m is also encouraging, confirming gold mineralisation off the main strike of the Harden Gold Mines. A large amount of clay was observed from 151m to 157m (end of hole) which is interpreted to be a newly identified fault zone. The clay intercepted does not appear to be responsible for the chargeability anomaly. Drilling was halted due to poor drilling conditions through the clay zone. The company now plans to test this IP target along strike and closer to the Harden Gold Mine where the chargeability response increases.

Assays and Sampling

The RC drilling initially recorded an assay result interval in RC21HN006 of **6m at 3.19g/t Au** from 79m, including a higher-grade interval of **3m at 4.62g/t Au** from 79m. Due to the high gold grades encountered and observed visible gold, LGM undertook an independent re-split and re-assay of the original drill sample. The results of this sampling confirmed the high-grade results and returned a better overall result of **6m at 3.6g/t Au** from 79m, including a higher-grade interval of **3m at 5.12g/t Au** from 80m. These results indicate that a nugget effect is causing variability in the assay results. LGM is currently having the original higher grade drill intervals re-split and re-assayed including the processing by screen fire assay of some samples to assess the significance of the nugget effect.



Diamond Drilling – November to December

The Company has five holes planned **totalling ~1,200m**. These holes will be testing along strike and underneath historical workings. The use of the diamond drilling will allow for the testing of depth extensions to these workings as well as provide structural information relating to the character of mineralisation and alteration previously intercepted in the RC drilling.




Figure 4: Oblique view of drilling at the Harden Gold Mine Prospect Looking South-West



About the Harden Project

The Harden Project encompasses several historical high-grade gold mines in a mineral district that has produced >460,000 oz Au from alluvial and hard rock mining. The historical mines within Legacy Minerals' tenement were the largest hard rock mines in the district. They produced a combined total of \sim 75,000 oz Au at an average grade of 28.6g/t Au – all before 1919. There are two main strikes of mine in the tenement area: the historical Harden Gold Mine corridor and McMahons Reef Gold Mine corridor.

Significant drilling across the tenement includes:

Harden Gold Mine Prospect

2.0m at 19.1g/t from 110m 3.0m at 10.5g/t Au from 20m 3.0m at 5.1/t Au from 79m 6.0m at 1.1g/t Au from 104m

McMahons Reef Gold Mine Prospect

3.6m at 21.7g/t Au from 115m 5.8m at 4.7g/t Au from 104m 5.2m at 1.9g/t Au from 82m 2.6m at 2.1g/t Au from 100m




Figure 5: Overview showing the Harden Project exploration licences



About Legacy Minerals

Legacy Minerals is an ASX listed public Company that has been involved in the acquisition and exploration of gold, copper, and base-metal projects in the Lachlan Fold Belt since 2017. The Company has five wholly owned and unencumbered tenements that present significant discovery opportunities.

Au-Cu (Pb-Zn) Cobar Project (EL8709, EL9256)

Undrilled targets next door to the Peak Gold Mines with several priority geophysical anomalies Late time AEM conductors, IP anomaly, and magnetic targets Geochemically anomalous - gold in lag up to 1.55g/t Au

Au-Ag Bauloora Project (EL8994)

One of the largest low sulphidation systems in NSW with bonanza Ag grades and high-grade Au and base metals. Face samples at the Bauloora Mine include 3701g/t Ag, 6.9g/t Au, 29% Pb, 26% Zn, and 6.4% Cu

Au Harden Project (EL8809, EL9257)

Large historic high-grade quartz-vein gold mineralisation open along strike and down plunge. Significant drill intercepts include 3.6 at 21.7g/t Au 116m and 2m at 19.09g/t Au from 111m

Au-Cu Fontenoy Project (EL8995)

The Project exhibits a greater than 8km long zone of Au and Cu anomalism defined in soil sampling and drilling. Significant drill intercepts include **79m at 0.27% Cu** from 1.5m

Cu-Au Rockley Project (EL8296)

Prospective for porphyry Cu-Au and situated in the Macquarie Arc Ordovician host rocks the project contains historic high-grade copper mines and rock chips up to **4.26% Cu and 90g/t Ag**.




Figure 6: Legacy Minerals' Tenements, Lachlan Fold Belt NSW



Approved by the Directors of Legacy Minerals Holdings Limited.

For more information:

Chris Byrne
CEO & Managing Director
chris.byrne@legacyminerals.com.au
+61 (0) 499 527 547

Victoria Humphries
Media & Investor Relations
victoria@nwrcommunications.com.au
+61 (0) 431 151 676

DISCLAIMER AND PREVIOUSLY REPORTED INFORMATION

Information in this announcement is extracted from the Company's Prospectus dated 28 July 2021 lodged as a market announcement on 9 September 2021 and the following market announcements by the Company:

- 5 October 2021 Additional High-Grade Gold Assays at Harden
- 23 September 2021 High-Grade Gold Assays Returned for Maiden Drilling
- 22 September 2021 Significant IP Chargeability Anomalies Define New Targets
- 16 September 2021 Maiden drill campaign intersects visible gold at Harden

The Company confirms that it is not aware of any new information that materially affects the information included in the original market announcement and that all material assumptions and technical parameters underpinning the estimates in the relevant market announcement continue to apply and have not materially changed.

This announcement contains certain forward-looking statements. Forward looking statements are only predictions and are subject to risks, uncertainties and assumptions which are outside of the control of Legacy Minerals Holdings Limited (LGM). These risks, uncertainties and assumptions include commodity prices, currency fluctuations, economic and financial market conditions, environmental risks and legislative, fiscal or regulatory developments, political risks, project delay, approvals and cost estimates. Actual values, results or events may be materially different to those contained in this announcement. Given these uncertainties, readers are cautioned not to place reliance on forward-looking statements. Any forward-looking statements in this announcement reflect the views of LGM only at the date of this announcement. Subject to any continuing obligations under applicable laws and ASX Listing Rules, LGM does not undertake any obligation to update or revise any information or any of the forward-looking statements in this announcement to reflect changes in events, conditions or circumstances on which any forward-looking statements is based.

COMPETENT PERSONS STATEMENT

The information in this report that relates to Exploration Targets, Exploration Results, Mineral Resources or Ore Reserves is based on information compiled by Thomas Wall, a Competent Person who is a Member of the Australian Institute of Geoscientists. Mr Wall is the Technical Director is a full-time employee of Legacy Minerals Limited and a shareholder, who has sufficient experience that is relevant to the style of mineralisation and type of deposit under consideration and to the activity being undertaken to qualify as a Competent Person as defined in the 2012 edition of the Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves. Mr Wall consents to the inclusion in the report of the matters based on his information in the form and context in which it appears in this announcement.



Table 1. Harden Project, Harden Gold Mine Prospect drill hole assay results

Significant intervals defined using >=0.2g/t Au, >=1m downhole width, <=1m internal waste and >=1g/t Au, >=1m downhole width, <=1m internal waste. All intercepts are down hole widths. Collar location and orientation information coordinates are MGA Zone 55, AHD RL. See Appendix 1 for additional details.

Above 0.2g/t Au cut-off. NSR = No significant results

Above 0.2g/t Au cut-off. NSR = No significant results Interval			Drill hole Collar Information							
Hole ID	From (m)	To (m)	Width (m)	Au (g/t)	Easting	Northing	RL	Depth (m)	Di p	Azimut h
RC21HN001				NSR	627433	6178285	419	138	70	200
RC21HN002				NSR	628252.5	6177906	435.29	162	-65	195
RC21HN003	110	111	1	0.2	628193	6177956	433.65	204	71	196
and	120	129	9	0.56						
and	133	141	8	0.38						
incl.	133	137	4	0.51						
and	146	148	2	0.3						
and	163	164	1	0.47						
and	186	187	1	0.22						
RC21HN004	97	98	1	0.41	628188.1	6177958	433.65	166	50	193
and	143	144	1	0.64						
and	150	151	1	0.67						
RC21HN005	110	115	5	7.81	628031.3	6178020	429	144	65	180
incl.	111	113	2	19.09						
Incl.	111	112	1	32.80						
and	133	138	5	1.47						
incl.	134	135	1	6.24						
RC21HN006 (original)	77	85	8	2.45	628028	6178021	428.72	85	50	200
incl.	79	82	3	4.62						
RC21HN006 (re-assay)	79	85	6	3.60						
Incl.	80	83	3	5.12						
RC21HN007	99	100	1	0.64	628079.7	6177983	430.42	114	-70	200
and	104	105	1	0.38						
RC21HN008	51	55	4	0.42	628327.6	6177843	437.19	96	-60	200
incl.	51	52	1	1.16						
RC21HN009	118	124	6	0.36	628398.9	6177870	439.49	156	-60	200
RC21HN010	113	114	1	0.7	628170.5	6177842	431.79	157	-60	245
RC21HN011	109	110	1	0.28	628009.8	6178030	428.62	140	-60	240
and	112	116	4	0.3						
and	124	125	1	0.78						
and	128	134	6	2.00						
incl.	128	129	1	7.55						

Appendix 1 – JORC Code, 2021 Edition Table 1

Section 1 Sampling Techniques and Data Criteria **JORC Code Explanation** Commentary Nature and quality of sampling (e.g., cut RC Sampling: All samples from the RC drilling are taken as 1m channels, random chips, or specific specialised samples for laboratory assay. Samples are collected using cone or industry standard measurement tools riffle splitter. Geological logging of RC chips is completed at site appropriate to the minerals under investigation, with representative chips being stored in drill chip trays. Magnetic such as down hole gamma sondes, or handheld susceptibility was recorded from the green bulk bag for each meter XRF instruments, etc). These examples should not by a KT-10 mag sus meter. be taken as limiting the broad meaning of sampling. RC drilling was undertaken by Durock Drilling Pty Ltd Include reference to measures taken to ensure RC Sampling: Samples are taken on a one metre basis and collected sample representivity and the appropriate using uniquely numbered calico bags. The remaining material for calibration of any measurement tools or systems that metre is collected and stored in a green plastic bag marked with that specific metre interval. The cyclone is cleaned with used. compressed air after each plastic and calico sample bag is removed. If wet sample or clays are encountered then the cyclone is opened and cleaned manually and where appropriate with the aid of a compressed air gun. A duplicate sample is taken every 50th sample and a certified sample standard at 1:50 samples. Standards may also be added according to geology. The RC samples are then assayed at a certified assay laboratory (ALS Laboratories). Sampling **Techniques** Geological logging of RC chips is completed at site with representative chips being stored in drill chip trays. Downhole surveys of dip and azimuth are conducted using a single shot camera every 30m, and using a downhole Gyro when required, to detect deviations of the hole from the planned dip and azimuth. The drill-hole collar locations are recorded using a hand-held GPS, which has an accuracy of +/- 5m. All drill-hole collars may be surveyed to a greater degree of accuracy using a certified surveyor at a later date. An Olympus Vanta pXRF is used to systematically analyse the RC sample onsite. One reading is taken per metre with field calibration of the pXRF instrument using standards periodically performed (usually daily). The handheld pXRF results are only used for preliminary assessment of element compositions, prior to the receipt of assay results from the certified laboratory. The holes were geologically logged and the magnetic susceptibility Sampling Aspects of the determination of mineralisation **Techniques** that are Material to the Public Report. In cases was recorded from the calico bag for each meter by a KT-10 mag where 'industry standard' work has been done sus meter. this would be relatively simple (e.g., 'reverse circulation drilling was used to obtain 1 m RC Drilling – the total sample (~20-30kg) is delivered via cyclone samples from which 3 kg was pulverised to into a large plastic bag which is retained for future use if required.

produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (e.g., submarine nodules) may warrant disclosure of detailed information.

Where appropriate, resampling is conducted using the bulk samples (~20-30kg green bags) where the sample is riffle split down to a 3kg representative sample.

The RC samples were transported to ALS Laboratory in Orange for assaying. Pulverize up to 3kg of raw sample. QC specification of 85% <75µm. Samples greater than 3kg are split prior to pulverizing and the remainder retained. Gold was determined by fire assay fusion of a 30g charge with an AAS analytical finish. The lower detection limit for gold is 0.01 ppm, which is believed to be an appropriate detection level.

The RC drilling initially recorded an assay result interval in RC21HN006 of 6m at 3.19g/t Au from 79m, including a higher-grade interval of 3m at 4.62g/t Au from 79m. Due to the high gold grades encountered and observed visible gold, LGM undertook an

		independent re-split and re-assay of the original drill sample. The results of this sampling confirmed the high-grade results and returned a better overall result of 6m at 3.6g/t Au from 79m, including a higher-grade interval of 3m at 5.12g/t Au from 80m. These results indicate that a nugget effect is causing variability in the assay results. LGM is currently having the original higher grade drill intervals re-split and re-assayed including the processing by screen fire assay of some samples to assess the significance of the nugget effect.
Drilling techniques	Drill type (e.g., core, reverse circulation, openhole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (e.g., core diameter, triple or standard tube, depth of diamond tails, facesampling bit or other type, whether core is oriented and if so, by what method, etc).	RC Sampling: The RC drilling uses a 144 mm diameter face hammer tool. High-capacity air compressors on the drill rig are used to ensure a continuously sealed and high-pressure system during drilling to maximise the recovery of the drill cuttings, and to ensure chips remain dry to the maximum extent possible.
	Method of recording and assessing core and chip sample recoveries and results assessed.	RC Sampling: RC samples are visually checked for recovery, moisture and contamination. Geological logging is completed at site with representative RC chips stored in chip trays. Sample weights were recorded on site using digital scales for each calico sample.
Drill sample recovery	Measures taken to maximise sample recovery and ensure representative nature of the samples.	RC Sampling: Samples are collected using cone or riffle splitter. Geological logging of RC chips is completed at site with representative chips being stored in drill chip trays. Sample sizes were monitored, and the splitter was regularly agitated to reduce the potential for sample contamination
	Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.	To date, no sample recovery issues have yet been identified that would impact on potential sample bias in the competent fresh rocks that host the mineralised sulphide intervals
	Whether core and chip samples have been	There is no known relationship between sample recovery and grade Geological logging is carried out on all drill holes with lithology,
	geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.	alteration, mineralisation, structure and veining recorded.
Logging	Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography.	Logging of RC samples records lithology, mineralogy, mineralisation, structures, weathering, colour and other noticeable features. Chip trays were photographed in wet form.
	The total length and percentage of the relevant intersections logged.	All drill holes are geologically logged in full and lithogeochemical information is collected by the field XRF unit. The data relating to the elements analysed is used to determine further information regarding the rock composition.
	If core, whether cut or sawn and whether quarter, half or all cores taken.	NA
	If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry.	RC samples are collected using acone or riffle splitter when available. Geological logging of RC chips is completed at site with representative chips being stored in drill chip trays.
	For all sample types, the nature, quality and appropriateness of the sample preparation technique.	RC Sampling: Sample preparation for RC chips follows a standard protocol. If a sample is wet or damp it is recorded. Most samples were dry.
Sub-sampling techniques and sample preparation		Samples were delivered by Legacy Minerals Holdings personnel to ALS Minerals Laboratory, Orange NSW. Sample preparation will comprise of an industry standard of drying, jaw crushing and pulverising to -75 microns (85% passing) (ALS code PUL-23). Pulverisers are washed with QAQC tests undertaken (PUL-QC). Samples are dried, crushed and pulverized to produce a homogenous representative sub-sample for analysis.
	Quality control procedures adopted for all subsampling stages to maximise representivity of samples.	Quality control procedures include submission of Certified Reference Materials (standards) and duplicates with each sample batch. QAQC results are routinely reviewed to identify and resolve any issues.
		RC Sampling: Field QC procedures maximise representivity of RC samples and involve the use of certified reference material as assay standards, along with blanks, duplicates and barren washes.
	Measures taken to ensure that the sampling is representative of the in-situ material collected,	Duplicate RC samples are captured using two separate sampling apertures on the splitter approximately every 50m.

	including for instance results for field duplicate/second-half sampling.	Should field duplicates indicate a possible nugget effect, where appropriate the retained bulk sample material is re-split and reassayed.				
	Whether sample sizes are appropriate to the grain size of the material being sampled.	The sample sizes are considered to be appropriate to correctly represent gold mineralisation and associated geology based on the style of mineralisation (quartz with minor sulphides), the thickness and consistency of the intersections and the sampling methodology.				
	The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or	All samples were analysed by ALS Global. Gold is determined using a 30g charge. The resultant prill is				
	total.	dissolved in aqua regia with gold determined by flame AAS.				
Quality of assay data and	For geophysical tools, spectrometres, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.	An Olympus Vanta pXRF is used to systematically analyse the RC sample onsite. One reading is taken per metre. Field calibration of the XRF instrument using standards is periodically performed (usually daily). The handheld pXRF results are only used for preliminary				
laboratory		assessment of element compositions, prior to the receipt of assay results from the certified laboratory.				
tests	Nature of quality control procedures adopted (e.g., standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (i.e., lack of bias) and precision have been established.	Laboratory QAQC involves the use of internal lab standards using certified reference material (CRMs), blanks and pulp duplicates as part of in-house procedures. The Company also submits a suite of CRMs, blanks where appropriate and selects appropriate samples for duplicates.				
		Sample preparation checks for fineness are performed by the laboratory to ensure the grind size of 85% passing 75µm is being attained.				
	The verification of significant intersections by either independent or alternative company personnel.	Significant intersections are verified by the Company's technical staff.				
	The use of twinned holes.	No twinned holes have been planned for the current drill programme.				
Verification of sampling and assaying	Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.	Primary data is captured onto a laptop through excel and using Datashed software and includes geological logging, sample data and QA/QC information. This data, together with the assay data, is stored both locally and entered into the LGM central online database which is managed by external consultants.				
		All primary assay data is received from the laboratory as electronic data files which are imported into sampling database with verification procedures in place. QAQC analysis is undertaken for each laboratory report				
	Discuss any adjustment to assay data.	No adjustments or calibrations will be made to any primary assay data collected for the purpose of reporting assay grades and mineralised intervals. For the geological analysis, standards and recognised factors may be used to calculate the oxide form assayed elements, or to calculate volatile free mineral levels in rocks.				
Location of data points	Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.	RC Drilling - A handheld Garmin GPSmap 65 was used to pick up collars with an averaged way point accuracy of 1m. Downhole surveys are conducted using a single shot camera approximately every 30m or downhole Gyro during drilling to record and monitor deviations of the hole from the planned dip and azimuth.				
	Specification of the grid system used.	The grid system used is GDA94, MGA Zone 55.				
	Quality and adequacy of topographic control.	Using government data topography and 2017 DTM data. A topographic surface has been created using this elevation data				
Data spacing and distribution	Data spacing for reporting of Exploration Results.	The results are at an early stage, reconnaissance drilling. The spacing and distribution of holes is not relevant to the drilling programs which are at this exploration stage rather than definition drilling.				
	Whether the data spacing, and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation	The completed drilling at the Project is not sufficient to establish the degree of geological and grade continuity to support the definition of Mineral Resource and Reserves and the classifications applied under the 2012 JORC code.				

	procedure(s) and classifications applied. Whether sample compositing has been applied.	
	Whether sample compositing has been applied.	No compositing has been applied to the exploration results.
Orientation of data in relation to geological structure	Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.	The drill holes are drilled to intersect the modelled mineralised zones at as near perpendicular orientation possible (unless otherwise stated). Drilling suggests a broadly sub vertical geometry, however the orientation of key structures may be locally variable and any relationship to mineralisation has yet to be identified.
	If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.	Estimated true width intervals at this early stage of drilling are possibly ~70% of downhole lengths
Sample security	The measures taken to ensure sample security.	All samples are bagged into tied calico bags, before being grouped into polyweave bags and transported to ALS Minerals Laboratory in Orange by Legacy Minerals personnel. All sample submissions are documented via ALS tracking system with results reported via email Sample pulps are returned to site and stored for an appropriate length of time. The Company has in place protocols to ensure data security.
Audits or reviews	The results of any audits or reviews of sampling techniques and data.	Sampling techniques and procedures are regularly reviewed internally, as is data. To date, no external audits have been completed on the drilling programme.

Section 2 Reporting of Exploration Results (Criteria in this section apply to all succeeding section)

Criteria	JORC Code Explanation	Commentary
Mineral Tenement and Land Status	Type, name/reference number, location and ownership including agreements or material issues with third parties including joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings. The security of the tenure held at the time of	The Harden Project is comprised of two granted Exploration Licenses: EL8809 and EL9257. Both licenses are owned 100% by Legacy Minerals Pty Ltd (a fully owned subsidiary of Legacy Minerals Holdings Limited). There are no royalties or encumbrances over the tenement areas. The land is primarily freehold land. There are no native title interests in the license area.
	reporting along with any known impediments to obtaining a licence to operate in the area.	The transmitter and receiver electrode positions are located to hand-held GPS accuracy, generally +-3m (UTM projection GDA94 Zone 55).
Exploration Done by Other Parties	Acknowledgment and appraisal of exploration by other parties.	RC Drilling - The RC drilling was planned by Legacy Minerals Holdings exploration staff in consultation with drilling contractor Durock Drilling.
Geology	Deposit type, geological setting and style of mineralisation	The Harden Gold Mine prospect is hosted within the Silurian Young Granodiorite. The prospect is prospective for high-grade gold mineralisation hosted within low-sulphide quartz veining of similar style to that which has been historically mined in the area.
Drill hole Information	A summary of all information material to the understanding of the exploration results including tabulation of the following information for all Material drill holes: • Easting and northing of the drill hole collar • Elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar • Dip and azimuth of the hole • Down hole length and interception depth • Hole length	See Table 1 in the body of the article
	If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.	N/A

Data aggregation	In reporting Exploration Results, weighting averaging techniques, maximum and/or	Exploration results reported for uncut gold grades, grades calculated by length weighted average
methods	minimum grade truncations (e.g., cutting of high grades) and cut-off grades are usually Material and should be stated.	
	Where aggregated intercepts incorporate short lengths of high-grade results and longer lengths of low-grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.	Reported intercepts (>0.2g/t Au) are calculated using a broad lower cut of 0.2g/t Au although grades lower than this may be present internally (internal dilution). No top cut has been used.
	The assumptions used for any reporting of metal equivalent values should be clearly stated.	No metal equivalents reported
Relationship between mineralisation widths and intercept lengths	These relationships are particularly important in the reporting of exploration results. If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect.	The mineralisation is structurally complex. Assay intersections are reported as down hole lengths. Drill holes are planned as perpendicular as possible to intersect the geological targets. At this early stage of drilling and geological knowledge of the project true widths are estimated to be approximately 70% of down hole intervals.
Diagrams	Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include, but not be limited to a plane view of drill hole collar locations and appropriate sectional views.	A prospect location map, cross section and long section are shown in the Company's Prospectus dated 28 July 2021 and within the body of this report.
Balanced Reporting	Where comprehensive reporting of all Exploration Results is not practical representative reporting of both low and high grades and/or widths should be practiced avoiding misleading reporting of Exploration Results.	Comprehensive reporting has been undertaken with all RC holes listed in the included table. See body of report and previous Legacy Minerals Holdings announcements. Historical exploration can be found in the Company's Prospectus dated 28 July 2021.
Other substantive exploration data	Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observation; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.	All material or meaningful data collected has been reported.
Further Work	The nature and scale of planned further work (e.g., tests for lateral extensions or depth extensions or large – scale step – out drilling). Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.	See body of report. See figures in body of report. Further exploration will be planned based on ongoing drill results, geophysical surveys and geological assessment of prospectivity.