

15 March 2023

BROAD COPPER MINERALISED ZONE INTERSECTED AT YANNERY

Highlights:

- **Copper mineralisation** intersected in all 15 RC holes drilled at Yannery prospect confirmed by pXRF analysis, 800m northeast of Whundo*
- Mineralised zone up to **100m wide** plunges to the north at 35 - 40 deg and remains open at depth
- The down dip portion of the mineralised zone remains largely untested
- Past drilling and historic mining highlights potential for high grade copper lodes within a broad mineralised envelope
- Historical production included **1,132 tonnes @ 21% Cu ore**
- Yannery is a typical Whundo cluster copper dominant VMS deposit
- Yannery adds potential for further expansion of the current Whundo project mineral resource of 3.6mt @ 1.2% Cu and 1.4% Zn
- A total 541 samples have been dispatched for laboratory analysis

GreenTech Metals Ltd (ASX: GRE), ('**GreenTech**' or 'the **Company**') is pleased to announce the drilling program at the Yannery prospect, part of the Company's Whundo Copper Project in Western Australia's Pilbara region, has concluded with the historically mined higher grade near surface mineralised horizon identified. The drilling has also provided preliminary evidence of a second mineralised zone potentially extending to depth.

Executive Director Thomas Reddicliffe commented: "Our recent maiden exploratory drill program at Yannery has not only confirmed significant copper mineralisation but has also provided important geospatial information relating to the nature and extent of the mineralisation. What we do know at this early stage is that Yannery is shaping up as another discrete Whundo cluster VMS deposit so we anticipate that the high-grade lodes reported both historically and more recently by Fox Resources will likely occur elsewhere within the larger mineralising event. Also, as at Whundo, we are seeing early evidence in the drilling of a second mineralised zone below that which was selectively mined. We are now looking forward to receiving the assay results to then be able to determine the next drill program required to unlock further potential at this prospect."

* Refer cautionary statement



ASX: GRE

BOARD & MANAGEMENT

Mark Potter
Non-executive Chairman

Thomas Reddicliffe
Executive Director

Guy Robertson
Non-executive Director

Rod Webster
Non-executive Director

Dan Smith
Company Secretary

CONTACT US

info@greentechmetals.com.au
greentechmetals.com.au

Level 8, 99 St Georges Tce, Perth WA 6000






Figure 1: Whundo project

Mining History

The Yannery prospect, located only ~800m from the main Whundo pits and 700m from Ayshia, was mined historically over two periods from 1920-1958 and 1952-1968. There are records of intermittent production in the period 1920-1958 of 1132 tonnes of copper ore **averaging 21% Cu**, and in the period 1952-1968 a further 1911.8 tonnes of cupreous ore **averaging 12.87% Cu** was reported to have been mined from the oxidised and supergene zone¹. Underground workings comprising an adit and numerous shafts are present which are limited to the near surface oxidised portion of the prospect.

¹Yannery Hill Copper mine, Karratha, City of Karratha, Western Australia, Australia (mindat.org)



Figure 2: Yannery copper mine tip, circa 1972

Past Exploration Activity

Exploration by Fox Resources Ltd in 2006 identified a mineralised zone within the Yannery prospect but peripheral to the historically mined area. This previous work by Fox included RC drilling for a total of nine holes and a fixed loop electro-magnetic (FLEM) survey. The Fox drill sample assay results included:

- Hole YNRC004 - 10m @ 2.05% Cu from 40m, including 3m @ 6.10% Cu
- Hole YNRC005 – 1m @ 3.16% Cu from 43m
- Hole YNRC007 – 10m @ 3.5% Cu from 39m, including 4m @ 8.3% from 41m²

Current Exploration

Greentech has expanded upon the previous drilling by Fox in 2006 aimed at determining the extent and tenor of the copper lodes that were historically selectively mined.

A 729m drilling program comprising 15 RC holes was conducted, many of which were shallow due to intersecting underground workings of which the locations were not accurately known. Details of the drilling are shown in Table 1.

²ASX Announcement Fox Resources Ltd, Down Hole & Surface Electromagnetic Surveys in Progress at Yannery 14 November 2012



Preliminary Drilling Results and Sampling

Initial visual results confirmed by the use of an Olympus Vanta pXRF analyser revealed a shallow copper mineralised horizon spatially consistent with the underground workings and mineralisation previously identified by drilling undertaken by Fox. This horizon plunges to the north at 35 -40 degrees and based on interpretation of drill intersections has a near surface **width of some 100m.**

The recent Greentech drilling also suggests evidence of a second copper mineralised zone at depth separate to and beneath the mineralised zone associated with the historic near surface workings. The extent and tenor of this deeper mineralisation is not clear from the drilling at this stage. To investigate this deeper mineralisation and the deeper extensions of the main mineralised horizon which currently remains largely untested, three of the deeper drill holes have been prepared for DHEM survey which will be completed in the coming days. These DHEM surveys are aimed at identifying additional targets that will potentially warrant follow-up drill testing.

A total of 541 drill samples have been dispatched to ALS Global Laboratories in Perth for analysis. Results will be reported following receipt and assessment of the results.




Figure 3: Yannery Interpreted EW section




Figure 4: Yannery Interpreted NS Section



Figure 5: Location of Yannery prospect relative to Ayshia

Bertram Prospect

The Company recently acquired the Bertram project, located just south of Whundo, covering approximately 16km². Fox Resources conducted exploration over the project area in 2008 and 2009 after concluding that there was potential for massive sulphide mineralisation within thin ultramafic horizons identified by their strong magnetic signature.




Figure 6: Bertram project

Fox undertook a VTEM survey over the Bertram area and identified four conductors proximal to previous historic drilling which intersected 1.8m at 3.4% Cu from 22m. Initial drilling of these targets intersected shallow, fresh massive and stringer nickel and copper sulphides. Greentech plans to undertake follow-up exploratory work on these targets.

This announcement is approved for release by the Board of Directors

ENDS

For Further Information:

Mr Thomas Reddicliffe
Executive Director
+61 8 9486 4036
Tom.Reddicliffe@greentechmetals.com.au

Mr George Ventouras
GM Business Development
+61 0 418 945 353

About GreenTech Metals Limited

The Company is an exploration and development company primarily established to discover, develop, and acquire Australian and overseas projects containing minerals and metals that are used in the battery storage and electric vehicle sectors. The Company's founding projects are focused on the underexplored nickel, copper and cobalt in the West Pilbara and Fraser Range Provinces.

The green energy transition that is currently underway will require a substantial increase in the supply of these minerals and metals for the electrification of the global vehicle fleet and for the massive investment in the electrical grid, renewable energy infrastructure and storage.

Competent Person Statement

Thomas Reddicliffe, BSc (Hons), MSc, a Director and Shareholder of the Company, is a Fellow of the AUSIMM, and has sufficient experience which is relevant to the style of mineralisation and type of deposit under consideration to qualify as a Competent Person as defined in the 2012 edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves'. Thomas Reddicliffe consents to the inclusion in the report of the information in the form and context in which it appears.

*Cautionary Statement

The Company notes that while the oxide mineral species malachite is readily observable in RC drill chips when present, the relative abundance of is particularly subjective due to the manner in which the logged chips are selected as only the chips are observed rather than the powdered fines. In this respect while the estimated percentage of malachite in mineralised intervals can be quite variable it never exceeded 15% and was more usually estimated at 1% – 2%. In relation to the disclosure of visual mineralisation, the Company cautions that visual estimates of oxide abundance should never be considered a proxy or substitute for laboratory analysis. Laboratory assay results are required to determine the widths and grade of mineralisation. The Company will update the market when laboratory analytical results become available for these samples.

Table 1. FOX Resources Drill Holes

Drill Hole Id	Easting_m	Northing_m	Grid	RL_m	Depth_m	Azimuth	Dip	Drill Type
YNRC003	492969	7669810	GDA94z50	143	92	6	74	RC
YNRC004	492972	7669797	GDA94z50	144	100	53	52	RC
YNRC005	492969	7669778	GDA94z50	144	100	67	79	RC
YNRC006	492969	7669770	GDA94z50	144	90	75	75	RC
YNRC007	492971	7669794	GDA94z50	144	70	120	67	RC
YNRC008	492970	7669800	GDA94z50	144	120	31	70	RC
YNRC009	492967	7669811	GDA94z50	143	125	352	70	RC

Table 2. Greentech Metals Drill Holes

HoleID	Easting_m*	Northing_m*	Grid	RL_m*	EOH	Azi_deg	Dip_deg	Drill Type
23GTRC002	492995	7669755	GDA94z50	140	24.0	3	-55	RC
23GTRC003	492996	7669743	GDA94z50	140	48.0	0	-90	RC
23GTRC004	492993	7669724	GDA94z50	140	30.0	0	-90	RC
23GTRC005	492999	7669760	GDA94z50	140	5.0	0	-90	RC
23GTRC006	493024	7669784	GDA94z50	135	60.0	0	-90	RC
23GTRC007	493068	7669795	GDA94z50	130	24.0	0	-90	RC
23GTRC008	493067	7669820	GDA94z50	130	24.0	0	-90	RC



HoleID	Easting_m*	Northing_m*	Grid	RL_m*	EOH	Azi_deg	Dip_deg	Drill Type
23GTRC009	492983	7669752	GDA94z50	140	45.0	3	-55	RC
23GTRC009A	492982	7669752	GDA94z50	140	72.0	3	-55	RC
23GTRC009B	492979	7669754	GDA94z50	140	33.0	3	-60	RC
23GTRC009C	492985	7669745	GDA94z50	140	102.0	3	-70	RC
23GTRC010	493063	7669795	GDA94z50	130	135.0	3	-55	RC
23GTRC011	493024	7669779	GDA94z50	135	31.0	3	-60	RC
23GTRC011A	493024	7669778	GDA94z50	135	96.0	3	-70	RC

Table 3. Assay Results Fox Resources Drilling

Hole_ID	Sample ID	Fromm	To m	Ag ppm	Au ppm	Co ppm	Cu pct	Zn pct	Pb pct	Fe pct	S pct	Sample Type	Sample Condition
YNRC003	ADA36255	0	1	-1	-0.01	10	0	0.004	0	1.6	-0.01	CHIPS	DRY
YNRC003	ADA36256	1	2	1	0.02	10	0	0.012	0	1.58	0.12	CHIPS	DRY
YNRC003	ADA36257	2	3	-1	0.03	10	0	0.004	0	1.8	-0.01	CHIPS	DRY
YNRC003	ADA36258	3	4	-1	-0.01	10	0	0.005	0	2.16	-0.01	CHIPS	DRY
YNRC003	ADA36259	4	5	-1	0.01	10	0	0.006	0	1.46	0.01	CHIPS	DRY
YNRC003	ADA36260	5	6	-1	0.02	10	0.01	0.012	0	2.3	0.01	CHIPS	DRY
YNRC003	ADA36261	6	7	1	0.03	30	0.02	0.021	0	4.44	0.01	CHIPS	DRY
YNRC003	ADA36262	7	8	-1	-0.01	40	0.02	0.06	0.01	5.15	0.04	CHIPS	DRY
YNRC003	ADA36263	8	9	-1	-0.01	20	0.01	0.034	0.01	5.01	0.02	CHIPS	DRY
YNRC003	ADA36264	9	10	-1	0.01	30	0	0.018	0	4.9	-0.01	CHIPS	DRY
YNRC003	ADA36265	10	11	-1	0.01	30	0.01	0.019	0	4.06	-0.01	CHIPS	DRY
YNRC003	ADA36266	11	12	-1	0.01	50	0.01	0.022	0	4.89	-0.01	CHIPS	DRY
YNRC003	ADA36267	12	13	-1	-0.01	80	0.01	0.023	0	5.38	-0.01	CHIPS	DRY
YNRC003	ADA36268	13	14	-1	0.02	60	0.01	0.019	0	5.16	-0.01	CHIPS	DRY
YNRC003	ADA36269	14	15	-1	-0.01	20	0	0.019	0	6.05	-0.01	CHIPS	DRY
YNRC003	ADA36270	15	16	-1	0.02	10	0	0.01	0	5.27	-0.01	CHIPS	DRY
YNRC003	ADA36271	16	17	-1	-0.01	10	0	0.013	0	6.73	-0.01	CHIPS	DRY
YNRC003	ADA36272	17	18	-1	-0.01	10	0	0.008	0	4.97	-0.01	CHIPS	DRY
YNRC003	ADA36273	18	19	-1	0.01	20	0.02	0.016	0	4.79	-0.01	CHIPS	DRY
YNRC003	ADA36274	19	20	-1	-0.01	10	0.01	0.022	0	5.49	-0.01	CHIPS	DRY
YNRC003	ADA36275	20	21	-1	-0.01	20	0.01	0.034	0	4.64	-0.01	CHIPS	DRY
YNRC003	ADA36276	21	22	-1	-0.01	20	0.01	0.049	0	4.01	-0.01	CHIPS	DRY
YNRC003	ADA36277	22	23	-1	-0.01	20	0.01	0.037	0	3.93	-0.01	CHIPS	DRY
YNRC003	ADA36278	23	24	-1	0.01	30	0.01	0.049	0	4.57	-0.01	CHIPS	DRY
YNRC003	ADA36279	24	25	-1	-0.01	20	0.01	0.046	0	6	-0.01	CHIPS	DRY
YNRC003	ADA36280	25	26	-1	0.01	20	0.01	0.08	0	11	-0.01	CHIPS	DRY
YNRC003	ADA36281	26	27	-1	-0.01	10	0	0.029	0	6.47	-0.01	CHIPS	DRY
YNRC003	ADA36282	27	28	-1	-0.01	20	0.01	0.032	0	6.25	-0.01	CHIPS	DRY
YNRC003	ADA36283	28	29	1	0.01	30	0.01	0.052	0	8.8	-0.01	CHIPS	DRY
YNRC003	ADA36284	29	30	-1	0.01	60	0.01	0.12	0	12.2	-0.01	CHIPS	DRY
YNRC003	ADA36285	30	31	-1	-0.01	50	0.01	0.073	0	10.9	-0.01	CHIPS	DRY
YNRC003	ADA36286	31	32	-1	-0.01	30	0.02	0.043	0	6.26	-0.01	CHIPS	DRY
YNRC003	ADA36287	32	33	1	-0.01	40	0.02	0.05	0	5.86	-0.01	CHIPS	DRY
YNRC003	ADA36288	33	34	-1	0.02	50	0.03	0.049	0	5.76	-0.01	CHIPS	DRY
YNRC003	ADA36289	34	35	-1	0.01	30	0.01	0.033	0	5.38	-0.01	CHIPS	DRY
YNRC003	ADA36290	35	36	-1	0.01	30	0	0.035	0	5.11	-0.01	CHIPS	DRY
YNRC003	ADA36291	36	37	-1	-0.01	110	0	0.057	0	10.35	-0.01	CHIPS	DRY
YNRC003	ADA36292	37	38	-1	-0.01	50	0	0.022	0	3.88	-0.01	CHIPS	DRY
YNRC003	ADA36293	38	39	-1	-0.01	90	0	0.022	0	3.45	-0.01	CHIPS	DRY
YNRC003	ADA36294	39	40	-1	-0.01	80	0.01	0.031	0	3.86	-0.01	CHIPS	DRY
YNRC003	ADA36295	40	41	-1	-0.01	60	0	0.036	0	5.01	-0.01	CHIPS	DRY



Hole_ID	Sample ID	Fromm	To m	Ag ppm	Au ppm	Co ppm	Cu pct	Zn pct	Pb pct	Fe pct	S pct	Sample Type	Sample Condition
YNRC003	ADA36296	41	42	-1	-0.01	30	0	0.025	0	5.28	-0.01	CHIPS	DRY
YNRC003	ADA36297	42	43	1	-0.01	30	0	0.024	0	4.51	0.07	CHIPS	DRY
YNRC003	ADA36298	43	44	-1	0.01	40	0	0.044	0	6.58	0.07	CHIPS	DRY
YNRC003	ADA36299	44	45	-1	-0.01	20	0	0.041	0	6.09	0.07	CHIPS	DRY
YNRC003	ADA36300	45	46	-1	-0.01	20	0.01	0.037	0	5.18	0.07	CHIPS	DRY
YNRC003	ADA36301	46	47	-1	-0.01	50	0	0.06	0	6.38	0.08	CHIPS	DRY
YNRC003	ADA36302	47	48	1	-0.01	30	0.01	0.046	0	4.69	0.06	CHIPS	DRY
YNRC003	ADA36303	48	49	-1	-0.01	30	0.02	0.075	0	7.89	0.07	CHIPS	DRY
YNRC003	ADA36304	49	50	-1	-0.01	10	0.01	0.027	0	4.81	0.06	CHIPS	DRY
YNRC003	ADA36305	50	51	-1	-0.01	30	0.01	0.06	0	4.08	0.08	CHIPS	DRY
YNRC003	ADA36306	51	52	-1	-0.01	10	0	0.036	0	5.6	0.09	CHIPS	DRY
YNRC003	ADA36307	52	53	-1	-0.01	20	0	0.036	0	5.2	0.08	CHIPS	DRY
YNRC003	ADA36308	53	54	1	-0.01	20	0	0.032	0	3.85	0.06	CHIPS	DRY
YNRC003	ADA36309	54	55	-1	-0.01	10	0	0.029	0	3.77	0.06	CHIPS	DRY
YNRC003	ADA36310	55	56	-1	-0.01	40	0	0.041	0	7.14	0.15	CHIPS	DRY
YNRC003	ADA36311	56	57	-1	-0.01	60	0.02	0.069	0	10.4	0.29	CHIPS	DRY
YNRC003	ADA36312	57	58	-1	-0.01	30	0.01	0.037	0	7.3	0.21	CHIPS	DRY
YNRC003	ADA36313	58	59	-1	0.01	30	0.01	0.039	0	8.85	0.21	CHIPS	DRY
YNRC003	ADA36314	59	60	-1	-0.01	100	0.01	0.044	0	15.25	0.2	CHIPS	DRY
YNRC003	ADA36315	60	61	-1	-0.01	30	0.01	0.034	0	10.05	0.4	CHIPS	DRY
YNRC003	ADA36316	61	62	-1	-0.01	30	0.03	0.024	0	10.1	0.95	CHIPS	DRY
YNRC003	ADA36317	62	63	-1	-0.01	20	0.01	0.017	0	7.9	0.6	CHIPS	DRY
YNRC003	ADA36318	63	64	-1	-0.01	10	0	0.013	0	6.74	0.24	CHIPS	DRY
YNRC003	ADA36319	64	65	-1	-0.01	20	0	0.015	0	7.68	0.23	CHIPS	DRY
YNRC003	ADA36320	65	66	-1	-0.01	10	0	0.013	0	6.25	0.19	CHIPS	DRY
YNRC003	ADA36321	66	67	-1	-0.01	10	0	0.015	0	6.47	0.17	CHIPS	DRY
YNRC003	ADA36322	67	68	-1	-0.01	10	0	0.015	0	8.29	0.14	CHIPS	DRY
YNRC003	ADA36323	68	69	-1	-0.01	20	0.01	0.023	0	12.3	0.39	CHIPS	DRY
YNRC003	ADA36324	69	70	2	0.02	190	0.72	3.03	0	29.7	19.65	CHIPS	DRY
YNRC003	ADA36325	70	71	2	0.01	220	1.01	2.82	0	35.8	24.9	CHIPS	DRY
YNRC003	ADA36326	71	72	1	0.02	130	0.57	2.07	0	25.9	15.55	CHIPS	DRY
YNRC003	ADA36327	72	73	2	-0.01	170	1.06	3.27	0	36.4	21.9	CHIPS	DRY
YNRC003	ADA36328	73	74	2	-0.01	130	1.1	2.02	0	34	15.6	CHIPS	DRY
YNRC003	ADA36329	74	75	1	-0.01	130	1.24	1.185	0	33.3	16.8	CHIPS	DRY
YNRC003	ADA36330	75	76	1	-0.01	130	0.8	0.454	0	34.6	16.7	CHIPS	DRY
YNRC003	ADA36331	76	77	2	0.01	150	1.07	1.745	0	38.8	18.15	CHIPS	DRY
YNRC003	ADA36332	77	78	1	-0.01	120	0.78	1.07	0	29.8	12.5	CHIPS	DRY
YNRC003	ADA36333	78	79	1	0.03	140	0.86	0.194	0	38.7	17.2	CHIPS	DRY
YNRC003	ADA36334	79	80	2	0.02	140	1.32	0.214	0	38.3	17.65	CHIPS	DRY
YNRC003	ADA36335	80	81	1	0.01	150	1.05	0.334	0	40.2	18.25	CHIPS	DRY
YNRC003	ADA36336	81	82	1	0.03	110	0.84	0.27	0	33.7	14.4	CHIPS	DRY
YNRC003	ADA36337	82	83	3	0.11	160	1.5	0.24	0.01	45.9	20.7	CHIPS	DRY
YNRC003	ADA36338	83	84	5	0.62	170	1.97	0.42	0	44.2	22	CHIPS	DRY
YNRC003	ADA36339	84	85	5	1.4	150	1.5	0.434	0	39.2	21.2	CHIPS	DRY
YNRC003	ADA36340	85	86	1	0.21	160	1	0.225	0	33.4	23.7	CHIPS	DRY
YNRC003	ADA36341	86	87	1	0.17	830	0.76	0.141	0	31.8	22.4	CHIPS	DRY
YNRC003	ADA36342	87	88	1	0.07	740	0.83	0.067	0	39.4	28.7	CHIPS	DRY
YNRC003	ADA36343	88	89	-1	0.02	270	0.55	0.086	0	32.8	13.6	CHIPS	DRY
YNRC003	ADA36344	89	90	-1	0.01	90	0.28	0.101	0	19.95	4.55	CHIPS	DRY
YNRC003	ADA36345	90	91	-1	0.01	40	0.07	0.064	0	13.35	1.66	CHIPS	DRY
YNRC003	ADA36346	91	92	-1	0.01	50	0.05	0.063	0	11.05	1.06	CHIPS	DRY
YNRC004	ADA36055	0	1	-1	0.06	10	0	0.004	0	2.1	0.01	CHIPS	DRY
YNRC004	ADA36056	1	2	1	0.04	-10	0	0.004	0	1.47	-0.01	CHIPS	DRY
YNRC004	ADA36057	2	3	1	0.08	10	0	0.004	0	1.56	-0.01	CHIPS	DRY
YNRC004	ADA36058	3	4	1	0.02	10	0	0.004	0	1.76	0.01	CHIPS	DRY



Hole_ID	Sample ID	Fromm	To m	Ag ppm	Au ppm	Co ppm	Cu pct	Zn pct	Pb pct	Fe pct	S pct	Sample Type	Sample Condition
YNRC004	ADA36059	4	5	-1	0.02	20	0	0.008	0	1.42	-0.01	CHIPS	DRY
YNRC004	ADA36060	5	6	-1	0.01	10	0	0.007	0	1.24	-0.01	CHIPS	DRY
YNRC004	ADA36061	6	7	-1	0.03	20	0.01	0.012	0	1.13	-0.01	CHIPS	DRY
YNRC004	ADA36062	7	8	-1	0.01	10	0.01	0.016	0	1.28	-0.01	CHIPS	DRY
YNRC004	ADA36063	8	9	-1	0.01	20	0.01	0.019	0	1.18	-0.01	CHIPS	DRY
YNRC004	ADA36064	9	10	-1	0.05	10	0.01	0.011	0	1.72	-0.01	CHIPS	DRY
YNRC004	ADA36065	10	11	-1	0.06	-10	0.01	0.007	0	2.24	-0.01	CHIPS	DRY
YNRC004	ADA36066	11	12	-1	-0.01	10	0.01	0.009	0	4.63	0.01	CHIPS	DRY
YNRC004	ADA36067	12	13	-1	0.01	-10	0.02	0.007	0	7.1	0.01	CHIPS	DRY
YNRC004	ADA36068	13	14	-1	0.01	-10	0.01	0.006	0	1.96	0.01	CHIPS	DRY
YNRC004	ADA36069	14	15	-1	0.01	-10	0.02	0.006	0	5.25	0.01	CHIPS	DRY
YNRC004	ADA36070	15	16	-1	0.01	-10	0.02	0.003	0	3.18	0.01	CHIPS	DRY
YNRC004	ADA36071	16	17	-1	0.01	-10	0.03	0.003	0	4.24	-0.01	CHIPS	DRY
YNRC004	ADA36072	17	18	-1	0.02	10	0.05	0.005	0	4.41	-0.01	CHIPS	DRY
YNRC004	ADA36073	18	19	-1	0.01	10	0.05	0.005	0	4.42	-0.01	CHIPS	DRY
YNRC004	ADA36074	19	20	-1	0.01	10	0.07	0.009	0	5.4	-0.01	CHIPS	DRY
YNRC004	ADA36075	20	21	-1	-0.01	10	0.04	0.01	0	3.6	-0.01	CHIPS	DRY
YNRC004	ADA36076	21	22	-1	-0.01	10	0.05	0.009	0	3.82	-0.01	CHIPS	DRY
YNRC004	ADA36077	22	23	-1	0.01	10	0.06	0.013	0	4.23	-0.01	CHIPS	DRY
YNRC004	ADA36078	23	24	2	0.01	10	0.05	0.058	0.02	3.84	0.06	CHIPS	DRY
YNRC004	ADA36079	24	25	1	0.02	20	0.03	0.013	0	2.94	-0.01	CHIPS	DRY
YNRC004	ADA36080	25	26	1	0.01	10	0.03	0.02	0	3.69	-0.01	CHIPS	DRY
YNRC004	ADA36081	26	27	-1	-0.01	40	0.07	0.038	0	7.79	-0.01	CHIPS	DRY
YNRC004	ADA36082	27	28	-1	-0.01	30	0.01	0.045	0	12.35	-0.01	CHIPS	DRY
YNRC004	ADA36083	28	29	-1	-0.01	20	0.01	0.02	0	8.08	-0.01	CHIPS	DRY
YNRC004	ADA36084	29	30	-1	-0.01	20	0.01	0.02	0	4.17	-0.01	CHIPS	DRY
YNRC004	ADA36085	30	31	-1	0.01	60	0.02	0.037	0	9.44	-0.01	CHIPS	DRY
YNRC004	ADA36086	31	32	-1	-0.01	30	0.01	0.024	0	4.69	-0.01	CHIPS	DRY
YNRC004	ADA36087	32	33	-1	-0.01	60	0.06	0.02	0	5.65	-0.01	CHIPS	DRY
YNRC004	ADA36088	33	34	-1	-0.01	20	0.22	0.011	0	3.98	-0.01	CHIPS	DRY
YNRC004	ADA36089	34	35	-1	-0.01	60	0.29	0.015	0	4.74	-0.01	CHIPS	DRY
YNRC004	ADA36090	35	36	-1	0.01	10	0.18	0.003	0	6.69	0.01	CHIPS	DRY
YNRC004	ADA36091	36	37	1	0.01	-10	0.08	0.001	0	2.4	0.02	CHIPS	DRY
YNRC004	ADA36092	37	38	-1	-0.01	-10	0.12	0.001	0	1.07	0.13	CHIPS	DRY
YNRC004	ADA36093	38	39	-1	0.01	-10	0.16	0.005	0.01	3.83	0.09	CHIPS	DRY
YNRC004	ADA36094	39	40	1	0.04	10	0.25	0.005	0.01	1.87	0.04	CHIPS	DRY
YNRC004	ADA36095	40	41	3	0.08	10	6.07	0.004	0.01	4.34	0.08	CHIPS	DRY
YNRC004	ADA36096	41	42	11	0.35	10	9.45	0.002	0.01	22.6	0.21	CHIPS	DRY
YNRC004	ADA36097	42	43	3	0.04	10	2.77	0.002	0	1.44	0.07	CHIPS	DRY
YNRC004	ADA36098	43	44	3	-0.01	-10	0.41	0.001	0	1.38	0.02	CHIPS	DRY
YNRC004	ADA36099	44	45	-1	-0.01	20	0.36	0.004	0	5.35	0.01	CHIPS	DRY
YNRC004	ADA36100	45	46	-1	-0.01	30	0.33	0.007	0	6.64	-0.01	CHIPS	DRY
YNRC004	ADA36101	46	47	-1	-0.01	20	0.18	0.005	0	4.41	-0.01	CHIPS	DRY
YNRC004	ADA36102	47	48	-1	0.01	30	0.24	0.009	0	4.56	0.01	CHIPS	DRY
YNRC004	ADA36103	48	49	-1	-0.01	60	0.44	0.018	0	5.78	-0.01	CHIPS	DRY
YNRC004	ADA36104	49	50	-1	-0.01	20	0.29	0.015	0	5.02	0.01	CHIPS	DRY
YNRC004	ADA36105	50	51	-1	-0.01	40	0.11	0.024	0	4.25	-0.01	CHIPS	DRY
YNRC004	ADA36106	51	52	1	-0.01	60	0.03	0.051	0	9.38	-0.01	CHIPS	DRY
YNRC004	ADA36107	52	53	-1	-0.01	70	0.02	0.044	0	11.3	-0.01	CHIPS	DRY
YNRC004	ADA36108	53	54	-1	-0.01	70	0.03	0.05	0	11.5	0.01	CHIPS	DRY
YNRC004	ADA36109	54	55	-1	-0.01	70	0.01	0.053	0	9.79	-0.01	CHIPS	DRY
YNRC004	ADA36110	55	56	-1	0.02	50	0	0.03	0	9.38	0.03	CHIPS	DRY
YNRC004	ADA36111	56	57	-1	0.01	60	0	0.042	0	9.47	-0.01	CHIPS	DRY
YNRC004	ADA36112	57	58	-1	-0.01	60	0.01	0.078	0.01	10.4	0.02	CHIPS	DRY
YNRC004	ADA36113	58	59	-1	-0.01	60	0	0.056	0	8.96	0.01	CHIPS	DRY



Hole_ID	Sample ID	Fromm	To m	Ag ppm	Au ppm	Co ppm	Cu pct	Zn pct	Pb pct	Fe pct	S pct	Sample Type	Sample Condition
YNRC004	ADA36114	59	60	-1	-0.01	70	0	0.053	0	10.25	-0.01	CHIPS	DRY
YNRC004	ADA36115	60	61	-1	0.01	50	0	0.027	0	7.36	-0.01	CHIPS	DRY
YNRC004	ADA36116	61	62	-1	-0.01	50	0.01	0.028	0	8.17	0.04	CHIPS	DRY
YNRC004	ADA36117	62	63	-1	-0.01	30	0.01	0.019	0	5.61	0.11	CHIPS	DRY
YNRC004	ADA36118	63	64	-1	-0.01	20	0	0.015	0	5.95	-0.01	CHIPS	DRY
YNRC004	ADA36119	64	65	-1	-0.01	20	0.01	0.02	0	6.77	0.02	CHIPS	DRY
YNRC004	ADA36120	65	66	-1	-0.01	20	0.01	0.022	0	7.1	0.01	CHIPS	DRY
YNRC004	ADA36121	66	67	-1	0.01	20	0	0.026	0	5.78	-0.01	CHIPS	DRY
YNRC004	ADA36122	67	68	-1	-0.01	20	0	0.015	0	6.08	-0.01	CHIPS	DRY
YNRC004	ADA36123	68	69	-1	-0.01	20	0	0.02	0	7.04	-0.01	CHIPS	DRY
YNRC004	ADA36124	69	70	-1	0.01	30	0.01	0.032	0	8.42	-0.01	CHIPS	DRY
YNRC004	ADA36125	70	71	-1	0.01	50	0	0.035	0	7.33	0.14	CHIPS	DRY
YNRC004	ADA36126	71	72	-1	0.01	10	0	0.013	0	3.69	0.01	CHIPS	DRY
YNRC004	ADA36127	72	73	-1	0.01	30	0	0.039	0	7.96	-0.01	CHIPS	DRY
YNRC004	ADA36128	73	74	-1	-0.01	70	0.01	0.077	0	13.5	0.03	CHIPS	DRY
YNRC004	ADA36129	74	75	-1	-0.01	80	0.01	0.076	0	16.05	0.06	CHIPS	DRY
YNRC004	ADA36130	75	76	-1	-0.01	80	0	0.057	0	15.35	0.18	CHIPS	DRY
YNRC004	ADA36131	76	77	-1	-0.01	70	0.01	0.056	0	15.25	0.22	CHIPS	DRY
YNRC004	ADA36132	77	78	-1	-0.01	90	0.02	0.07	0	15.5	0.69	CHIPS	DRY
YNRC004	ADA36133	78	79	-1	-0.01	80	0.01	0.071	0	15.25	0.47	CHIPS	DRY
YNRC004	ADA36134	79	80	-1	-0.01	110	0	0.128	0	18.75	0.16	CHIPS	DRY
YNRC004	ADA36135	80	81	-1	-0.01	110	0	0.098	0	18.35	0.28	CHIPS	DRY
YNRC004	ADA36136	81	82	-1	-0.01	110	0	0.126	0	21.5	0.2	CHIPS	DRY
YNRC004	ADA36137	82	83	-1	-0.01	60	0	0.065	0	9.82	0.1	CHIPS	DRY
YNRC004	ADA36138	83	84	-1	-0.01	50	0.01	0.05	0	11	0.09	CHIPS	DRY
YNRC004	ADA36139	84	85	-1	-0.01	30	0	0.025	0	5.91	0.09	CHIPS	DRY
YNRC004	ADA36140	85	86	-1	-0.01	60	0	0.074	0	11.6	0.15	CHIPS	DRY
YNRC004	ADA36141	86	87	-1	-0.01	70	0	0.079	0	11.7	0.22	CHIPS	DRY
YNRC004	ADA36142	87	88	-1	0.01	70	0.01	0.095	0	11.85	0.22	CHIPS	DRY
YNRC004	ADA36143	88	89	-1	0.01	60	0.01	0.05	0	10.35	0.38	CHIPS	DRY
YNRC004	ADA36144	89	90	-1	0.02	60	0	0.05	0	9.19	0.09	CHIPS	DRY
YNRC004	ADA36145	90	91	-1	0.02	70	0	0.064	0	12.1	0.08	CHIPS	DRY
YNRC004	ADA36146	91	92	-1	0.01	40	0	0.021	0	6.58	0.02	CHIPS	DRY
YNRC004	ADA36147	92	93	1	-0.01	20	0	0.013	0	5.18	0.02	CHIPS	DRY
YNRC004	ADA36148	93	94	1	-0.01	30	0	0.02	0	5.09	0.01	CHIPS	DRY
YNRC004	ADA36149	94	95	-1	-0.01	70	0.01	0.045	0	9.27	0.2	CHIPS	DRY
YNRC004	ADA36150	95	96	-1	-0.01	30	0	0.014	0	5.61	0.03	CHIPS	DRY
YNRC004	ADA36151	96	97	-1	-0.01	30	0	0.019	0	6.05	0.06	CHIPS	DRY
YNRC004	ADA36152	97	98	-1	-0.01	40	0	0.015	0	9.55	0.02	CHIPS	DRY
YNRC004	ADA36153	98	99	-1	-0.01	30	0	0.012	0	7.39	0.02	CHIPS	DRY
YNRC004	ADA36154	99	100	-1	-0.01	60	0	0.014	0	8.27	0.01	CHIPS	DRY
YNRC005	ADA36155	0	1	-1	-0.01	30	0.01	0.01	0	2.97	0.03	CHIPS	DRY
YNRC005	ADA36156	1	2	-1	0.01	20	0.01	0.009	0	2.27	0.01	CHIPS	DRY
YNRC005	ADA36157	2	3	-1	0.01	10	0	0.004	0	1.29	0.01	CHIPS	DRY
YNRC005	ADA36158	3	4	1	0.06	20	0.01	0.005	0	1.12	0.03	CHIPS	DRY
YNRC005	ADA36159	4	5	-1	-0.01	10	0	0.002	0	0.83	-0.01	CHIPS	DRY
YNRC005	ADA36160	5	6	-1	0.01	10	0.01	0.006	0	0.92	-0.01	CHIPS	DRY
YNRC005	ADA36161	6	7	-1	0.01	10	0.01	0.009	0	1.9	0.01	CHIPS	DRY
YNRC005	ADA36162	7	8	-1	0.05	-10	0.01	0.006	0	2.91	-0.01	CHIPS	DRY
YNRC005	ADA36163	8	9	-1	0.02	-10	0.01	0.012	0	7.29	0.01	CHIPS	DRY
YNRC005	ADA36164	9	10	-1	0.01	-10	0.01	0.002	0	4.01	0.01	CHIPS	DRY
YNRC005	ADA36165	10	11	-1	0.01	-10	0.01	0.002	0	3.07	0.01	CHIPS	DRY
YNRC005	ADA36166	11	12	-1	0.02	-10	0.01	0.003	0	2.58	0.01	CHIPS	DRY
YNRC005	ADA36167	12	13	-1	-0.01	-10	0.01	0.002	0	1.94	-0.01	CHIPS	DRY
YNRC005	ADA36168	13	14	-1	-0.01	-10	0.01	0.002	0	2.4	0.01	CHIPS	DRY



Hole_ID	Sample ID	Fromm	To m	Ag ppm	Au ppm	Co ppm	Cu pct	Zn pct	Pb pct	Fe pct	S pct	Sample Type	Sample Condition
YNRC005	ADA36169	14	15	-1	-0.01	-10	0.05	0.003	0	2.99	0.01	CHIPS	DRY
YNRC005	ADA36170	15	16	-1	-0.01	-10	0.1	0.045	0.02	3.84	0.06	CHIPS	DRY
YNRC005	ADA36171	16	17	-1	-0.01	10	0.07	0.009	0	4.04	-0.01	CHIPS	DRY
YNRC005	ADA36172	17	18	-1	0.01	10	0.05	0.009	0	4.02	-0.01	CHIPS	DRY
YNRC005	ADA36173	18	19	-1	-0.01	10	0.03	0.005	0	2.89	-0.01	CHIPS	DRY
YNRC005	ADA36174	19	20	-1	0.01	10	0.05	0.008	0	4.16	-0.01	CHIPS	DRY
YNRC005	ADA36175	20	21	-1	-0.01	30	0.01	0.016	0	5.2	-0.01	CHIPS	DRY
YNRC005	ADA36176	21	22	-1	-0.01	40	0.01	0.024	0	9.81	-0.01	CHIPS	DRY
YNRC005	ADA36177	22	23	-1	-0.01	20	0	0.02	0	11.35	0.01	CHIPS	DRY
YNRC005	ADA36178	23	24	-1	-0.01	20	0.01	0.029	0	11.15	0.01	CHIPS	DRY
YNRC005	ADA36179	24	25	-1	-0.01	40	0	0.071	0	11.65	0.01	CHIPS	DRY
YNRC005	ADA36180	25	26	3	-0.01	40	0.02	0.036	0	5.59	0.01	CHIPS	DRY
YNRC005	ADA36181	26	27	-1	0.01	50	0.02	0.059	0	9.9	0.01	CHIPS	DRY
YNRC005	ADA36182	27	28	-1	0.01	40	0.01	0.045	0	9.52	0.01	CHIPS	DRY
YNRC005	ADA36183	28	29	-1	0.01	60	0.01	0.048	0	11.2	0.01	CHIPS	DRY
YNRC005	ADA36184	29	30	-1	-0.01	70	0	0.062	0	11.6	0.01	CHIPS	DRY
YNRC005	ADA36185	30	31	-1	-0.01	20	0.01	0.015	0	3.8	0.01	CHIPS	DRY
YNRC005	ADA36186	31	32	-1	0.02	60	0.11	0.018	0	4.66	0.01	CHIPS	DRY
YNRC005	ADA36187	32	33	-1	0.01	120	0.49	0.042	0	8.1	0.01	CHIPS	DRY
YNRC005	ADA36188	33	34	-1	-0.01	70	0.28	0.022	0	4.63	0.01	CHIPS	DRY
YNRC005	ADA36189	34	35	-1	-0.01	200	0.15	0.008	0	5.23	0.01	CHIPS	DRY
YNRC005	ADA36190	35	36	-1	-0.01	10	0.16	0.006	0	6.52	0.01	CHIPS	DRY
YNRC005	ADA36191	36	37	-1	-0.01	10	0.13	0.008	0	8.2	0.01	CHIPS	DRY
YNRC005	ADA36192	37	38	-1	-0.01	10	0.08	0.008	0	6.29	0.01	CHIPS	DRY
YNRC005	ADA36193	38	39	-1	-0.01	-10	0.07	0.006	0	4.25	0.03	CHIPS	DRY
YNRC005	ADA36194	39	40	-1	0.01	-10	0.04	0.003	0	1.16	0.06	CHIPS	DRY
YNRC005	ADA36195	40	41	-1	-0.01	-10	0.04	0.002	0	0.48	0.06	CHIPS	DRY
YNRC005	ADA36196	41	42	1	-0.01	-10	0.07	0.001	0	0.31	0.03	CHIPS	DRY
YNRC005	ADA36197	42	43	-1	-0.01	-10	0.09	0.001	0	0.28	0.02	CHIPS	DRY
YNRC005	ADA36198	43	44	33	0.03	30	3.16	0.005	0.01	8.72	1.04	CHIPS	DRY
YNRC005	ADA36199	44	45	1	-0.01	10	0.25	0.004	0	2.98	0.02	CHIPS	DRY
YNRC005	ADA36200	45	46	1	-0.01	30	0.33	0.008	0	6.17	0.01	CHIPS	DRY
YNRC005	ADA36201	46	47	-1	-0.01	30	0.18	0.043	0.01	6.37	0.05	CHIPS	DRY
YNRC005	ADA36202	47	48	1	-0.01	20	0.21	0.008	0	4.68	0.01	CHIPS	DRY
YNRC005	ADA36203	48	49	1	-0.01	30	0.31	0.018	0	6.72	0.01	CHIPS	DRY
YNRC005	ADA36204	49	50	1	-0.01	40	0.13	0.028	0	8.95	0.04	CHIPS	DRY
YNRC005	ADA36205	50	51	-1	-0.01	10	0.02	0.02	0	7.19	0.17	CHIPS	DRY
YNRC005	ADA36206	51	52	-1	-0.01	10	0.01	0.015	0	6.45	0.18	CHIPS	DRY
YNRC005	ADA36207	52	53	-1	-0.01	20	0.01	0.015	0	7.65	1.76	CHIPS	DRY
YNRC005	ADA36208	53	54	-1	-0.01	10	0	0.018	0	6.64	0.56	CHIPS	DRY
YNRC005	ADA36209	54	55	-1	-0.01	20	0	0.032	0	7.25	0.97	CHIPS	DRY
YNRC005	ADA36210	55	56	-1	-0.01	40	0.01	0.021	0	8.49	1.02	CHIPS	DRY
YNRC005	ADA36211	56	57	-1	-0.01	70	0	0.087	0	11.45	0.13	CHIPS	DRY
YNRC005	ADA36212	57	58	-1	-0.01	70	0	0.096	0	10.15	0.02	CHIPS	DRY
YNRC005	ADA36213	58	59	-1	-0.01	180	0	0.257	0	12.9	0.03	CHIPS	DRY
YNRC005	ADA36214	59	60	-1	-0.01	110	0	0.172	0	10.8	0.05	CHIPS	DRY
YNRC005	ADA36215	60	61	1	-0.01	110	0	0.156	0	11.6	0.04	CHIPS	DRY
YNRC005	ADA36216	61	62	-1	-0.01	50	0	0.07	0	5.54	0.03	CHIPS	DRY
YNRC005	ADA36217	62	63	-1	-0.01	60	0	0.083	0	9.45	0.04	CHIPS	DRY
YNRC005	ADA36218	63	64	-1	-0.01	50	0	0.073	0	7.56	0.05	CHIPS	DRY
YNRC005	ADA36219	64	65	-1	-0.01	90	0	0.128	0	9.59	0.04	CHIPS	DRY
YNRC005	ADA36220	65	66	-1	-0.01	40	0	0.039	0	7.33	0.02	CHIPS	DRY
YNRC005	ADA36221	66	67	-1	-0.01	50	0	0.034	0	7.88	0.03	CHIPS	DRY
YNRC005	ADA36222	67	68	-1	-0.01	40	0	0.024	0	7.05	0.01	CHIPS	DRY
YNRC005	ADA36223	68	69	1	-0.01	30	0	0.019	0	7.15	0.02	CHIPS	DRY



Hole_ID	Sample ID	Fromm	To m	Ag ppm	Au ppm	Co ppm	Cu pct	Zn pct	Pb pct	Fe pct	S pct	Sample Type	Sample Condition
YNRC005	ADA36224	69	70	-1	-0.01	40	0	0.021	0	7.44	0.03	CHIPS	DRY
YNRC005	ADA36225	70	71	-1	-0.01	40	0	0.021	0	7.19	0.01	CHIPS	DRY
YNRC005	ADA36226	71	72	-1	-0.01	40	0	0.02	0	7.54	0.03	CHIPS	DRY
YNRC005	ADA36227	72	73	-1	-0.01	30	0	0.023	0	5.12	0.02	CHIPS	DRY
YNRC005	ADA36228	73	74	-1	-0.01	50	0	0.037	0	9.41	0.15	CHIPS	DRY
YNRC005	ADA36229	74	75	-1	-0.01	50	0.02	0.036	0	11.75	0.92	CHIPS	DRY
YNRC005	ADA36230	75	76	-1	-0.01	50	0.01	0.034	0	12.3	0.41	CHIPS	DRY
YNRC005	ADA36231	76	77	-1	-0.01	70	0.01	0.061	0	14.2	0.4	CHIPS	DRY
YNRC005	ADA36232	77	78	-1	-0.01	50	0.01	0.044	0	12.25	0.63	CHIPS	DRY
YNRC005	ADA36233	78	79	-1	-0.01	110	0.01	0.106	0	16.6	0.32	CHIPS	DRY
YNRC005	ADA36234	79	80	-1	-0.01	120	0.01	0.136	0.01	16.05	0.46	CHIPS	DRY
YNRC005	ADA36235	80	81	1	-0.01	100	0.02	0.134	0	15.25	0.5	CHIPS	DRY
YNRC005	ADA36236	81	82	-1	-0.01	90	0.06	0.126	0	12.85	1.4	CHIPS	DRY
YNRC005	ADA36237	82	83	1	-0.01	50	0.02	0.082	0	11.65	0.78	CHIPS	DRY
YNRC005	ADA36238	83	84	-1	-0.01	60	0.02	0.085	0	10.6	0.68	CHIPS	DRY
YNRC005	ADA36239	84	85	-1	-0.01	80	0.03	0.076	0	12.35	0.77	CHIPS	DRY
YNRC005	ADA36240	85	86	-1	-0.01	80	0.02	0.082	0	10.9	0.44	CHIPS	DRY
YNRC005	ADA36241	86	87	-1	-0.01	120	0.04	0.128	0	14.75	1.02	CHIPS	DRY
YNRC005	ADA36242	87	88	-1	-0.01	50	0	0.054	0	7.55	0.03	CHIPS	DRY
YNRC005	ADA36243	88	89	1	-0.01	30	0	0.027	0	5.27	0.02	CHIPS	DRY
YNRC005	ADA36244	89	90	-1	-0.01	20	0	0.018	0	3.89	0.01	CHIPS	DRY
YNRC005	ADA36245	90	91	1	-0.01	20	0	0.01	0	5.1	0.01	CHIPS	DRY
YNRC005	ADA36246	91	92	-1	-0.01	20	0	0.014	0	6.34	0.01	CHIPS	DRY
YNRC005	ADA36247	92	93	-1	-0.01	20	0	0.009	0	4.65	0.02	CHIPS	DRY
YNRC005	ADA36248	93	94	1	-0.01	20	0	0.012	0	5.13	0.01	CHIPS	DRY
YNRC005	ADA36249	94	95	-1	-0.01	20	0	0.011	0	4.75	0.01	CHIPS	DRY
YNRC005	ADA36250	95	96	-1	-0.01	30	0	0.018	0	5.57	0.01	CHIPS	DRY
YNRC005	ADA36251	96	97	-1	-0.01	20	0	0.014	0	5	0.01	CHIPS	DRY
YNRC005	ADA36252	97	98	-1	-0.01	30	0	0.016	0	6.53	0.01	CHIPS	DRY
YNRC005	ADA36253	98	99	-1	-0.01	20	0	0.015	0	6.85	0.12	CHIPS	DRY
YNRC005	ADA36254	99	100	-1	-0.01	10	0	0.009	0	5.5	0.1	CHIPS	DRY
YNRC006	ADA36347	0	1	-1	0.01	10	0.02	0.028	0	3.17	0.36	CHIPS	DRY
YNRC006	ADA36348	1	2	-1	0.01	10	0.01	0.014	0	2.36	0.15	CHIPS	DRY
YNRC006	ADA36349	2	3	-1	0.03	10	0.02	0.025	0	3.02	0.33	CHIPS	DRY
YNRC006	ADA36350	3	4	-1	0.02	-10	0.01	0.004	0	1.5	0.08	CHIPS	DRY
YNRC006	ADA36351	4	5	-1	0.02	-10	0	0.004	0	1.26	0.07	CHIPS	DRY
YNRC006	ADA36352	5	6	-1	0.01	-10	0.01	0.009	0	2.27	0.06	CHIPS	DRY
YNRC006	ADA36353	6	7	-1	0.01	-10	0.01	0.005	0	3.2	0.03	CHIPS	DRY
YNRC006	ADA36354	7	8	-1	0.03	-10	0.01	0.003	0	6.51	0.03	CHIPS	DRY
YNRC006	ADA36355	8	9	-1	0.03	-10	0	0.001	0	1.58	0.01	CHIPS	DRY
YNRC006	ADA36356	9	10	-1	0.01	-10	0.01	-0.001	0	0.9	0.01	CHIPS	DRY
YNRC006	ADA36357	10	11	-1	0.01	-10	0.01	-0.001	0	2.35	-0.01	CHIPS	DRY
YNRC006	ADA36358	11	12	-1	0.01	10	0.16	0.014	0	9.77	0.01	CHIPS	DRY
YNRC006	ADA36359	12	13	-1	-0.01	20	0.22	0.027	0	12.85	0.01	CHIPS	DRY
YNRC006	ADA36360	13	14	-1	0.01	40	0.13	0.045	0	12.5	0.01	CHIPS	DRY
YNRC006	ADA36361	14	15	-1	-0.01	20	0.1	0.036	0	12.9	-0.01	CHIPS	DRY
YNRC006	ADA36362	15	16	1	-0.01	50	0.12	0.086	0.04	11.95	0.16	CHIPS	DRY
YNRC006	ADA36363	16	17	-1	-0.01	30	0.01	0.031	0	9.12	0.01	CHIPS	DRY
YNRC006	ADA36364	17	18	-1	-0.01	20	0.01	0.017	0	5.35	0.01	CHIPS	DRY
YNRC006	ADA36365	18	19	-1	-0.01	40	0.01	0.021	0	10.9	0.01	CHIPS	DRY
YNRC006	ADA36366	19	20	-1	-0.01	50	0	0.038	0	11.5	0.01	CHIPS	DRY
YNRC006	ADA36367	20	21	-1	-0.01	20	0.01	0.024	0	6.79	0.01	CHIPS	DRY
YNRC006	ADA36368	21	22	-1	0.05	10	0	0.024	0	5	-0.01	CHIPS	DRY
YNRC006	ADA36369	22	23	-1	-0.01	10	0	0.027	0	5.18	0.01	CHIPS	DRY
YNRC006	ADA36370	23	24	-1	-0.01	10	0	0.02	0	5.22	0.01	CHIPS	DRY



Hole_ID	Sample ID	Fromm	To m	Ag ppm	Au ppm	Co ppm	Cu pct	Zn pct	Pb pct	Fe pct	S pct	Sample Type	Sample Condition
YNRC006	ADA36371	24	25	-1	-0.01	10	0	0.022	0	5.18	-0.01	CHIPS	DRY
YNRC006	ADA36372	25	26	-1	-0.01	-10	0	0.005	0	1.82	-0.01	CHIPS	DRY
YNRC006	ADA36373	26	27	-1	-0.01	60	0.06	0.027	0	6.24	-0.01	CHIPS	DRY
YNRC006	ADA36374	27	28	1	-0.01	30	0.24	0.021	0	4.92	-0.01	CHIPS	DRY
YNRC006	ADA36375	28	29	1	-0.01	120	0.13	0.012	0	7.36	0.01	CHIPS	DRY
YNRC006	ADA36376	29	30	-1	0.01	30	0.13	0.005	0	7.23	0.02	CHIPS	DRY
YNRC006	ADA36377	30	31	-1	0.01	-10	0.23	0.006	0	17.1	0.06	CHIPS	DRY
YNRC006	ADA36378	31	32	-1	0.07	-10	0.15	0.003	0	5.01	0.05	CHIPS	DRY
YNRC006	ADA36379	32	33	-1	0.12	10	0.84	0.004	0.01	22.3	0.13	CHIPS	DRY
YNRC006	ADA36380	33	34	-1	0.01	-10	0.13	-0.001	0	1.39	0.11	CHIPS	DRY
YNRC006	ADA36381	34	35	1	-0.01	10	0.24	0.005	0.01	5.72	0.05	CHIPS	DRY
YNRC006	ADA36382	35	36	-1	0.01	40	0.21	0.017	0	12.65	0.02	CHIPS	DRY
YNRC006	ADA36383	36	37	-1	0.01	50	0.2	0.016	0	11.7	0.01	CHIPS	DRY
YNRC006	ADA36384	37	38	-1	-0.01	30	0.1	0.007	0	5.91	-0.01	CHIPS	DRY
YNRC006	ADA36385	38	39	-1	-0.01	10	0.06	0.004	0	3.96	-0.01	CHIPS	DRY
YNRC006	ADA36386	39	40	-1	-0.01	10	0.04	0.003	0	3.49	-0.01	CHIPS	DRY
YNRC006	ADA36387	40	41	-1	-0.01	10	0.08	0.007	0	5.29	-0.01	CHIPS	DRY
YNRC006	ADA36388	41	42	-1	-0.01	20	0.16	0.008	0	4.91	-0.01	CHIPS	DRY
YNRC006	ADA36389	42	43	-1	-0.01	10	0.09	0.006	0	3.53	-0.01	CHIPS	DRY
YNRC006	ADA36390	43	44	1	-0.01	20	0.13	0.009	0	4.42	-0.01	CHIPS	DRY
YNRC006	ADA36391	44	45	-1	-0.01	10	0.09	0.008	0	3.46	0.01	CHIPS	DRY
YNRC006	ADA36392	45	46	-1	-0.01	20	0.08	0.015	0	5.18	-0.01	CHIPS	DRY
YNRC006	ADA36393	46	47	-1	-0.01	50	0.01	0.028	0	10.55	0.05	CHIPS	DRY
YNRC006	ADA36394	47	48	-1	-0.01	20	0.02	0.021	0	7.4	0.02	CHIPS	DRY
YNRC006	ADA36395	48	49	-1	-0.01	20	0	0.021	0	6.38	0.01	CHIPS	DRY
YNRC006	ADA36396	49	50	1	-0.01	20	0.01	0.084	0.04	6.83	0.14	CHIPS	DRY
YNRC006	ADA36397	50	51	-1	-0.01	10	0	0.019	0	5.95	0.04	CHIPS	DRY
YNRC006	ADA36398	51	52	-1	-0.01	10	0	0.016	0	5.88	0.6	CHIPS	DRY
YNRC006	ADA36399	52	53	-1	-0.01	10	0	0.024	0	5.59	0.24	CHIPS	DRY
YNRC006	ADA36400	53	54	-1	-0.01	40	0.01	0.07	0	10.6	0.71	CHIPS	DRY
YNRC006	ADA36401	54	55	-1	-0.01	60	0.02	0.064	0	10.55	0.14	CHIPS	DRY
YNRC006	ADA36402	55	56	-1	-0.01	50	0.01	0.053	0	10.7	0.02	CHIPS	DRY
YNRC006	ADA36403	56	57	-1	-0.01	80	0.01	0.099	0	12.35	0.02	CHIPS	DRY
YNRC006	ADA36404	57	58	-1	-0.01	110	0.01	0.136	0	14.55	0.04	CHIPS	DRY
YNRC006	ADA36405	58	59	-1	-0.01	110	0.01	0.083	0	13.2	0.05	CHIPS	DRY
YNRC006	ADA36406	59	60	-1	-0.01	110	0.01	0.068	0	14.4	0.1	CHIPS	DRY
YNRC006	ADA36407	60	61	-1	-0.01	70	0	0.034	0	9.9	0.03	CHIPS	DRY
YNRC006	ADA36408	61	62	-1	-0.01	40	0	0.027	0	7.63	0.04	CHIPS	DRY
YNRC006	ADA36409	62	63	-1	-0.01	50	0	0.028	0	8.96	0.05	CHIPS	DRY
YNRC006	ADA36410	63	64	-1	-0.01	40	0	0.025	0	7.84	0.03	CHIPS	DRY
YNRC006	ADA36411	64	65	-1	-0.01	40	0	0.031	0	7.68	0.1	CHIPS	DRY
YNRC006	ADA36412	65	66	-1	-0.01	40	0	0.029	0	8.16	0.04	CHIPS	DRY
YNRC006	ADA36413	66	67	-1	-0.01	40	0	0.027	0	7.83	0.01	CHIPS	DRY
YNRC006	ADA36414	67	68	-1	-0.01	50	0	0.027	0	7.51	0.02	CHIPS	DRY
YNRC006	ADA36415	68	69	-1	-0.01	40	0	0.024	0	7.54	0.04	CHIPS	DRY
YNRC006	ADA36416	69	70	-1	-0.01	40	0	0.026	0	8.35	0.05	CHIPS	DRY
YNRC006	ADA36417	70	71	-1	-0.01	50	0	0.046	0	11.35	0.06	CHIPS	DRY
YNRC006	ADA36418	71	72	-1	-0.01	60	0.01	0.064	0	11.75	0.16	CHIPS	DRY
YNRC006	ADA36419	72	73	-1	-0.01	150	0.01	0.085	0	10.6	0.22	CHIPS	DRY
YNRC006	ADA36420	73	74	-1	-0.01	130	0.01	0.097	0	15	0.21	CHIPS	DRY
YNRC006	ADA36421	74	75	-1	-0.01	140	0.01	0.11	0	15.35	0.12	CHIPS	DRY
YNRC006	ADA36422	75	76	-1	-0.01	130	0.01	0.077	0	14.8	0.1	CHIPS	DRY
YNRC006	ADA36423	76	77	-1	-0.01	140	0.02	0.087	0	16.2	0.12	CHIPS	DRY
YNRC006	ADA36424	77	78	-1	-0.01	120	0.01	0.097	0	16.8	0.12	CHIPS	DRY
YNRC006	ADA36425	78	79	-1	-0.01	120	0.01	0.069	0	14.75	0.2	CHIPS	DRY



Hole_ID	Sample ID	Fromm	To m	Ag ppm	Au ppm	Co ppm	Cu pct	Zn pct	Pb pct	Fe pct	S pct	Sample Type	Sample Condition
YNRC006	ADA36426	79	80	1	-0.01	110	0.03	0.112	0.05	13.85	0.34	CHIPS	DRY
YNRC006	ADA36427	80	81	-1	-0.01	70	0.02	0.043	0	11.1	0.48	CHIPS	DRY
YNRC006	ADA36428	81	82	-1	-0.01	80	0.02	0.048	0	10.85	0.86	CHIPS	DRY
YNRC006	ADA36429	82	83	-1	-0.01	120	0.04	0.083	0	15.4	0.29	CHIPS	DRY
YNRC006	ADA36430	83	84	-1	-0.01	120	0.05	0.067	0	14.25	0.17	CHIPS	DRY
YNRC006	ADA36431	84	85	-1	-0.01	130	0.06	0.106	0	14.4	0.13	CHIPS	DRY
YNRC006	ADA36432	85	86	-1	-0.01	140	0.06	0.11	0	15.3	0.14	CHIPS	DRY
YNRC006	ADA36433	86	87	-1	-0.01	100	0.02	0.085	0	12.6	0.13	CHIPS	DRY
YNRC006	ADA36434	87	88	1	-0.01	130	0.02	0.063	0	14.55	0.21	CHIPS	DRY
YNRC006	ADA36435	88	89	-1	-0.01	100	0.02	0.065	0	13.9	0.31	CHIPS	DRY
YNRC006	ADA36436	89	90	1	-0.01	120	0.02	0.071	0	14.55	0.38	CHIPS	DRY
YNRC007	ADA37310	0	1	-1	0.03	10	0	0.008	0	2.29	0.01	CHIPS	DRY
YNRC007	ADA37311	1	2	-1	0.02	10	0	0.008	0	1.67	-0.01	CHIPS	DRY
YNRC007	ADA37312	2	3	-1	0.03	10	0	0.006	0	1.48	-0.01	CHIPS	DRY
YNRC007	ADA37313	3	4	-1	0.02	10	0	0.006	0	1.54	-0.01	CHIPS	DRY
YNRC007	ADA37314	4	5	-1	0.02	10	0.01	0.011	0	1.45	-0.01	CHIPS	DRY
YNRC007	ADA37315	5	6	-1	0.01	-10	0	0.007	0	0.98	-0.01	CHIPS	DRY
YNRC007	ADA37316	6	7	-1	0.01	10	0	0.019	0	1.22	-0.01	CHIPS	DRY
YNRC007	ADA37317	7	8	-1	0.03	10	0.01	0.014	0	1.53	-0.01	CHIPS	DRY
YNRC007	ADA37318	8	9	-1	0.01	10	0.01	0.012	0	3.48	-0.01	CHIPS	DRY
YNRC007	ADA37319	9	10	-1	0.02	10	0.01	0.011	0	4.7	-0.01	CHIPS	DRY
YNRC007	ADA37320	10	11	-1	0.02	10	0.04	0.016	0.01	11.2	-0.01	CHIPS	DRY
YNRC007	ADA37321	11	12	-1	0.03	10	0.07	0.023	0	13	-0.01	CHIPS	DRY
YNRC007	ADA37322	12	13	-1	0.2	20	0.06	0.021	0	6.33	0.02	CHIPS	DRY
YNRC007	ADA37323	13	14	-1	-0.01	20	0.04	0.007	0	4.22	0.01	CHIPS	DRY
YNRC007	ADA37324	14	15	-1	0.01	20	0.07	0.01	0	6.09	0.01	CHIPS	DRY
YNRC007	ADA37325	15	16	-1	-0.01	-10	0.05	0.007	0	4.88	0.01	CHIPS	DRY
YNRC007	ADA37326	16	17	-1	-0.01	-10	0.04	0.007	0	4.83	0.01	CHIPS	DRY
YNRC007	ADA37327	17	18	-1	-0.01	-10	0.04	0.009	0	3.95	0.01	CHIPS	DRY
YNRC007	ADA37328	18	19	1	0.01	10	0.05	0.028	0.01	3.97	0.03	CHIPS	DRY
YNRC007	ADA37329	19	20	1	-0.01	-10	0.04	0.013	0	3.67	0.01	CHIPS	DRY
YNRC007	ADA37330	20	21	-1	-0.01	-10	0.05	0.011	0	3.21	0.01	CHIPS	DRY
YNRC007	ADA37331	21	22	-1	-0.01	10	0.06	0.016	0	4.17	0.01	CHIPS	DRY
YNRC007	ADA37332	22	23	-1	-0.01	10	0.06	0.017	0	4.89	0.01	CHIPS	DRY
YNRC007	ADA37333	23	24	2	-0.01	-10	0.03	0.013	0	3.65	0.01	CHIPS	DRY
YNRC007	ADA37334	24	25	-1	-0.01	10	0.02	0.022	0	4.24	0.01	CHIPS	DRY
YNRC007	ADA37335	25	26	-1	-0.01	-10	0.01	0.018	0	3.7	0.01	CHIPS	DRY
YNRC007	ADA37336	26	27	-1	0.01	10	0.02	0.021	0	4.52	0.01	CHIPS	DRY
YNRC007	ADA37337	27	28	-1	0.01	10	0.06	0.015	0	3.63	0.01	CHIPS	DRY
YNRC007	ADA37338	28	29	1	-0.01	30	0.05	0.06	0	10.35	0.01	CHIPS	DRY
YNRC007	ADA37339	29	30	-1	-0.01	40	0.01	0.044	0	10.95	0.01	CHIPS	DRY
YNRC007	ADA37340	30	31	-1	-0.01	30	0.01	0.04	0	11.15	0.01	CHIPS	DRY
YNRC007	ADA37341	31	32	-1	-0.01	50	0.01	0.046	0	10.45	0.02	CHIPS	DRY
YNRC007	ADA37342	32	33	-1	0.01	90	0.02	0.043	0	7.64	0.01	CHIPS	DRY
YNRC007	ADA37343	33	34	-1	-0.01	70	0.15	0.028	0	8.54	0.01	CHIPS	DRY
YNRC007	ADA37344	34	35	-1	-0.01	40	0.23	0.008	0	4.94	0.01	CHIPS	DRY
YNRC007	ADA37345	35	36	-1	-0.01	-10	0.31	0.003	0	5.52	0.02	CHIPS	DRY
YNRC007	ADA37346	36	37	-1	0.01	-10	0.23	0.003	0	6.13	0.03	CHIPS	DRY
YNRC007	ADA37347	37	38	1	-0.01	-10	0.06	0.002	0	0.79	0.06	CHIPS	DRY
YNRC007	ADA37348	38	39	1	-0.01	-10	0.05	0.003	0	0.83	0.07	CHIPS	DRY
YNRC007	ADA37349	39	40	1	0.04	-10	0.24	0.003	0.01	5.49	0.05	CHIPS	DRY
YNRC007	ADA37350	40	41	5	0.3	-10	0.52	0.005	0.06	15.55	0.11	CHIPS	DRY
YNRC007	ADA37351	41	42	34	0.9	-10	26.8	0.003	0.03	8.06	0.05	CHIPS	DRY
YNRC007	ADA37352	42	43	7	0.15	-10	3.61	0.006	0.01	3.95	0.07	CHIPS	DRY
YNRC007	ADA37353	43	44	2	0.04	-10	1.01	0.008	0	1.74	0.11	CHIPS	DRY



Hole_ID	Sample ID	Fromm	To m	Ag ppm	Au ppm	Co ppm	Cu pct	Zn pct	Pb pct	Fe pct	S pct	Sample Type	Sample Condition
YNRC007	ADA37354	44	45	4	0.02	10	1.75	0.013	0	4.02	0.07	CHIPS	DRY
YNRC007	ADA37355	45	46	-1	-0.01	-10	0.26	0.008	0	4.71	0.02	CHIPS	DRY
YNRC007	ADA37356	46	47	-1	-0.01	10	0.13	0.007	0	5.38	0.01	CHIPS	DRY
YNRC007	ADA37357	47	48	-1	-0.01	10	0.2	0.01	0	4.44	0.01	CHIPS	DRY
YNRC007	ADA37358	48	49	1	-0.01	10	0.11	0.01	0	4.81	0.14	CHIPS	DRY
YNRC007	ADA37359	49	50	-1	-0.01	30	0.1	0.018	0	6.07	0.01	CHIPS	DRY
YNRC007	ADA37360	50	51	-1	-0.01	40	0.09	0.042	0	7.81	0.01	CHIPS	DRY
YNRC007	ADA37361	51	52	3	-0.01	40	0.04	0.045	0	6.78	0.03	CHIPS	DRY
YNRC007	ADA37362	52	53	-1	-0.01	50	0.02	0.045	0	7.53	0.01	CHIPS	DRY
YNRC007	ADA37363	53	54	-1	-0.01	50	0.02	0.055	0	7.44	0.01	CHIPS	DRY
YNRC007	ADA37364	54	55	1	-0.01	80	0.01	0.105	0	10.6	0.01	CHIPS	DRY
YNRC007	ADA37365	55	56	1	-0.01	60	0.01	0.084	0	9.56	-0.01	CHIPS	DRY
YNRC007	ADA37366	56	57	-1	-0.01	40	0.01	0.024	0	5.97	0.86	CHIPS	DRY
YNRC007	ADA37367	57	58	1	-0.01	70	0.03	0.029	0	7.54	0.8	CHIPS	DRY
YNRC007	ADA37368	58	59	-1	-0.01	40	0.01	0.028	0	7.17	0.3	CHIPS	DRY
YNRC007	ADA37369	59	60	-1	-0.01	10	0.01	0.023	0	5.86	0.01	CHIPS	DRY
YNRC007	ADA37370	60	61	-1	-0.01	10	0	0.025	0	5.96	0.04	CHIPS	DRY
YNRC007	ADA37371	61	62	-1	-0.01	10	0	0.025	0	5.66	0.05	CHIPS	DRY
YNRC007	ADA37372	62	63	1	-0.01	10	0.01	0.027	0	5.69	0.06	CHIPS	DRY
YNRC007	ADA37373	63	64	1	-0.01	10	0	0.031	0	5.89	0.18	CHIPS	DRY
YNRC007	ADA37374	64	65	-1	-0.01	20	0.01	0.036	0	6.1	0.35	CHIPS	DRY
YNRC007	ADA37375	65	66	-1	-0.01	20	0.01	0.043	0	6	0.22	CHIPS	DRY
YNRC007	ADA37376	66	67	-1	-0.01	20	0.01	0.031	0	5.41	0.63	CHIPS	DRY
YNRC007	ADA37377	67	68	-1	-0.01	20	0	0.036	0	7.53	0.13	CHIPS	DRY
YNRC007	ADA37378	68	69	1	-0.01	10	0	0.029	0	6.46	0.16	CHIPS	DRY
YNRC007	ADA37379	69	70	-1	-0.01	20	0	0.036	0	6.31	0.1	CHIPS	DRY
YNRC008	ADA37380	0	1	-1	0.02	10	0.01	0.012	0	3.79	0.17	CHIPS	DRY
YNRC008	ADA37381	1	2	-1	0.03	10	0.01	0.006	0	2.52	0.03	CHIPS	DRY
YNRC008	ADA37382	2	3	-1	0.1	10	0	0.006	0	1.36	0.01	CHIPS	DRY
YNRC008	ADA37383	3	4	-1	0.11	10	0.01	0.006	0	1.62	0.01	CHIPS	DRY
YNRC008	ADA37384	4	5	-1	0.02	10	0	0.006	0	1.55	-0.01	CHIPS	DRY
YNRC008	ADA37385	5	6	1	-0.01	10	0	0.007	0	1.7	-0.01	CHIPS	DRY
YNRC008	ADA37386	6	7	1	-0.01	10	0	0.008	0	1.44	-0.01	CHIPS	DRY
YNRC008	ADA37387	7	8	-1	-0.01	10	0.01	0.015	0	2.88	-0.01	CHIPS	DRY
YNRC008	ADA37388	8	9	1	0.19	10	0.01	0.011	0	3.85	-0.01	CHIPS	DRY
YNRC008	ADA37389	9	10	1	0.01	70	0.02	0.037	0	4.98	-0.01	CHIPS	DRY
YNRC008	ADA37390	10	11	1	-0.01	90	0.04	0.053	0	5.15	-0.01	CHIPS	DRY
YNRC008	ADA37391	11	12	-1	-0.01	90	0.05	0.128	0	13.8	-0.01	CHIPS	DRY
YNRC008	ADA37392	12	13	-1	-0.01	50	0.01	0.065	0	8.32	-0.01	CHIPS	DRY
YNRC008	ADA37393	13	14	-1	-0.01	30	0.01	0.051	0	7.57	-0.01	CHIPS	DRY
YNRC008	ADA37394	14	15	-1	-0.01	60	0.04	0.1	0	13.35	-0.01	CHIPS	DRY
YNRC008	ADA37395	15	16	-1	-0.01	60	0.04	0.095	0	13.45	0.01	CHIPS	DRY
YNRC008	ADA37396	16	17	-1	-0.01	50	0.01	0.074	0	15.65	-0.01	CHIPS	DRY
YNRC008	ADA37397	17	18	-1	-0.01	130	0.06	0.07	0	11.05	-0.01	CHIPS	DRY
YNRC008	ADA37398	18	19	-1	-0.01	10	0	0.028	0	5.07	-0.01	CHIPS	DRY
YNRC008	ADA37399	19	20	-1	-0.01	50	0.02	0.038	0	5.24	-0.01	CHIPS	DRY
YNRC008	ADA37400	20	21	-1	-0.01	30	0.02	0.033	0	4.22	-0.01	CHIPS	DRY
YNRC008	ADA37401	21	22	-1	-0.01	20	0.02	0.032	0	4.44	-0.01	CHIPS	DRY
YNRC008	ADA37402	22	23	-1	-0.01	10	0.01	0.023	0	4.46	-0.01	CHIPS	DRY
YNRC008	ADA37403	23	24	-1	-0.01	10	0	0.016	0	3.53	-0.01	CHIPS	DRY
YNRC008	ADA37404	24	25	-1	-0.01	10	0	0.021	0	4.06	-0.01	CHIPS	DRY
YNRC008	ADA37405	25	26	-1	-0.01	60	0.01	0.033	0	3.88	-0.01	CHIPS	DRY
YNRC008	ADA37406	26	27	-1	-0.01	30	0.01	0.063	0	7.19	0.06	CHIPS	DRY
YNRC008	ADA37407	27	28	-1	-0.01	60	0.01	0.058	0	6.91	0.05	CHIPS	DRY
YNRC008	ADA37408	28	29	-1	-0.01	10	0	0.016	0	3.99	0.06	CHIPS	DRY



Hole_ID	Sample ID	Fromm	To m	Ag ppm	Au ppm	Co ppm	Cu pct	Zn pct	Pb pct	Fe pct	S pct	Sample Type	Sample Condition
YNRC008	ADA37409	29	30	-1	-0.01	10	0.01	0.022	0	3.51	0.06	CHIPS	DRY
YNRC008	ADA37410	30	31	-1	-0.01	10	0.01	0.018	0	3.92	0.06	CHIPS	DRY
YNRC008	ADA37411	31	32	1	-0.01	10	0	0.005	0	1.43	-0.01	CHIPS	DRY
YNRC008	ADA37412	32	33	-1	-0.01	10	0	0.02	0	4.51	-0.01	CHIPS	DRY
YNRC008	ADA37413	33	34	-1	-0.01	50	0.01	0.052	0	5.22	-0.01	CHIPS	DRY
YNRC008	ADA37414	34	35	-1	-0.01	60	0.02	0.046	0	4.5	-0.01	CHIPS	DRY
YNRC008	ADA37415	35	36	-1	-0.01	30	0.01	0.032	0	4.78	-0.01	CHIPS	DRY
YNRC008	ADA37416	36	37	-1	-0.01	30	0.01	0.02	0	3.5	-0.01	CHIPS	DRY
YNRC008	ADA37417	37	38	-1	-0.01	20	0.01	0.021	0	4.78	-0.01	CHIPS	DRY
YNRC008	ADA37418	38	39	-1	-0.01	140	0.01	0.022	0	4.15	-0.01	CHIPS	DRY
YNRC008	ADA37419	39	40	-1	-0.01	30	0	0.021	0	3.76	-0.01	CHIPS	DRY
YNRC008	ADA37420	40	41	-1	-0.01	50	0	0.032	0	4.97	-0.01	CHIPS	DRY
YNRC008	ADA37421	41	42	-1	-0.01	20	0	0.014	0	4.04	-0.01	CHIPS	DRY
YNRC008	ADA37422	42	43	-1	-0.01	20	0	0.017	0	4.7	0.01	CHIPS	DRY
YNRC008	ADA37423	43	44	1	-0.01	290	0.17	0.109	0	8	0.01	CHIPS	DRY
YNRC008	ADA37424	44	45	1	-0.01	100	0.01	0.043	0	11.05	-0.01	CHIPS	DRY
YNRC008	ADA37425	45	46	1	0.01	120	0.01	0.058	0	12.4	-0.01	CHIPS	DRY
YNRC008	ADA37426	46	47	-1	-0.01	130	0.02	0.044	0	14.65	-0.01	CHIPS	DRY
YNRC008	ADA37427	47	48	-1	-0.01	310	0.12	0.047	0	12.75	-0.01	CHIPS	DRY
YNRC008	ADA37428	48	49	2	-0.01	480	0.61	0.055	0	10.6	0.01	CHIPS	DRY
YNRC008	ADA37429	49	50	-1	0.01	90	0.07	0.038	0	7.01	-0.01	CHIPS	DRY
YNRC008	ADA37430	50	51	1	0.17	70	0.02	0.052	0.01	8.56	-0.01	CHIPS	DRY
YNRC008	ADA37431	51	52	1	0.01	50	0.02	0.042	0	8.93	-0.01	CHIPS	DRY
YNRC008	ADA37432	52	53	-1	-0.01	70	0.01	0.055	0	12.8	0.01	CHIPS	DRY
YNRC008	ADA37433	53	54	-1	-0.01	60	0.01	0.059	0	13.35	0.08	CHIPS	DRY
YNRC008	ADA37434	54	55	-1	-0.01	20	0	0.016	0	5.47	0.01	CHIPS	DRY
YNRC008	ADA37435	55	56	-1	-0.01	30	0.01	0.019	0	9.34	0.06	CHIPS	DRY
YNRC008	ADA37436	56	57	-1	-0.01	30	0.01	0.019	0	9.73	0.21	CHIPS	DRY
YNRC008	ADA37437	57	58	-1	-0.01	40	0	0.018	0	8.61	0.16	CHIPS	DRY
YNRC008	ADA37438	58	59	-1	-0.01	30	0	0.021	0	10.25	0.23	CHIPS	DRY
YNRC008	ADA37439	59	60	-1	-0.01	30	0.01	0.021	0	10.8	0.73	CHIPS	DRY
YNRC008	ADA37440	60	61	-1	-0.01	30	0.01	0.03	0	14.7	0.43	CHIPS	DRY
YNRC008	ADA37441	61	62	1	-0.01	60	0.35	0.098	0	14.5	1.7	CHIPS	DRY
YNRC008	ADA37442	62	63	1	0.02	320	0.68	0.338	0	38.8	34.5	CHIPS	DRY
YNRC008	ADA37443	63	64	2	0.01	360	1.33	0.48	0	37.6	36.8	CHIPS	DRY
YNRC008	ADA37444	64	65	2	0.01	220	1.39	1.62	0	26.9	24.3	CHIPS	DRY
YNRC008	ADA37445	65	66	2	0.01	250	1.52	0.65	0	31.6	28.3	CHIPS	DRY
YNRC008	ADA37446	66	67	2	0.01	240	0.97	2.26	0	34.6	30.6	CHIPS	DRY
YNRC008	ADA37447	67	68	4	0.1	1830	2.93	2.82	0	32.2	29	CHIPS	DRY
YNRC008	ADA37448	68	69	1	0.58	11400	0.51	0.554	0	19.25	13.75	CHIPS	DRY
YNRC008	ADA37449	69	70	1	0.06	1080	1.25	0.576	0	37.5	24.6	CHIPS	DRY
YNRC008	ADA37450	70	71	2	0.05	630	1.11	0.513	0	42.3	28.3	CHIPS	DRY
YNRC008	ADA37451	71	72	3	0.08	390	1.47	0.301	0	37.2	27.7	CHIPS	DRY
YNRC008	ADA37452	72	73	1	0.04	530	0.79	0.402	0	42.2	31.4	CHIPS	DRY
YNRC008	ADA37453	73	74	2	0.04	720	0.89	0.225	0	32.5	26	CHIPS	DRY
YNRC008	ADA37454	74	75	2	0.13	430	0.63	0.133	0	31.1	22.7	CHIPS	DRY
YNRC008	ADA37455	75	76	4	0.29	260	1.96	0.283	0	29.7	21	CHIPS	DRY
YNRC008	ADA37456	76	77	3	0.36	340	2.01	1.175	0	32.5	24.1	CHIPS	DRY
YNRC008	ADA37457	77	78	3	0.19	270	1.7	3	0	29.3	20.9	CHIPS	DRY
YNRC008	ADA37458	78	79	2	0.1	260	0.96	1.345	0	32.3	23.7	CHIPS	DRY
YNRC008	ADA37459	79	80	1	0.05	200	0.56	2.01	0	34.4	16.5	CHIPS	DRY
YNRC008	ADA37460	80	81	-1	0.01	70	0.13	0.365	0	14.05	2.96	CHIPS	DRY
YNRC008	ADA37461	81	82	-1	0.01	130	0.14	0.276	0	13.85	3.6	CHIPS	DRY
YNRC008	ADA37462	82	83	-1	-0.01	90	0.06	0.075	0	9.9	1.38	CHIPS	DRY
YNRC008	ADA37463	83	84	1	0.01	60	0.05	0.053	0	5.98	1.12	CHIPS	DRY



Hole_ID	Sample ID	Fromm	To m	Ag ppm	Au ppm	Co ppm	Cu pct	Zn pct	Pb pct	Fe pct	S pct	Sample Type	Sample Condition
YNRC008	ADA37464	84	85	-1	-0.01	40	0.04	0.047	0	5.57	1.06	CHIPS	DRY
YNRC008	ADA37465	85	86	-1	0.01	120	0.13	0.132	0	8.97	3.54	CHIPS	DRY
YNRC008	ADA37466	86	87	-1	-0.01	40	0.04	0.042	0	5.86	1.14	CHIPS	DRY
YNRC008	ADA37467	87	88	-1	-0.01	50	0.02	0.031	0	7.12	0.55	CHIPS	DRY
YNRC008	ADA37468	88	89	-1	0.01	110	0.09	0.091	0	8.37	2.51	CHIPS	DRY
YNRC008	ADA37469	89	90	-1	-0.01	60	0.04	0.038	0	7.57	0.92	CHIPS	DRY
YNRC008	ADA37470	90	91	-1	-0.01	50	0.03	0.034	0	7.13	0.78	CHIPS	DRY
YNRC008	ADA37471	91	92	-1	0.01	100	0.05	0.058	0	5.84	1.18	CHIPS	DRY
YNRC008	ADA37472	92	93	-1	-0.01	40	0.01	0.013	0	5.85	0.53	CHIPS	DRY
YNRC008	ADA37473	93	94	-1	-0.01	30	0.01	0.012	0	6.83	0.37	CHIPS	DRY
YNRC008	ADA37474	94	95	-1	-0.01	40	0.01	0.014	0	7.16	0.33	CHIPS	DRY
YNRC008	ADA37475	95	96	-1	-0.01	30	0.01	0.026	0.01	5.63	0.28	CHIPS	DRY
YNRC008	ADA37476	96	97	-1	-0.01	30	0.01	0.013	0	5.74	0.2	CHIPS	DRY
YNRC008	ADA37477	97	98	-1	-0.01	40	0.01	0.016	0	6.34	0.34	CHIPS	DRY
YNRC008	ADA37478	98	99	-1	-0.01	40	0.01	0.014	0	8.59	0.18	CHIPS	DRY
YNRC008	ADA37479	99	100	-1	-0.01	40	0	0.012	0	7.95	0.19	CHIPS	DRY
YNRC008	ADA37480	100	101	-1	-0.01	40	0.01	0.012	0	7.64	0.19	CHIPS	DRY
YNRC008	ADA37481	101	102	-1	-0.01	30	0	0.01	0	7.22	0.12	CHIPS	DRY
YNRC008	ADA37482	102	103	1	-0.01	40	0.04	0.011	0	8.19	0.16	CHIPS	DRY
YNRC008	ADA37483	103	104	-1	-0.01	40	0	0.011	0	7.23	0.17	CHIPS	DRY
YNRC008	ADA37484	104	105	-1	-0.01	30	0	0.009	0	6.72	0.12	CHIPS	DRY
YNRC008	ADA37485	105	106	-1	-0.01	40	0.01	0.014	0	8.66	0.2	CHIPS	DRY
YNRC008	ADA37486	106	107	-1	-0.01	40	0.01	0.017	0	9.09	0.27	CHIPS	DRY
YNRC008	ADA37487	107	108	-1	-0.01	30	0	0.014	0	8.96	0.1	CHIPS	DRY
YNRC008	ADA37488	108	109	-1	-0.01	30	0.01	0.01	0	6.99	0.11	CHIPS	DRY
YNRC008	ADA37489	109	110	-1	-0.01	30	0	0.015	0	8.21	0.28	CHIPS	DRY
YNRC008	ADA37490	110	111	-1	-0.01	40	0	0.013	0	7.63	0.17	CHIPS	DRY
YNRC008	ADA37491	111	112	-1	-0.01	20	0.01	0.013	0	6.75	0.1	CHIPS	DRY
YNRC008	ADA37492	112	113	-1	-0.01	40	0.02	0.022	0	8.15	0.16	CHIPS	DRY
YNRC008	ADA37493	113	114	-1	-0.01	50	0.05	0.032	0	9.1	0.24	CHIPS	DRY
YNRC008	ADA37494	114	115	-1	-0.01	50	0.02	0.026	0	8.59	0.21	CHIPS	DRY
YNRC008	ADA37495	115	116	-1	-0.01	40	0.01	0.016	0	7.76	0.12	CHIPS	DRY
YNRC008	ADA37496	116	117	-1	-0.01	40	0.01	0.022	0	8.31	0.08	CHIPS	DRY
YNRC008	ADA37497	117	118	-1	-0.01	30	0.01	0.031	0	9.16	0.08	CHIPS	DRY
YNRC008	ADA37498	118	119	-1	-0.01	40	0.01	0.04	0	9.1	0.27	CHIPS	DRY
YNRC008	ADA37499	119	120	-1	-0.01	30	0	0.029	0	7.45	0.12	CHIPS	DRY
YNRC009	ADA37075	0	1	1	0.01	10	0	0.004	0	2.44	0.01	CHIPS	DRY
YNRC009	ADA37076	1	2	-1	0.03	10	0.01	0.005	0	2.6	0.01	CHIPS	DRY
YNRC009	ADA37077	2	3	-1	0.01	10	0	0.002	0	1.39	-0.01	CHIPS	DRY
YNRC009	ADA37078	3	4	-1	0.01	10	0	0.003	0	1.38	-0.01	CHIPS	DRY
YNRC009	ADA37079	4	5	-1	0.04	30	0.01	0.026	0	2.87	-0.01	CHIPS	DRY
YNRC009	ADA37080	5	6	-1	0.04	50	0.02	0.03	0	3.32	-0.01	CHIPS	DRY
YNRC009	ADA37081	6	7	-1	0.02	20	0.01	0.021	0	3.44	-0.01	CHIPS	DRY
YNRC009	ADA37082	7	8	-1	0.01	30	0.01	0.018	0	3.93	-0.01	CHIPS	DRY
YNRC009	ADA37083	8	9	-1	0.01	30	0	0.015	0	4.19	-0.01	CHIPS	DRY
YNRC009	ADA37084	9	10	-1	0.01	10	0	0.009	0	3.57	-0.01	CHIPS	DRY
YNRC009	ADA37085	10	11	-1	0.01	20	0	0.008	0	3.75	-0.01	CHIPS	DRY
YNRC009	ADA37086	11	12	-1	0.01	20	0	0.01	0	3.37	-0.01	CHIPS	DRY
YNRC009	ADA37087	12	13	-1	0.01	10	0	0.008	0	3.47	-0.01	CHIPS	DRY
YNRC009	ADA37088	13	14	-1	-0.01	20	0	0.013	0	3.71	-0.01	CHIPS	DRY
YNRC009	ADA37089	14	15	-1	0.01	40	0.01	0.027	0	5.5	-0.01	CHIPS	DRY
YNRC009	ADA37090	15	16	-1	0.01	10	0	0.011	0	3.77	-0.01	CHIPS	DRY
YNRC009	ADA37091	16	17	-1	0.01	20	0	0.01	0	4.63	-0.01	CHIPS	DRY
YNRC009	ADA37092	17	18	-1	0.01	20	0	0.008	0	4.6	-0.01	CHIPS	DRY
YNRC009	ADA37093	18	19	-1	-0.01	40	0	0.006	0	3.36	0.01	CHIPS	DRY



Hole_ID	Sample ID	Fromm	To m	Ag ppm	Au ppm	Co ppm	Cu pct	Zn pct	Pb pct	Fe pct	S pct	Sample Type	Sample Condition
YNRC009	ADA37094	19	20	-1	0.01	10	0	0.01	0.01	3.61	0.01	CHIPS	DRY
YNRC009	ADA37095	20	21	-1	-0.01	10	0	0.015	0	3.87	-0.01	CHIPS	DRY
YNRC009	ADA37096	21	22	-1	0.01	60	0.03	0.081	0	5.3	-0.01	CHIPS	DRY
YNRC009	ADA37097	22	23	-1	0.01	10	0.01	0.02	0	3.82	-0.01	CHIPS	DRY
YNRC009	ADA37098	23	24	-1	0.01	10	0.01	0.028	0	3.17	-0.01	CHIPS	DRY
YNRC009	ADA37099	24	25	-1	-0.01	20	0.01	0.036	0	4.28	-0.01	CHIPS	DRY
YNRC009	ADA37100	25	26	-1	0.01	30	0.01	0.04	0	3.55	-0.01	CHIPS	DRY
YNRC009	ADA37101	26	27	-1	-0.01	40	0.01	0.058	0	4.36	-0.01	CHIPS	DRY
YNRC009	ADA37102	27	28	-1	0.01	20	0	0.036	0	4.47	-0.01	CHIPS	DRY
YNRC009	ADA37103	28	29	-1	-0.01	10	0	0.026	0	4.45	-0.01	CHIPS	DRY
YNRC009	ADA37104	29	30	-1	0.01	10	0	0.021	0	4.08	-0.01	CHIPS	DRY
YNRC009	ADA37105	30	31	-1	0.01	30	0.03	0.07	0	9.68	-0.01	CHIPS	DRY
YNRC009	ADA37106	31	32	-1	0.01	20	0.01	0.06	0	11.35	-0.01	CHIPS	DRY
YNRC009	ADA37107	32	33	-1	0.01	20	0.02	0.028	0	4.55	-0.01	CHIPS	DRY
YNRC009	ADA37108	33	34	-1	-0.01	20	0	0.018	0	3.81	-0.01	CHIPS	DRY
YNRC009	ADA37109	34	35	-1	-0.01	20	0.01	0.016	0	4.43	-0.01	CHIPS	DRY
YNRC009	ADA37110	35	36	-1	0.01	490	0.06	0.061	0	6.22	-0.01	CHIPS	DRY
YNRC009	ADA37111	36	37	-1	0.01	60	0.02	0.035	0	4.56	-0.01	CHIPS	DRY
YNRC009	ADA37112	37	38	-1	0.01	200	0.04	0.035	0	4.68	-0.01	CHIPS	DRY
YNRC009	ADA37113	38	39	-1	0.03	110	0.02	0.035	0	3.88	-0.01	CHIPS	DRY
YNRC009	ADA37114	39	40	-1	0.01	80	0.01	0.025	0	3.42	-0.01	CHIPS	DRY
YNRC009	ADA37115	40	41	-1	0.01	30	0	0.016	0	3.79	-0.01	CHIPS	DRY
YNRC009	ADA37116	41	42	-1	0.01	30	0	0.012	0	3.23	-0.01	CHIPS	DRY
YNRC009	ADA37117	42	43	-1	-0.01	40	0	0.018	0	6.48	-0.01	CHIPS	DRY
YNRC009	ADA37118	43	44	-1	0.01	80	0	0.033	0	11.05	-0.01	CHIPS	DRY
YNRC009	ADA37119	44	45	-1	0.01	90	0	0.042	0	9.84	-0.01	CHIPS	DRY
YNRC009	ADA37120	45	46	-1	0.01	180	0	0.106	0	11.15	-0.01	CHIPS	DRY
YNRC009	ADA37121	46	47	-1	-0.01	140	0	0.081	0	11.6	-0.01	CHIPS	DRY
YNRC009	ADA37122	47	48	-1	0.01	150	0.01	0.118	0	12.8	-0.01	CHIPS	DRY
YNRC009	ADA37123	48	49	-1	0.01	60	0.01	0.043	0	8.36	-0.01	CHIPS	DRY
YNRC009	ADA37124	49	50	-1	0.01	120	0	0.109	0	12.3	-0.01	CHIPS	DRY
YNRC009	ADA37125	50	51	-1	0.01	80	0.01	0.062	0	12.9	-0.01	CHIPS	DRY
YNRC009	ADA37126	51	52	-1	0.01	30	0	0.017	0	6.05	0.01	CHIPS	DRY
YNRC009	ADA37127	52	53	-1	0.01	10	0	0.013	0	4.03	-0.01	CHIPS	DRY
YNRC009	ADA37128	53	54	-1	-0.01	10	0	0.017	0	4.02	-0.01	CHIPS	DRY
YNRC009	ADA37129	54	55	-1	0.01	20	0	0.028	0	5.45	-0.01	CHIPS	DRY
YNRC009	ADA37130	55	56	-1	-0.01	20	0	0.028	0	4.99	-0.01	CHIPS	DRY
YNRC009	ADA37131	56	57	-1	0.01	20	0	0.033	0	4.15	-0.01	CHIPS	DRY
YNRC009	ADA37132	57	58	-1	0.01	20	0	0.032	0	4.55	0.02	CHIPS	DRY
YNRC009	ADA37133	58	59	-1	0.02	20	0.01	0.198	0	7.11	0.96	CHIPS	DRY
YNRC009	ADA37134	59	60	-1	0.01	20	0.11	0.166	0	11.8	2.19	CHIPS	DRY
YNRC009	ADA37135	60	61	-1	0.01	30	0	0.033	0	8.38	0.05	CHIPS	DRY
YNRC009	ADA37136	61	62	-1	0.01	20	0	0.016	0	4.56	0.02	CHIPS	DRY
YNRC009	ADA37137	62	63	-1	-0.01	20	0	0.021	0	5.83	0.01	CHIPS	DRY
YNRC009	ADA37138	63	64	-1	-0.01	10	0	0.026	0.01	5.36	0.03	CHIPS	DRY
YNRC009	ADA37139	64	65	-1	0.01	10	0	0.012	0	5.43	0.01	CHIPS	DRY
YNRC009	ADA37140	65	66	-1	0.01	20	0	0.013	0	6.46	0.02	CHIPS	DRY
YNRC009	ADA37141	66	67	-1	0.01	10	0	0.009	0	5.42	0.01	CHIPS	DRY
YNRC009	ADA37142	67	68	-1	-0.01	20	0	0.015	0	8.13	-0.01	CHIPS	DRY
YNRC009	ADA37143	68	69	1	0.01	20	0.02	0.015	0	8.32	0.13	CHIPS	DRY
YNRC009	ADA37144	69	70	-1	0.01	10	0	0.009	0	4.58	0.02	CHIPS	DRY
YNRC009	ADA37145	70	71	-1	0.01	10	0	0.008	0	3.43	0.01	CHIPS	DRY
YNRC009	ADA37146	71	72	-1	0.01	20	0.01	0.012	0	5.9	0.02	CHIPS	DRY
YNRC009	ADA37147	72	73	-1	0.01	80	0.07	0.036	0	14.85	0.96	CHIPS	DRY
YNRC009	ADA37148	73	74	-1	0.01	20	0.01	0.014	0	7.34	0.12	CHIPS	DRY



Hole_ID	Sample ID	Fromm	To m	Ag ppm	Au ppm	Co ppm	Cu pct	Zn pct	Pb pct	Fe pct	S pct	Sample Type	Sample Condition
YNRC009	ADA37149	74	75	-1	0.01	10	0	0.011	0	6.05	0.07	CHIPS	DRY
YNRC009	ADA37150	75	76	-1	0.01	10	0	0.011	0	7.09	0.04	CHIPS	DRY
YNRC009	ADA37151	76	77	-1	0.01	10	0	0.014	0	9.56	0.07	CHIPS	DRY
YNRC009	ADA37152	77	78	-1	0.01	20	0.01	0.088	0	13.5	1.61	CHIPS	DRY
YNRC009	ADA37153	78	79	-1	-0.01	40	0.04	0.159	0	14.85	1.17	CHIPS	DRY
YNRC009	ADA37154	79	80	2	0.01	150	1.01	0.522	0	24.4	13.7	CHIPS	DRY
YNRC009	ADA37155	80	81	-1	0.04	190	0.63	0.839	0	34.4	23.8	CHIPS	DRY
YNRC009	ADA37156	81	82	2	0.03	180	1.23	0.837	0.01	34.9	27.3	CHIPS	DRY
YNRC009	ADA37157	82	83	2	0.04	220	1.12	0.168	0	38.6	33	CHIPS	DRY
YNRC009	ADA37158	83	84	3	0.03	210	1.45	0.755	0.01	43.9	30.4	CHIPS	DRY
YNRC009	ADA37159	84	85	3	0.02	100	0.8	0.162	0	31.5	13.6	CHIPS	DRY
YNRC009	ADA37160	85	86	2	0.01	130	0.61	0.715	0	38.7	21.6	CHIPS	DRY
YNRC009	ADA37161	86	87	2	0.01	230	0.8	0.319	0	39	23.9	CHIPS	DRY
YNRC009	ADA37162	87	88	2	0.3	590	0.31	0.14	0	42.2	36.5	CHIPS	DRY
YNRC009	ADA37163	88	89	2	0.16	730	0.28	0.069	0	45.4	38.4	CHIPS	DRY
YNRC009	ADA37164	89	90	1	0.08	630	0.2	0.122	0	31.6	22.2	CHIPS	DRY
YNRC009	ADA37165	90	91	4	0.46	430	0.6	1.305	0.01	38.4	24.2	CHIPS	DRY
YNRC009	ADA37166	91	92	2	0.05	240	0.64	0.568	0	39	21.9	CHIPS	DRY
YNRC009	ADA37167	92	93	2	0.03	120	1.09	0.362	0	41.3	15.95	CHIPS	DRY
YNRC009	ADA37168	93	94	2	0.08	130	1.22	1.21	0	37.1	18.5	CHIPS	DRY
YNRC009	ADA37169	94	95	2	0.03	120	0.79	0.889	0.01	34.5	17.45	CHIPS	DRY
YNRC009	ADA37170	95	96	2	0.02	140	0.77	1.77	0.01	34	20.3	CHIPS	DRY
YNRC009	ADA37171	96	97	4	0.12	190	1.66	3.58	0	38.8	29.3	CHIPS	DRY
YNRC009	ADA37172	97	98	1	0.04	130	0.45	0.336	0	26.4	15.35	CHIPS	DRY
YNRC009	ADA37173	98	99	1	-0.01	60	0.63	0.146	0	18.15	5.95	CHIPS	DRY
YNRC009	ADA37174	99	100	-1	-0.01	30	0.07	0.068	0	14.7	1.66	CHIPS	DRY
YNRC009	ADA37175	100	101	-1	-0.01	20	0.06	0.083	0	10.9	1.28	CHIPS	DRY
YNRC009	ADA37176	101	102	-1	-0.01	10	0.04	0.056	0	7.63	0.9	CHIPS	DRY
YNRC009	ADA37177	102	103	-1	-0.01	30	0.03	0.037	0	10.15	0.66	CHIPS	DRY
YNRC009	ADA37178	103	104	-1	-0.01	40	0.05	0.044	0	11.8	1.5	CHIPS	DRY
YNRC009	ADA37179	104	105	1	-0.01	40	0.02	0.033	0	10.1	0.35	CHIPS	DRY
YNRC009	ADA37180	105	106	-1	-0.01	40	0.02	0.037	0	8.48	0.78	CHIPS	DRY
YNRC009	ADA37181	106	107	-1	-0.01	30	0.01	0.021	0	6.24	0.24	CHIPS	DRY
YNRC009	ADA37182	107	108	-1	-0.01	160	0.1	0.019	0.01	8.34	4.43	CHIPS	DRY
YNRC009	ADA37183	108	109	-1	0.01	50	0.07	0.084	0	9.03	2.57	CHIPS	DRY
YNRC009	ADA37184	109	110	-1	-0.01	40	0.04	0.048	0	7.59	1.38	CHIPS	DRY
YNRC009	ADA37185	110	111	1	-0.01	30	0.01	0.024	0	6.06	0.38	CHIPS	DRY
YNRC009	ADA37186	111	112	1	0.01	50	0.05	0.067	0	8.33	2.02	CHIPS	DRY
YNRC009	ADA37187	112	113	1	0.01	50	0.05	0.063	0	8.62	1.92	CHIPS	DRY
YNRC009	ADA37188	113	114	3	-0.01	70	0.03	0.082	0.01	9.84	1.06	CHIPS	DRY
YNRC009	ADA37189	114	115	2	0.01	70	0.04	0.063	0	9.88	1.54	CHIPS	DRY
YNRC009	ADA37190	115	116	-1	0.01	80	0.07	0.09	0	11.1	3.02	CHIPS	DRY
YNRC009	ADA37191	116	117	-1	-0.01	50	0.02	0.033	0	8.26	0.81	CHIPS	DRY
YNRC009	ADA37192	117	118	-1	0.01	50	0.05	0.061	0	8.31	2	CHIPS	DRY
YNRC009	ADA37193	118	119	1	-0.01	30	0.02	0.023	0	6.84	0.52	CHIPS	DRY
YNRC009	ADA37194	119	120	1	-0.01	30	0.05	0.016	0	6.44	0.31	CHIPS	DRY
YNRC009	ADA37195	120	121	-1	-0.01	50	0.04	0.045	0	8.12	1.47	CHIPS	DRY
YNRC009	ADA37196	121	122	-1	-0.01	40	0.01	0.017	0	6.84	0.35	CHIPS	DRY
YNRC009	ADA37197	122	123	-1	-0.01	50	0.01	0.018	0	7.68	0.34	CHIPS	DRY
YNRC009	ADA37198	123	124	1	0.01	50	0.03	0.044	0	8.42	1.34	CHIPS	DRY
YNRC009	ADA37199	124	125	-1	-0.01	30	0.01	0.019	0	6.78	0.43	CHIPS	DRY



JORC Code, 2012 Edition – Table 1 report template

Section 1 Sampling Techniques and Data

(Criteria in this section apply to all succeeding sections.)

Criteria	JORC Code explanation	Commentary
Sampling techniques	<ul style="list-style-type: none"> Nature and quality of sampling (eg cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling. Include reference to measures taken to ensure sample representiveness and the appropriate calibration of any measurement tools or systems used. Aspects of the determination of mineralisation that are Material to the Public Report. In cases where 'industry standard' work has been done this would be relatively simple (eg 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information. 	<ul style="list-style-type: none"> Reverse Circulation (RC) drilling was carried out on the Yannery Project by Fox Resources(2006) and GreenTech Metals (2023). This RC drilling was designed to obtain drill chip samples at one metre intervals, from which a 2-4 kilogram sub-sample was collected for laboratory multi-element analysis including: Ag,Al,As,Ba,Be,Bi,Ca,Cd,Co,Cr,Cu,Fe,Ga,K,La,Mg,Mn,Mo,Na,Ni,P,Pb,S,Sb,Sr,Th,Ti,Tl,U,V,W,Zn. Samples from each metre were collected through a rig-mounted cyclone and split using a rig-mounted static cone splitter. Field duplicates were taken as well as blanks and Certified Reference Samples inserted at regular intervals and submitted for analysis to monitor QAQC.
Drilling techniques	<ul style="list-style-type: none"> Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc). 	<ul style="list-style-type: none"> An RC drill rig was used by both Fox Resources and GreenTech Metals to undertake the drill programs.
Drill sample recovery	<ul style="list-style-type: none"> Method of recording and assessing core and chip sample recoveries and results assessed. Measures taken to maximise sample recovery and ensure representative nature of the samples. Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material. 	<ul style="list-style-type: none"> Sample recoveries are recorded by the geologist in the field during logging and sampling. If poor sample recovery is encountered during drilling, the supervising geologist and driller endeavour to rectify the problem to ensure maximum sample recovery. Visual assessments are made for recovery, moisture, and possible contamination. A cyclone and static cone splitter were used to ensure representative sampling, and were routinely inspected and cleaned. Sample recoveries during drilling were recorded as being high. Since the sample recoveries were good there is no geological reason known that would result in biased grades as a result of poor sample recovery.
Logging	<ul style="list-style-type: none"> Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies. Whether logging is qualitative or quantitative in nature. Core (or costean, 	<ul style="list-style-type: none"> All drill chip samples are geologically logged from surface to the bottom of each drill hole. It is considered that geological logging is completed at an adequate level to allow appropriate future Mineral Resource estimation. Geological logging of the RC chips is considered quantitative

Criteria	JORC Code explanation	Commentary
	<ul style="list-style-type: none"> channel, etc) photography. The total length and percentage of the relevant intersections logged. 	<ul style="list-style-type: none"> All the RC drill holes have been logged in full.
Sub-sampling techniques and sample preparation	<ul style="list-style-type: none"> If core, whether cut or sawn and whether quarter, half or all core taken. If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry. For all sample types, the nature, quality and appropriateness of the sample preparation technique. Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples. Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling. Whether sample sizes are appropriate to the grain size of the material being sampled. 	<ul style="list-style-type: none"> The RC drilling rig was equipped with a rig-mounted cyclone and static cone splitter, which provided one bulk sample of approximately 20-30 kg, and a representative sub-sample of approximately 2-4 kg for every metre drilled. The sample size of 2-4 kg for both types of samples is considered to be appropriate and representative of the grain size and mineralisation style of the deposit. The RC drilling samples were kept dry. Duplicate samples were collected and submitted for analysis. Reference standards were inserted during drilling.
Quality of assay data and laboratory tests	<ul style="list-style-type: none"> The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total. For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc. Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established. 	<ul style="list-style-type: none"> ALS Global (Perth) were used for all analysis of drill samples submitted by both Fox and GreenTech. The laboratory techniques below are for all samples submitted to ALS and are considered appropriate for the style of mineralisation defined within the Yannery Project area: <ul style="list-style-type: none"> Samples above 3 Kg riffle split. Pulverise to 95% passing 75 microns 50-gram Fire Assay (Au-AA26) with ICP finish - Au. 4 Acid Digest ICP-AES Finish (ME-ICP61) – Ag,Al,As,Ba,Be,Bi,Ca,Cd,Co,Cr,Cu,Fe,Ga,K,La,Mg,Mn,Mo,Na,Ni,P,Pb,S,Sb,Sc,Sr,Th,Ti,Tl,U,V,W,Zn. Ore Grade 4 Acid Digest ICP-AES Finish (ME-OG62) Standards were used for external laboratory checks. Duplicates were used for external laboratory checks. No assay results have been received for the samples submitted by GreenTech pertaining to the 2023 drill program.
Verification of sampling and assaying	<ul style="list-style-type: none"> The verification of significant intersections by either independent or alternative company personnel. The use of twinned holes. Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols. Discuss any adjustment to assay data. 	<ul style="list-style-type: none"> Many of the significant results were compared with the lithological logging. None of the holes have been twinned to verify grades. All geological logging and sampling information is completed firstly on to paper logs before being transferred to Microsoft Excel spreadsheets. Physical logs and sampling data are returned to the head office for scanning and storage. No adjustments to the assay data were considered necessary.
Location of data points	<ul style="list-style-type: none"> Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation. 	<ul style="list-style-type: none"> A hand-held GPS was used to locate drill hole collars prior to drilling. After drilling Fox reported that all holes surveyed with DGPS. Drill holes from the GreenTech drill program have not been surveyed.

Criteria	JORC Code explanation	Commentary
	<ul style="list-style-type: none"> • <i>Specification of the grid system used.</i> • <i>Quality and adequacy of topographic control.</i> 	<ul style="list-style-type: none"> • Downhole surveys for the 2006 drill holes were captured at approximately 30 m intervals using a multishot survey camera with potential problems in zones containing magnetic minerals such as magnetite and pyrrhotite. • The grid system used for all GreenTech drilling is GDA94 (MGA 94 Zone 50) • Topographic control is obtained from surface profiles created by drillhole collar data and regional DTMs downloaded from Geoscience Australia Elvis website.
<i>Data spacing and distribution</i>	<ul style="list-style-type: none"> • <i>Data spacing for reporting of Exploration Results.</i> • <i>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</i> • <i>Whether sample compositing has been applied.</i> 	<ul style="list-style-type: none"> • Current drillhole spacing is variable and mainly dependent on access requirements for each drill hole. There is usually a fan of several holes with different dips and azimuths drilled from a single drill pad. • Sample compositing has been used for drilling completed by both FOX and GreenTech. All results from the RC drilling is reported at 1 metre downhole sample intervals.
<i>Orientation of data in relation to geological structure</i>	<ul style="list-style-type: none"> • <i>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</i> • <i>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</i> 	<ul style="list-style-type: none"> • Drill holes were mainly located in order to intersect the target at an angle perpendicular to strike direction however many of the drill holes intersect the mineralisation obliquely. As the target structures were considered to be moderately dipping and moderately plunging, most drill holes were angled at -60 degrees from horizontal. • The orientation of the drill holes has not biased the intercept grades except that the intercept widths are often significantly longer than the true width of the mineralisation.
<i>Sample security</i>	<ul style="list-style-type: none"> • <i>The measures taken to ensure sample security.</i> 	<ul style="list-style-type: none"> • The chain of custody is managed by the supervising geologist who places calico sample bags in polyweave sacks. Up to 5 calico sample bags are placed in each sack. Sacks from individual holes were placed into bulk bags, each bulk bag is clearly labelled with the address of laboratory and Sample ID range • Samples were delivered by Fox personnel to the transport company in Karratha on pallets. • The transport company then delivered the samples directly to the laboratory.
<i>Audits or reviews</i>	<ul style="list-style-type: none"> • <i>The results of any audits or reviews of sampling techniques and data.</i> 	<ul style="list-style-type: none"> • Data was validated by Fox upon up-loading into the master database. Any validation issues identified are investigated prior to reporting of results.

Section 2 Reporting of Exploration Results

(Criteria listed in the preceding section also apply to this section.)

Criteria	JORC Code explanation	Commentary
<i>Mineral tenement and</i>	<ul style="list-style-type: none"> • <i>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites,</i> 	<ul style="list-style-type: none"> • RC drilling by Fox was carried out on M47/009 – now 100% owned by Green Tech Resources Ltd. This tenement forms a part of a broader tenement package that comprises the West Pilbara Project.

Criteria	JORC Code explanation	Commentary
<i>land tenure status</i>	<p><i>wilderness or national park and environmental settings.</i></p> <ul style="list-style-type: none"> <i>The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.</i> 	<ul style="list-style-type: none"> This tenement is in good standing and no known impediments exist (see map provided in this report for location).
<i>Exploration done by other parties</i>	<ul style="list-style-type: none"> <i>Acknowledgment and appraisal of exploration by other parties.</i> 	<ul style="list-style-type: none"> The most significant work to have been completed historically in the Whundo area, was by Westfield Minerals NL, later Whim Creek Consolidated NL. Work completed by Westfield/Whim Creek consisted of geological mapping, geophysical surveying, geochemical sampling and diamond and RAB drilling and sampling. This outlined several high-grade shoots including the one mined in the Whundo pit in 1976. An estimated 6,746t of 27.4% Cu ore was produced from the Whundo pit. Whim Creek continued involvement with the project area after becoming Dominion Metals until 1995 when the tenements were sold to Straits Resources Ltd. Dominion had completed drilling and resource estimation on Whundo and pit plans were completed but not implemented. Straits completed drilling along strike to expand resources and did not identify sufficient additional oxide resources to warrant development and shipping to Whim Creek. Fox Resources Ltd obtained control of the tenements from Straits in 2003 and subsequently undertook an extensive drilling program on the West Whundo deposit outlining a combined Oxide/Supergene/Primary Mineral Resource. Most of the original Oxide resource at Whundo and West Whundo was mined by Fox between 2005-2006 in two open pits. Yannery is reported as being mined historically in the periods 1920 -1958 and 1951 – 1958 with a total 3044 tonnes mined by underground mining.
<i>Geology</i>	<ul style="list-style-type: none"> <i>Deposit type, geological setting and style of mineralisation.</i> 	<ul style="list-style-type: none"> The Yannery deposit lies on the edge of a window of metamorphosed sedimentary rocks within the Whundo Group (Asv) emerging from below the younger overlying Hardey Formation (AFh) - poorly to moderately sorted, medium- to coarse-grained sandstone, conglomerate, siltstone, shale, and tuff. The mineralisation at Yannery is logged in historical Fox Resources drilling as being massive sulphide lodes with selvages of disseminated sulphides associated with stockworks of veinlet “feeder zones”. The main sulphide minerals within the unweathered mineralised lodes are pyrite, pyrrhotite, and chalcopyrite. Quartz and calcite veins and veinlets are common. The mineralisation in the oxide zone from shallow drilling undertaken by GreenTech was malachite, with native copper observed in some holes.
<i>Drill hole Information</i>	<ul style="list-style-type: none"> <i>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for</i> 	<ul style="list-style-type: none"> Collar information for all drill holes reported is provided as an appendix to the body of this report.

Criteria	JORC Code explanation	Commentary
	<p><i>all Material drill holes:</i></p> <ul style="list-style-type: none"> ○ <i>easting and northing of the drill hole collar</i> ○ <i>elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</i> ○ <i>dip and azimuth of the hole</i> ○ <i>down hole length and interception depth</i> ○ <i>hole length.</i> <ul style="list-style-type: none"> ● <i>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.</i> 	
<i>Data aggregation methods</i>	<ul style="list-style-type: none"> ● <i>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (eg cutting of high grades) and cut-off grades are usually Material and should be stated.</i> ● <i>Where aggregate intercepts incorporate short lengths of high grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</i> ● <i>The assumptions used for any reporting of metal equivalent values should be clearly stated.</i> 	<ul style="list-style-type: none"> ● All RC sample intervals reported are composed of 1 metre or 3m down hole intervals and are therefore length weighted. ● No upper or lower cut-off grades have been used in reporting results. ●
<i>Relationship between mineralisation widths and intercept lengths</i>	<ul style="list-style-type: none"> ● <i>These relationships are particularly important in the reporting of Exploration Results.</i> ● <i>If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported.</i> ● <i>If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (eg ‘down hole length, true width not known’).</i> 	<ul style="list-style-type: none"> ● True widths of mineralisation have not been calculated for this report, and as such all intersections reported are down-hole thicknesses and compensated for in 3D for the resource modelling. ● Due to the moderately to steeply dipping nature of the mineralised zones, it is expected that true thicknesses will be less than the reported down-hole thicknesses.
<i>Diagrams</i>	<ul style="list-style-type: none"> ● <i>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</i> 	<ul style="list-style-type: none"> ● Appropriate maps and sections are available in the body of this report.
<i>Balanced reporting</i>	<ul style="list-style-type: none"> ● <i>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</i> 	<ul style="list-style-type: none"> ● Reporting of results in this report is considered balanced.
<i>Other substantive exploration data</i>	<ul style="list-style-type: none"> ● <i>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</i> 	<ul style="list-style-type: none"> ● There is no other relevant data to report on.

Criteria	JORC Code explanation	Commentary
Further work	<ul style="list-style-type: none"> <i>The nature and scale of planned further work (eg tests for lateral extensions or depth extensions or large-scale step-out drilling).</i> <i>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</i> 	<ul style="list-style-type: none"> Infill RC and diamond drilling including shallow holes up dip from the current shallow holes to properly define the effects on grade and bulk density within the weathered zone. Twinning of selected existing holes to verify the accuracy of the earlier drilling results Bulk density sampling Sample analysis supported by detailed QAQC sample submission Accurate surveying of drill hole collars Metallurgical testing Scoping level economic study work.