

## SUCCESSFUL PRODUCTION OF LITHIUM HYDROXIDE

European Metals Holdings Limited (ASX & AIM: EMH) (“European Metals” or the “Company”) is pleased to announce the successful production of lithium hydroxide monohydrate from pregnant leach solution manufactured during the recent larger-scale Cinovec pilot programme.

### Highlights

- The pilot programme has confirmed the viability of the Lithium Chemical Plant (“LCP”) process flowsheet for the industrial-scale production of either lithium carbonate or lithium hydroxide.
- Crude lithium carbonate from the pilot programme has been converted into exceptionally clean battery-grade lithium hydroxide monohydrate at laboratory scale.
- The pilot programme processed ore is fully-representative in all respects of the run-of-mine for the first seven years of mining planned at Cinovec, including average grade and expected rock-type mix from the bulk mining.

Executive Chairman Keith Coughlan commented, “We are extremely pleased with the results from the lithium hydroxide test program. The lithium hydroxide produced was of the highest grade possible and exceptionally clean. This, when combined with the ability to produce either battery-grade lithium carbonate or hydroxide, enables a wider range of off-takers for the Cinovec product.”

### Pilot Programme and Battery-Grade Lithium End-Products

The Cinovec LCP flowsheet produces a high purity lithium sulphate solution which is capable of being used to produce either lithium carbonate or lithium hydroxide.

The first stage (un-reprocessed) crude lithium carbonate produced is very close to battery grade and easily upgraded to battery grade in a single bicarbonation step (see the Company’s ASX/ AIM announcement of 9 November 2023 “**Successful Battery-Grade pilot programme for Cinovec Lithium Project**”).

The Cinovec LCP flowsheet lends itself to producing battery-grade lithium hydroxide monohydrate either directly, or indirectly via re-processing the first stage crude lithium carbonate. The project team has assessed the relative industrial process risks of manufacturing battery-grade lithium hydroxide monohydrate using both methods. It was concluded the indirect method was regarded as the lower-risk method, when considering process risks and costs.

This method of production of lithium hydroxide monohydrate has been tested as part of the pilot programme and has successfully produced battery-grade lithium hydroxide monohydrate at a laboratory scale.

European Metals has previously produced battery-grade lithium hydroxide monohydrate (see the Company’s ASX/ AIM announcement of 8 April 2019 “**Cinovec Project Update – Battery Grade Lithium Hydroxide Sample Produced**”). The principal differences between the previous and current samples produced are that the current sample has come from the much larger-scale batch-continuous pilot programme for the revised LCP flowsheet commenced in 2023; and that the assaying requirements have been more extensive, to a better-developed reference standard published in 2020 (see further below). The revised substantially simpler LCP flowsheet was announced by the Company on 31 October

2022 – see the Company's ASX/ AIM announcement "**Simplified Extraction Process Delivers Exceptionally Clean Battery Grade Lithium Product with Improved Economics**").

The table below details the assay results of this product, compared with the globally-accepted Chinese reference standard for battery-grade lithium hydroxide monohydrate, GB/T 26008-2020. "D1" grade is the highest grade specified by the standard.

	Na pp m	K pp m	Fe pp m	Ca pp m	Cu pp m	Mg pp m	Mn pp m	Si pp m	Cl- pp m	SO <sub>4</sub> <sup>2-</sup> pp m	CO <sub>3</sub> <sup>2-</sup> ppm	B pp m	Acid Solubles †
<b>GB/T 26008-2020 D1</b>	50	30	7	20	1	10	10	50	20	80	4,000	50	50
<b>GB/T 26008-2020 D2</b>	50	30	7	50	1	10	10	50	20	100	5,000	50	50
<b>GB/T 26008-2020 D3</b>	100	50	7	100	1	10	10	50	20	100	5,000	100	50
<b>Cinovec Pilot LHM Assay</b>	4.83	1.63	2.78	0.28	0.32	0.33	0.17	3.28	9.20	25.3 1	9,658	0.03	NA
<b>Cinovec Highest Grade met</b>	D1	D1	D1	D1	D1	D1	D1	D1	D1	D1	Over *	D1	NA

\*Cinovec battery-grade lithium hydroxide monohydrate contains a higher carbonate level than specified in the reference standard because it has been prepared at laboratory scale. Lithium carbonate crystallises simultaneously with lithium hydroxide monohydrate; conditions are optimised to reduce the production of lithium carbonate to a minimum. In an industrial-scale plant, the lithium carbonate, which is produced in much finer crystals than the lithium hydroxide monohydrate, is separated from the end-product by the physical process of elutriation in solution. Elutriation is a process for separating the finer lithium carbonate particles, using a stream of solution flowing in the opposite direction to the sedimentation of the larger lithium hydroxide monohydrate crystals. This process is not possible in laboratory-scale tests.

†Acid solubles were not measured as there was not enough sample for this test. Magnetic metal particles were also not measured due to the large sample that is required as well as pilot plant equipment being materially different to the commercial plant and there being far less contact with metal components in the pilot plant.

This announcement has been approved for release by the Board.

## CONTACT

For further information on this update or the Company generally, please visit our website at [www.europeanmet.com](http://www.europeanmet.com) or see full contact details at the end of this release.

## BACKGROUND INFORMATION ON CINOVEC

### PROJECT OVERVIEW

#### Cinovec Lithium Project

Geomet s.r.o. controls the mineral exploration licenses awarded by the Czech State over the Cinovec Lithium Project. Geomet has been granted a preliminary mining permit by the Ministry of Environment and the Ministry of Industry. The company is owned 49% by EMH and 51% by CEZ a.s. through its wholly owned subsidiary, SDAS. Cinovec hosts a globally significant hard rock lithium deposit with a total Measured Mineral Resource of 53.3Mt at 0.48% Li<sub>2</sub>O, Indicated Mineral Resource of 360.2Mt at 0.44% Li<sub>2</sub>O and an Inferred Mineral Resource of 294.7Mt at 0.39% Li<sub>2</sub>O containing a combined 7.39 million tonnes Lithium Carbonate Equivalent (refer to the Company's ASX/ AIM release dated 13 October 2021) (**Resource Upgrade at Cinovec Lithium Project**).

An initial Probable Ore Reserve of 34.5Mt at 0.65% Li<sub>2</sub>O reported 4 July 2017 (**Cinovec Maiden Ore Reserve – Further Information**) has been declared to cover the first 20 years mining at an output of 22,500tpa of lithium carbonate (refer to the Company's ASX/ AIM release dated 11 July 2018) (**Cinovec Production Modelled to Increase to 22,500tpa of Lithium Carbonate**).

This makes Cinovec the largest hard rock lithium deposit in Europe and the fifth largest non-brine deposit in the world.

The deposit has previously had over 400,000 tonnes of ore mined as a trial sub-level open stope underground mining operation.

On 19 January 2022, EMH provided an update to the 2019 PFS Update. It confirmed the deposit is amenable to bulk underground mining (refer to the Company's ASX/ AIM release dated 19 January 2022) (**PFS Update delivers outstanding results**). Metallurgical test-work has produced both battery-grade lithium hydroxide and battery-grade lithium carbonate at excellent recoveries. In February 2023 DRA Global Limited ("DRA") was appointed to complete the Definitive Feasibility Study ("DFS").

Cinovec is centrally located for European end-users and is well serviced by infrastructure, with a sealed road adjacent to the deposit, rail lines located 5 km north and 8 km south of the deposit, and an active 22 kV transmission line running to the historic mine. The deposit lies in an active mining region.

The economic viability of Cinovec has been enhanced by the recent push for supply security of critical raw materials for battery production, including the strong increase in demand for lithium globally, and within Europe specifically, as demonstrated by the European Union's Critical Raw Materials Act (CRMA).

## BACKGROUND INFORMATION ON CEZ

Headquartered in the Czech Republic, CEZ a.s. is one of the largest companies in the Czech Republic and a leading energy group operating in Western and Central Europe. CEZ's core business is the generation, distribution, trade in, and sales of electricity and heat, trade in and sales of natural gas, and coal extraction. The foundation of power generation at CEZ Group are emission-free sources. The CEZ strategy named Clean Energy for Tomorrow is based on ambitious decarbonisation, development of renewable sources and nuclear energy. CEZ announced that it would move forward its climate neutrality commitment by ten years to 2040.

The largest shareholder of its parent company, CEZ a.s., is the Czech Republic with a stake of approximately 70%. The shares of CEZ a.s. are traded on the Prague and Warsaw stock exchanges and included in the PX and WIG-CEE exchange indices. CEZ's market capitalization is approximately EUR 20.3 billion.

As one of the leading Central European power companies, CEZ intends to develop several projects in areas of energy storage and battery manufacturing in the Czech Republic and in Central Europe.

CEZ is also a market leader for E-mobility in the region and has installed and operates a network of EV charging stations throughout Czech Republic. The automotive industry in the Czech Republic is a significant contributor to GDP, and the number of EV's in the country is expected to grow significantly in the coming years.

## **COMPETENT PERSONS**

Information in this release that relates to the FECAB metallurgical testwork is based on, and fairly reflects, technical data and supporting documentation compiled or supervised by Mr Walter Mädel, a full-time employee of Geomet s.r.o an associate of the Company. Mr Mädel is a member of the Australasian Institute of Mining and Metallurgy (AUSIMM) and a mineral processing professional with over 27 years of experience in metallurgical process and project development, process design, project implementation and operations. Of his experience, at least 5 years have been specifically focused on hard rock pegmatite Lithium processing development. Mr Mädel consents to the inclusion in the announcement of the matters based on this information in the form and context in which it appears. Mr Mädel is a participant in the long-term incentive plan of the Company.

Information in this release that relates to exploration results is based on, and fairly reflects, information and supporting documentation compiled by Dr Vojtech Sesulka. Dr Sesulka is a Certified Professional Geologist (certified by the European Federation of Geologists), a member of the Czech Association of Economic Geologist, and a Competent Person as defined in the JORC Code 2012 edition of the Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves. Dr Sesulka has provided his prior written consent to the inclusion in this report of the matters based on his information in the form and context in which it appears. Dr Sesulka is an independent consultant with more than 10 years working for the EMH or Geomet companies. Dr Sesulka does not own any shares in the Company and is not a participant in any short- or long-term incentive plans of the Company.

Information in this release that relates to metallurgical test work and the process design criteria and flow sheets in relation to the LCP is based on, and fairly reflects, information and supporting documentation compiled by Mr Grant Harman (B.Sc Chem Eng, B.Com). Mr Harman is an independent consultant and the principal of Lithium Consultants Australasia Pty Ltd with in excess of 14 years of lithium chemicals experience. Mr Harman has provided his prior written consent to the inclusion in this report of the matters based on his information in the form and context that the information appears. Mr Harman is a participant in the long-term incentive plan of the Company.

The information in this release that relates to Mineral Resources and Exploration Targets is based on, and fairly reflects, information and supporting documentation prepared by Mr Lynn Widenbar. Mr Widenbar, who is a Member of the Australasian Institute of Mining and Metallurgy and a Member of the Australasian Institute of Geoscientists, is a full-time employee of Widenbar and Associates and produced the estimate based on data and geological information supplied by European Metals. Mr Widenbar has sufficient experience that is relevant to the style of mineralisation and type of deposit under consideration and to the activity that he is undertaking to qualify as a Competent Person as defined in the JORC Code 2012 Edition of the Australasian Code for Reporting of Exploration Results, Minerals Resources and Ore Reserves. Mr Widenbar has provided his prior written consent to the inclusion in this report of the matters based on his information in the form and context that the information appears. Mr Widenbar does not own any shares in the Company and is not a participant in any short- or long-term incentive plans of the Company.

The Company confirms that it is not aware of any new information or data that materially affects the information included in the original market announcement and, in the case of estimates of Mineral

Resources or Ore Reserves, that all material assumptions and technical parameters underpinning the estimates in the relevant market announcement continue to apply and have not materially changed. The Company confirms that the form and context in which the Competent Person's findings are presented have not been materially modified from the original market announcement.

## CAUTION REGARDING FORWARD LOOKING STATEMENTS

Information included in this release constitutes forward-looking statements. Often, but not always, forward looking statements can generally be identified by the use of forward looking words such as "may", "will", "expect", "intend", "plan", "estimate", "anticipate", "continue", and "guidance", or other similar words and may include, without limitation, statements regarding plans, strategies and objectives of management, anticipated production or construction commencement dates and expected costs or production outputs.

Forward looking statements inherently involve known and unknown risks, uncertainties and other factors that may cause the company's actual results, performance, and achievements to differ materially from any future results, performance, or achievements. Relevant factors may include, but are not limited to, changes in commodity prices, foreign exchange fluctuations and general economic conditions, increased costs and demand for production inputs, the speculative nature of exploration and project development, including the risks of obtaining necessary licences and permits and diminishing quantities or grades of reserves, political and social risks, changes to the regulatory framework within which the company operates or may in the future operate, environmental conditions including extreme weather conditions, recruitment and retention of personnel, industrial relations issues and litigation.

Forward looking statements are based on the company and its management's good faith assumptions relating to the financial, market, regulatory and other relevant environments that will exist and affect the company's business and operations in the future. The company does not give any assurance that the assumptions on which forward looking statements are based will prove to be correct, or that the company's business or operations will not be affected in any material manner by these or other factors not foreseen or foreseeable by the company or management or beyond the company's control.

Although the company attempts and has attempted to identify factors that would cause actual actions, events or results to differ materially from those disclosed in forward looking statements, there may be other factors that could cause actual results, performance, achievements or events not to be as anticipated, estimated or intended, and many events are beyond the reasonable control of the company. Accordingly, readers are cautioned not to place undue reliance on forward looking statements. Forward looking statements in these materials speak only at the date of issue. Subject to any continuing obligations under applicable law or any relevant stock exchange listing rules, in providing this information the company does not undertake any obligation to publicly update or revise any of the forward looking statements or to advise of any change in events, conditions or circumstances on which any such statement is based.

## LITHIUM CLASSIFICATION AND CONVERSION FACTORS

Lithium grades are normally presented in percentages or parts per million (ppm). Grades of deposits are also expressed as lithium compounds in percentages, for example as a percent lithium oxide ( $\text{Li}_2\text{O}$ ) content or percent lithium carbonate ( $\text{Li}_2\text{CO}_3$ ) content.

Lithium carbonate equivalent ("**LCE**") is the industry standard terminology for, and is equivalent to,  $\text{Li}_2\text{CO}_3$ . Use of LCE is to provide data comparable with industry reports and is the total equivalent amount of lithium carbonate, assuming the lithium content in the deposit is converted to lithium carbonate, using the conversion rates in the table included below to get an equivalent  $\text{Li}_2\text{CO}_3$  value in percent. Use of LCE assumes 100% recovery and no process losses in the extraction of  $\text{Li}_2\text{CO}_3$  from the deposit.

Lithium resources and reserves are usually presented in tonnes of LCE or Li.

The standard conversion factors are set out in the table below:

**Table: Conversion Factors for Lithium Compounds and Minerals**

Convert from		Convert to Li	Convert to Li <sub>2</sub> O	Convert to Li <sub>2</sub> CO <sub>3</sub>	Convert to LiOH.H <sub>2</sub> O
Lithium	Li	1.000	2.153	5.325	6.048
Lithium Oxide	Li <sub>2</sub> O	0.464	1.000	2.473	2.809
Lithium Carbonate	Li <sub>2</sub> CO <sub>3</sub>	0.188	0.404	1.000	1.136
Lithium Hydroxide	LiOH.H <sub>2</sub> O	0.165	0.356	0.880	1.000
Lithium Fluoride	LiF	0.268	0.576	1.424	1.618

## WEBSITE

A copy of this announcement is available from the Company's website at [www.europeanmet.com/announcements/](http://www.europeanmet.com/announcements/).

## ENQUIRIES:

### European Metals Holdings Limited

Keith Coughlan, Executive Chairman

Tel: +61 (0) 419 996 333

Email: [keith@europeanmet.com](mailto:keith@europeanmet.com)

Kiran Morzaria, Non-Executive Director

Tel: +44 (0) 20 7440 0647

Henko Vos, Company Secretary

Tel: +61 (0) 400 550 042

Email: [cosec@europeanmet.com](mailto:cosec@europeanmet.com)

### WH Ireland Ltd (Nomad & Broker)

James Joyce / Darshan Patel / Isaac Hooper  
(Corporate Finance)  
Harry Ansell (Broking)

Tel: +44 (0) 20 7220 1666

### Blytheweigh (Financial PR)

Tim Blythe  
Megan Ray

Tel: +44 (0) 20 7138 3222

### Chapter 1 Advisors (Financial PR - Aus)

David Tasker

Tel: +61 (0) 433 112 936

The information contained within this announcement is deemed by the Company to constitute inside information under the Market Abuse Regulation (EU) No. 596/2014 ("MAR") as it forms part of UK domestic law by virtue of the European Union (Withdrawal) Act 2018 and is disclosed in accordance with the Company's obligations under Article 17 of MAR.

**JORC Code, 2012 Edition – Table 1**
**Section 1 Sampling Techniques and Data**

<b>Criteria</b>	<b>JORC Code explanation</b>	<b>Commentary</b>
<i>Sampling techniques</i>	<ul style="list-style-type: none"> <li>• <i>Nature and quality of sampling (eg cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling.</i></li> <li>• <i>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</i></li> <li>• <i>Aspects of the determination of mineralisation that are Material to the Public Report.</i></li> <li>• <i>In cases where ‘industry standard’ work has been done this would be relatively simple (eg ‘reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay’). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information.</i></li> </ul>	<ul style="list-style-type: none"> <li>• Between 2014 and 2021, the Company commenced a core drilling program and collected samples from core splits in line with JORC Code guidelines.</li> <li>• Sample intervals honour geological or visible mineralisation boundaries and vary between 50cm and 2m. The majority of samples are 1m in length.</li> <li>• The samples are half or quarter of core; the latter applied for large diameter core.</li> <li>• Between 1952 and 1989, the Cinovec deposit was sampled in two ways: in drill core and underground channel samples.</li> <li>• Channel samples, from drift ribs and faces, were collected during detailed exploration between 1952 and 1989 by Geindustria n.p. and Rudne Doly n.p., both Czechoslovak State companies. Sample length was 1m, channel 10x5cm, sample mass about 15kg. Up to 1966, samples were collected using hammer and chisel; from 1966 a small drill (Holman Hammer) was used. 14179 samples were collected and transported to a crushing facility.</li> <li>• Core and channel samples were crushed in two steps: to -5mm, then to -0.5mm. 100g splits were obtained and pulverized to -0.045mm for analysis.</li> </ul>
<i>Drilling techniques</i>	<ul style="list-style-type: none"> <li>• <i>Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc).</i></li> </ul>	<ul style="list-style-type: none"> <li>• In 2014, three core holes were drilled for a total of 940.1m. In 2015, six core holes were drilled for a total of 2,455.0m. In 2016, eighteen core holes were drilled for a total of 6,459.6m. In 2017, six core holes were drilled for a total of 2697.1m. In 2018, 5 core holes were drilled for a total of 1,640.3 and in 2020, 22 core holes were drilled for a total of 6,621.7m.</li> <li>• In 2014 and 2015, the core size was HQ3 (60mm diameter) in upper parts of holes; in deeper sections the core size was reduced to NQ3 (44mm diameter). Core recovery was high (average 98%). Between 2016 and 2021 up to four drill rigs were used, and select holes employed PQ sized core for upper parts of the drillholes.</li> <li>• Historically only core drilling was employed, either from surface or from underground.</li> <li>• Surface drilling: 149 holes, total 55,570 meters; vertical and inclined, maximum</li> </ul>

Criteria	JORC Code explanation	Commentary
		<p>depth 1596m (structural hole). Core diameters from 220mm near surface to 110 mm at depth. Average core recovery 89.3%.</p> <ul style="list-style-type: none"> <li>Underground drilling: 766 holes for 53,126m; horizontal and inclined. Core diameter 46mm; drilled by Craelius XC42 or DIAMEC drills.</li> </ul>
<i>Drill sample recovery</i>	<ul style="list-style-type: none"> <li><i>Method of recording and assessing core and chip sample recoveries and results assessed.</i></li> <li><i>Measures taken to maximise sample recovery and ensure representative nature of the samples.</i></li> <li><i>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</i></li> </ul>	<ul style="list-style-type: none"> <li>Core recovery for historical surface drill holes was recorded on drill logs and entered into the database.</li> <li>No correlation between grade and core recovery was established.</li> </ul>
<i>Logging</i>	<ul style="list-style-type: none"> <li><i>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</i></li> <li><i>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography.</i></li> <li><i>The total length and percentage of the relevant intersections logged.</i></li> </ul>	<ul style="list-style-type: none"> <li>In 2014-2021, core descriptions were recorded into paper logging forms by hand and later entered into an Excel database.</li> <li>Core was logged in detail historically in a facility 6km from the mine site. The following features were logged and recorded in paper logs: lithology, alteration (including intensity divided into weak, medium and strong/pervasive), and occurrence of ore minerals expressed in %, macroscopic description of congruous intervals and structures and core recovery.</li> </ul>
<i>Sub-sampling techniques and sample preparation</i>	<ul style="list-style-type: none"> <li><i>If core, whether cut or sawn and whether quarter, half or all core taken.</i></li> <li><i>If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry.</i></li> <li><i>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</i></li> <li><i>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</i></li> <li><i>Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling.</i></li> <li><i>Whether sample sizes are appropriate to the grain size of the material being sampled.</i></li> </ul>	<ul style="list-style-type: none"> <li>In 2014-21, core was washed, geologically logged, sample intervals determined and marked then the core was cut in half. Larger core was cut in half and one half was cut again to obtain a quarter core sample. One half or one quarter samples was delivered to ALS Global for assaying after duplicates, blanks and standards were inserted in the sample stream. The remaining drill core is stored on site for reference.</li> <li>Sample preparation was carried out by ALS Global in Romania, using industry standard techniques appropriate for the style of mineralisation represented at Cinovec.</li> <li>Historically, core was either split or consumed entirely for analyses.</li> <li>Samples are considered to be representative.</li> <li>Sample sizes relative to grain sizes are deemed appropriate for the analytical techniques used.</li> </ul>

Criteria	JORC Code explanation	Commentary
Quality of assay data and laboratory tests	<ul style="list-style-type: none"> <li>• <i>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</i></li> <li>• <i>For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.</i></li> <li>• <i>Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established.</i></li> </ul>	<ul style="list-style-type: none"> <li>• In 2014-21, core samples were assayed by ALS Global. The most appropriate analytical methods were determined by results of tests for various analytical techniques.</li> <li>• The following analytical methods were chosen: ME-MS81 (lithium borate fusion or 4 acid digest, ICP-MS finish) for a suite of elements including Sn and W and ME-4ACD81 (4 acid digest, ICP-AES finish) additional elements including lithium.</li> <li>• About 40% of samples were analysed by ME-MS81d (ME-MS81 plus whole rock package). Samples with over 1% tin are analysed by XRF. Samples over 1% lithium were analysed by Li-OG63 (four acid and ICP finish).</li> <li>• Standards, blanks and duplicates were inserted into the sample stream. Initial tin standard results indicated possible downgrading bias; the laboratory repeated the analysis with satisfactory results.</li> <li>• Historically, Sn content was measured by XRF and using wet chemical methods. W and Li were analysed by spectral methods.</li> <li>• Analytical QA was internal and external. The former subjected 5% of the sample to repeat analysis in the same facility. 10% of samples were analysed in another laboratory, also located in Czechoslovakia. The QA/QC procedures were set to the State norms and are considered adequate. It is unknown whether external standards or sample duplicates were used.</li> <li>• Overall accuracy of sampling and assaying was proved later by test mining and reconciliation of mined and analysed grades.</li> </ul>
Verification of sampling and assaying	<ul style="list-style-type: none"> <li>• <i>The verification of significant intersections by either independent or alternative company personnel.</i></li> <li>• <i>The use of twinned holes.</i></li> <li>• <i>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</i></li> <li>• <i>Discuss any adjustment to assay data.</i></li> </ul>	<ul style="list-style-type: none"> <li>• During the 2014-21 drill campaigns Geomet indirectly verified grades of tin and lithium by comparing the length and grade of mineral intercepts with the current block model.</li> </ul>
Location of data points	<ul style="list-style-type: none"> <li>• <i>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource</i></li> </ul>	<ul style="list-style-type: none"> <li>• In 2014-21, drill collar locations were surveyed by a registered surveyor.</li> <li>• Down hole surveys were recorded by a contractor.</li> </ul>

Criteria	JORC Code explanation	Commentary
	<p><i>estimation.</i></p> <ul style="list-style-type: none"> <li>• <i>Specification of the grid system used.</i></li> <li>• <i>Quality and adequacy of topographic control.</i></li> </ul>	<ul style="list-style-type: none"> <li>• Historically, drill hole collars were surveyed with a great degree of precision by the mine survey crew.</li> <li>• Hole locations are recorded in the local S-JTSK Krovak grid.</li> <li>• Topographic control is excellent.</li> </ul>
<i>Data spacing and distribution</i>	<ul style="list-style-type: none"> <li>• <i>Data spacing for reporting of Exploration Results.</i></li> <li>• <i>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</i></li> <li>• <i>Whether sample compositing has been applied.</i></li> </ul>	<ul style="list-style-type: none"> <li>• Historical data density is very high.</li> <li>• Spacing is sufficient to establish Measured, Indicated and Inferred Mineral Resource Estimates.</li> <li>• Areas with lower coverage of Li% assays have been identified as Exploration Targets.</li> <li>• Sample compositing to 1m intervals has been applied mathematically prior to estimation but not physically.</li> </ul>
<i>Orientation of data in relation to geological structure</i>	<ul style="list-style-type: none"> <li>• <i>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</i></li> <li>• <i>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</i></li> </ul>	<ul style="list-style-type: none"> <li>• In 2014-21, drill hole azimuth and dip was planned to intercept the mineralized zones at near-true thickness. As the mineralized zones dip shallowly to the south, drill holes were vertical or near vertical and directed to the north. Due to land access restrictions, certain holes could not be positioned in sites with ideal drill angle.</li> <li>• Geomet has not directly collected any samples underground because the workings are inaccessible at this time.</li> <li>• Based on historic reports, level plan maps, sections and core logs, the samples were collected in an unbiased fashion, systematically on two underground levels from drift ribs and faces, as well as from underground holes drilled perpendicular to the drift directions. The sample density is adequate for the style of deposit.</li> <li>• Multiple samples were taken and analysed by the Company from the historic tailing repository. Only lithium was analysed (Sn and W too low). The results matched the historic grades.</li> </ul>
<i>Sample security</i>	<ul style="list-style-type: none"> <li>• <i>The measures taken to ensure sample security.</i></li> </ul>	<ul style="list-style-type: none"> <li>• In the 2014-21 programs, only Geomet's employees and contractors handled drill core and conducted sampling. The core was collected from the drill rig each day and transported in a company vehicle to the secure Geomet premises where it was logged and cut. Geomet geologists supervised the process and logged/sampled the core. The samples were transported by Geomet personnel in a company vehicle to the ALS Global laboratory pick-up station. The remaining core is stored under lock and key.</li> <li>• Historically, sample security was ensured</li> </ul>

Criteria	JORC Code explanation	Commentary
		by State norms applied to exploration. The State norms were similar to currently accepted best practice and JORC guidelines for sample security.
<i>Audits or reviews</i>	<ul style="list-style-type: none"> <li><i>The results of any audits or reviews of sampling techniques and data.</i></li> </ul>	<ul style="list-style-type: none"> <li>Review of sampling techniques was carried out from written records. No flaws found.</li> </ul>

## Section 2 Reporting of Exploration Results

(Criteria listed in section 1 also apply to this section.)

Criteria	JORC Code explanation	Commentary
<i>Mineral tenement and land tenure status</i>	<ul style="list-style-type: none"> <li><i>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</i></li> <li><i>The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.</i></li> </ul>	<ul style="list-style-type: none"> <li>In June 2020, the Czech Ministry of the Environment granted Geomet three Preliminary Mining Permits which cover the whole of the Cinovec deposit. The permits are valid until 2028.</li> <li>Geomet plans to amalgamate these into a single Final Mining Permit.</li> </ul>
<i>Exploration done by other parties</i>	<ul style="list-style-type: none"> <li><i>Acknowledgment and appraisal of exploration by other parties.</i></li> </ul>	<ul style="list-style-type: none"> <li>There has been no acknowledgment or appraisal of exploration by other parties.</li> </ul>
<i>Geology</i>	<ul style="list-style-type: none"> <li><i>Deposit type, geological setting and style of mineralisation.</i></li> </ul>	<ul style="list-style-type: none"> <li>Cinovec is a granite-hosted tin-tungsten-lithium deposit.</li> <li>Late Variscan age, post-orogenic granite intrusion tin and tungsten occur in oxide minerals (cassiterite and wolframite). Lithium occurs in zinnwaldite, a Li-rich muscovite.</li> <li>Mineralization in a small granite cupola. Vein and greisen type. Alteration is greisenisation, silicification.</li> </ul>
<i>Drill hole Information</i>	<ul style="list-style-type: none"> <li><i>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes:</i> <ul style="list-style-type: none"> <li><i>easting and northing of the drill hole collar</i></li> <li><i>elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</i></li> <li><i>dip and azimuth of the hole</i></li> <li><i>down hole length and interception depth</i></li> </ul> </li> </ul>	<ul style="list-style-type: none"> <li>Reported previously.</li> </ul>

Criteria	JORC Code explanation	Commentary
	<ul style="list-style-type: none"> <li>○ hole length.</li> <li>● <i>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.</i></li> </ul>	
<i>Data aggregation methods</i>	<ul style="list-style-type: none"> <li>● <i>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (eg cutting of high grades) and cut-off grades are usually Material and should be stated.</i></li> <li>● <i>Where aggregate intercepts incorporate short lengths of high grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</i></li> <li>● <i>The assumptions used for any reporting of metal equivalent values should be clearly stated.</i></li> </ul>	<ul style="list-style-type: none"> <li>● Reporting of exploration results has not and will not include aggregate intercepts.</li> <li>● Metal equivalent not used in reporting.</li> <li>● No grade truncations applied.</li> </ul>
<i>Relationship between mineralisation widths and intercept lengths</i>	<ul style="list-style-type: none"> <li>● <i>These relationships are particularly important in the reporting of Exploration Results.</i></li> <li>● <i>If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported.</i></li> <li>● <i>If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (eg 'down hole length, true width not known').</i></li> </ul>	<ul style="list-style-type: none"> <li>● Intercept widths are approximate true widths.</li> <li>● The mineralization is mostly of disseminated nature and relatively homogeneous; the orientation of samples is of limited impact.</li> <li>● For higher grade veins care was taken to drill at angles ensuring closeness of intercept length and true widths.</li> <li>● The block model accounts for variations between apparent and true dip.</li> </ul>
<i>Diagrams</i>	<ul style="list-style-type: none"> <li>● <i>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</i></li> </ul>	<ul style="list-style-type: none"> <li>● Appropriate maps and sections have been generated by Geomet and independent consultants. Available in customary vector and raster outputs and partially in consultant's reports.</li> </ul>
<i>Balanced reporting</i>	<ul style="list-style-type: none"> <li>● <i>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high</i></li> </ul>	<ul style="list-style-type: none"> <li>● Balanced reporting in historic reports guaranteed by norms and standards, verified in 1997 and 2012 by independent consultants.</li> </ul>

<b>Criteria</b>	<b>JORC Code explanation</b>	<b>Commentary</b>
<i>Other substantive exploration data</i>	<p><i>grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</i></p> <ul style="list-style-type: none"> <li><i>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</i></li> </ul>	<ul style="list-style-type: none"> <li>The historic reporting was completed by several State institutions and cross validated.</li> <li>Data available: bulk density for all representative rock and ore types; (historic data + 92 measurements in 2016-21 from current core holes); petrographic and mineralogical studies, hydrological information, hardness, moisture content, fragmentation etc.</li> </ul>
<i>Further work</i>	<ul style="list-style-type: none"> <li><i>The nature and scale of planned further work (eg tests for lateral extensions or depth extensions or large-scale step-out drilling).</i></li> <li><i>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</i></li> </ul>	<ul style="list-style-type: none"> <li>Grade verification sampling from underground or drilling from surface. Historically-reported grades require modern validation in order to improve resource classification.</li> <li>The number and location of sampling sites will be determined from a 3D wireframe model and geostatistical considerations reflecting grade continuity.</li> <li>The geologic model will be used to determine if any infill drilling is required.</li> <li>The deposit is open down-dip on the southern extension, and locally poorly constrained at its western and eastern extensions, where limited additional drilling might be required.</li> <li>No large-scale drilling campaigns are required.</li> </ul>

## Section 3 Estimation and Reporting of Mineral Resources

(Criteria listed in section 1, and where relevant in section 2, also apply to this section.)

Criteria	JORC Code explanation	Commentary
<i>Database integrity</i>	<ul style="list-style-type: none"> <li>Measures taken to ensure that data has not been corrupted by, for example, transcription or keying errors, between its initial collection and its use for Mineral Resource estimation purposes.</li> <li>Data validation procedures used.</li> </ul>	<ul style="list-style-type: none"> <li>Assay and geologic data were compiled by Geomet staff from primary historic records, such as copies of drill logs and large scale sample location maps.</li> <li>Sample data were entered in to Excel spreadsheets by Geomet staff.</li> <li>The database entry process was supervised by a Professional Geologist who works for Geomet.</li> <li>The database was checked by independent competent persons (Lynn Widenbar of Widenbar &amp; Associates).</li> </ul>
<i>Site visits</i>	<ul style="list-style-type: none"> <li>Comment on any site visits undertaken by the Competent Person and the outcome of those visits.</li> <li>If no site visits have been undertaken indicate why this is the case.</li> </ul>	<ul style="list-style-type: none"> <li>The site was visited by Dr Pavel Reichl who identified the previous shaft sites, tails dams and observed the mineralisation underground through an adjacent mine working and was previously the Competent Person for exploration results.</li> <li>The current Competent Person for exploration results, Dr Vojtech Sesulka, has visited the site on multiple occasions and has been involved in 2014 to 2021 drilling campaigns.</li> <li>The site was visited in June 2016 by Mr Lynn Widenbar, the Competent Person for Mineral Resource Estimation. Diamond drill rigs were viewed, as was core; a visit was carried out to the adjacent underground mine in Germany which is a continuation of the Cinovec Deposit.</li> </ul>
<i>Geological interpretation</i>	<ul style="list-style-type: none"> <li>Confidence in (or conversely, the uncertainty of) the geological interpretation of the mineral deposit.</li> <li>Nature of the data used and of any assumptions made.</li> <li>The effect, if any, of alternative interpretations on Mineral Resource estimation.</li> <li>The use of geology in guiding and controlling Mineral Resource estimation.</li> <li>The factors affecting continuity both of grade and geology.</li> </ul>	<ul style="list-style-type: none"> <li>The overall geology of the deposit is relatively simple and well understood due to excellent data control from surface and underground.</li> <li>Nature of data: underground mapping, structural measurements, detailed core logging, 3D data synthesis on plans and maps.</li> <li>Geological continuity is good. The grade is highest and shows most variability in quartz veins.</li> <li>Grade correlates with degree of silicification and greisenisation of the host granite.</li> <li>The primary control is the granite-country rock contact. All mineralization is in the uppermost</li> </ul>

Criteria	JORC Code explanation	Commentary
		200m of the granite and is truncated by the contact.
<i>Dimensions</i>	<ul style="list-style-type: none"> <li><i>The extent and variability of the Mineral Resource expressed as length (along strike or otherwise), plan width, and depth below surface to the upper and lower limits of the Mineral Resource.</i></li> </ul>	<ul style="list-style-type: none"> <li>The Cinovec Deposit strikes north-south, is elongated, and dips gently south parallel to the upper granite contact. The surface projection of mineralization is about 1km long and 900m wide.</li> <li>Mineralization extends from about 200m to 500m below surface.</li> </ul>
<i>Estimation and modelling techniques</i>	<ul style="list-style-type: none"> <li><i>The nature and appropriateness of the estimation technique(s) applied and key assumptions, including treatment of extreme grade values, domaining, interpolation parameters and maximum distance of extrapolation from data points. If a computer assisted estimation method was chosen include a description of computer software and parameters used.</i></li> <li><i>The availability of check estimates, previous estimates and/or mine production records and whether the Mineral Resource estimate takes appropriate account of such data.</i></li> <li><i>The assumptions made regarding recovery of by-products.</i></li> <li><i>Estimation of deleterious elements or other non-grade variables of economic significance (eg sulphur for acid mine drainage characterisation).</i></li> <li><i>In the case of block model interpolation, the block size in relation to the average sample spacing and the search employed.</i></li> <li><i>Any assumptions behind modelling of selective mining units.</i></li> <li><i>Any assumptions about correlation between variables.</i></li> <li><i>Description of how the geological interpretation was used to control the resource estimates.</i></li> <li><i>Discussion of basis for using or not using grade cutting or capping.</i></li> <li><i>The process of validation, the checking process used, the comparison of model data to drill hole data, and use of reconciliation data if available.</i></li> </ul>	<ul style="list-style-type: none"> <li>Block estimation was carried out in Micromine 2021.5 using Ordinary Kriging interpolation.</li> <li>A geological domain model was constructed using Leapfrog software with solid wireframes representing greisen, granite, greisenised granite and the overlying barren rhyolite. This was used to both control interpolation and to assign density to the model (2.57 for granite, 2.70 for greisen and 2.60 for all other material).</li> <li>Analysis of sample lengths indicated that compositing to 1m was necessary.</li> <li>Search ellipse sizes and orientations for the estimation were based on drill hole spacing, the known orientations of mineralisation and variography.</li> <li>An “unfolding” search strategy was used which allowed the search ellipse orientation to vary with the locally changing dip and strike.</li> <li>After statistical analysis, a top cut of 5% was applied to Sn% and W%; a 1.2% top cut is applied to Li%.</li> <li>Sn% and Li% were then estimated by Ordinary Kriging within the mineralisation solids.</li> <li>The primary search ellipse was 150m along strike, 150m down dip and 7.5m across the mineralisation. A minimum of 4 composites and a maximum of 8 composites were required.</li> <li>A second interpolation with search ellipse of 300m x 300m x 12.5m was carried out to inform blocks to be used as the basis for an exploration target.</li> <li>Block size was 10m (E-W) by 10m (N-S) by 5m</li> <li>Validation of the final resource has been carried out in a number of ways including section comparison of data versus model, swath plots and</li> </ul>

Criteria	JORC Code explanation	Commentary
		production reconciliation. All methods produced satisfactory results.
Moisture	<ul style="list-style-type: none"> <li>Whether the tonnages are estimated on a dry basis or with natural moisture, and the method of determination of the moisture content.</li> </ul>	<ul style="list-style-type: none"> <li>Tonnages are estimated on a dry basis using the average bulk density for each geological domain.</li> </ul>
Cut-off parameters	<ul style="list-style-type: none"> <li>The basis of the adopted cut-off grade(s) or quality parameters applied.</li> </ul>	<ul style="list-style-type: none"> <li>A series of alternative cutoffs was used to report tonnage and grade: Lithium 0.1%, 0.2%, 0.3% and 0.4%.</li> <li>The final reporting cutoff of 0.1% Li was chosen based on underground mining studies carried out By Bara Consulting in 2017 while developing an initial Probable Ore Reserve Estimate.</li> </ul>
Mining factors or assumptions	<ul style="list-style-type: none"> <li>Assumptions made regarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made.</li> </ul>	<ul style="list-style-type: none"> <li>Mining is assumed to be by underground methods, with fill.</li> <li>An updated Preliminary Feasibility Study prepared in 2019 established that it was feasible and economic to use large-scale, long-hole open stope mining.</li> <li>The 2022 updated Preliminary Feasibility Study establishes that it is feasible and economic to mine using long hole open stoping with paste backfill.</li> <li>Using a total processing cost of \$41/t and a recovery of 77% of Li grade in ROM ore, a gross payable value per ROM ore tonne of \$96/t (\$55/t net margin) has been assumed before inclusion in the mine plan.</li> </ul>
Metallurgical factors or assumptions	<ul style="list-style-type: none"> <li>The basis for assumptions or predictions regarding metallurgical amenability. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential metallurgical methods, but the assumptions regarding metallurgical treatment processes and parameters made when reporting Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the metallurgical assumptions made.</li> </ul>	<ul style="list-style-type: none"> <li>Successful locked-cycle tests (“LCT”) results carried out in 2022 and a pilot programme carried out in 2023 demonstrate the Cinovec project’s ability to produce battery-grade lithium carbonate. <ul style="list-style-type: none"> <li>European Metals has also demonstrated that Cinovec battery grade lithium carbonate can be easily converted into lithium hydroxide monohydrate with a commonly utilised liming plant process.</li> <li>Six LCTs were run in 2022 and the crude lithium carbonate from LCTs 4, 5 and 6 was successfully converted to battery grade lithium carbonate.</li> <li>Lithium recoveries of up to 93% were achieved in the LCTs performed.</li> <li>The LCTs and the pilot programme tested zinnwaldite concentrate from</li> </ul> </li> </ul>

Criteria	JORC Code explanation	Commentary
		<p>the southern part of Cinovec, representative of the first five years of mining.</p> <ul style="list-style-type: none"> <li>The 2023 pilot programme successfully demonstrated the hydrometallurgical process flowsheet on a semi-industrial batch-continuous basis..</li> <li>Extensive testwork was conducted on Cinovec ore in the past. Testing culminated with a pilot plant trial in 1970, where three batches of Cinovec ore were processed, each under slightly different conditions. The best result, with a tin recovery of 76.36%, was obtained from a batch of 97.13t grading 0.32% Sn. A more elaborate flowsheet was also investigated and with flotation produced final Sn and W recoveries of better than 96% and 84%, respectively.</li> <li>Historical laboratory testwork also demonstrated that lithium can be extracted from the ore (lithium carbonate was produced from 1958-1966 at Cinovec).</li> </ul>
<i>Environmental factors or assumptions</i>	<ul style="list-style-type: none"> <li><i>Assumptions made regarding possible waste and process residue disposal options. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider the potential environmental impacts of the mining and processing operation. While at this stage the determination of potential environmental impacts, particularly for a greenfields project, may not always be well advanced, the status of early consideration of these potential environmental impacts should be reported. Where these aspects have not been considered this should be reported with an explanation of the environmental assumptions made.</i></li> </ul>	<ul style="list-style-type: none"> <li>Cinovec is in an area of historic mining activity spanning the past 600 years. Extensive State exploration was conducted until 1990.</li> <li>The property is located in a sparsely populated area, most of the land belongs to the State. Few problems are anticipated with regards to the acquisition of surface rights for any potential underground mining operation.</li> <li>The envisaged mining method will see much of the waste and tailings used as underground fill.</li> </ul>
<i>Bulk density</i>	<ul style="list-style-type: none"> <li><i>Whether assumed or determined. If assumed, the basis for the assumptions. If determined, the method used, whether wet or dry, the frequency of the measurements, the nature, size and representativeness of the samples.</i></li> <li><i>The bulk density for bulk material</i></li> </ul>	<ul style="list-style-type: none"> <li>Historical bulk density measurements were made in a laboratory.</li> <li>The following densities were applied: <ul style="list-style-type: none"> <li>2.57 for granite</li> <li>2.70 for greisen</li> <li>2.60 for all other material</li> </ul> </li> </ul>

Criteria	JORC Code explanation	Commentary
	<p><i>must have been measured by methods that adequately account for void spaces (vugs, porosity, etc), moisture and differences between rock and alteration zones within the deposit.</i></p> <ul style="list-style-type: none"> <li>• <i>Discuss assumptions for bulk density estimates used in the evaluation process of the different materials.</i></li> </ul>	
Classification	<ul style="list-style-type: none"> <li>• <i>The basis for the classification of the Mineral Resources into varying confidence categories.</i></li> <li>• <i>Whether appropriate account has been taken of all relevant factors (ie relative confidence in tonnage/grade estimations, reliability of input data, confidence in continuity of geology and metal values, quality, quantity and distribution of the data).</i></li> <li>• <i>Whether the result appropriately reflects the Competent Person's view of the deposit.</i></li> </ul>	<ul style="list-style-type: none"> <li>• The new 2014 to 2021 drilling has confirmed the Lithium mineralisation model and allowed the Mineral Resource to be classified in the Measured, Indicated and Inferred categories.</li> <li>• The detailed classification is based on a combination of drill hole spacing and the output from the kriging interpolation.</li> <li>• Measured material is located in the south of the deposit in the area of new infill drilling carried out between 2014 and 2021.</li> <li>• Material outside the classified area has been used as the basis for an Exploration Target.</li> <li>• The Competent Person (Lynn Widenbar) endorses the final results and classification.</li> </ul>
Audits or reviews	<ul style="list-style-type: none"> <li>• <i>The results of any audits or reviews of Mineral Resource estimates.</i></li> </ul>	<ul style="list-style-type: none"> <li>• Wardell Armstrong International, in their review of Lynn Widenbar's initial resource estimate stated "the Widenbar model appears to have been prepared in a diligent manner and given the data available provides a reasonable estimate of the drillhole assay data at the Cinovec deposit".</li> </ul>
Discussion of relative accuracy/ confidence	<ul style="list-style-type: none"> <li>• <i>Where appropriate a statement of the relative accuracy and confidence level in the Mineral Resource estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the resource within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors that could affect the relative accuracy and confidence of the estimate.</i></li> <li>• <i>The statement should specify</i></li> </ul>	<ul style="list-style-type: none"> <li>• In 2012, WAI carried out model validation exercises on the initial Widenbar model, which included visual comparison of drilling sample grades and the estimated block model grades, and Swath plots to assess spatial local grade variability.</li> <li>• A visual comparison of Block model grades vs drillhole grades was carried out on a sectional basis for both Sn and Li mineralisation. Visually, grades in the block model correlated well with drillhole grade for both Sn and Li.</li> <li>• Swath plots were generated from the model by averaging composites and blocks in all 3 dimensions using 10m panels. Swath plots were generated</li> </ul>

Criteria	JORC Code explanation	Commentary
	<p><i>whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used.</i></p> <ul style="list-style-type: none"> <li>• <i>These statements of relative accuracy and confidence of the estimate should be compared with production data, where available.</i></li> </ul>	<p>for the Sn and Li estimated grades in the block model, these should exhibit a close relationship to the composite data upon which the estimation is based. As the original drillhole composites were not available to WAI. 1m composite samples based on 0.1% cut-offs for both Sn and Li assays were</p> <ul style="list-style-type: none"> <li>• Overall Swath plots illustrate a good correlation between the composites and the block grades. As is visible in the Swath plots, there has been a large amount of smoothing of the block model grades when compared to the composite grades, this is typical of the estimation method.</li> </ul>