



Bellevue Gold Mine
"A forgotten treasure"
 Unlocking the potential of
 one of Australia's historic
 great high-grade gold mines

Global Inferred Resource
1.8 Moz @ 11.1g/t gold
& historically produced
800,000oz @ 15g/t gold¹

Significant landholding of
+3,600km in a major gold
producing district

Corporate Directory
 Non-Executive Chairman
 Mr Kevin Tomlinson

Managing Director
 Mr Steve Parsons

Executive Director and Company
Secretary
 Mr Michael Naylor

Contact Details
 Principal and Registered Office
 Level 3, Suite 3
 24 Outram Street
 West Perth WA 6005
 T: +61 8 6424 8077
 E: admin@bellevuegold.com.au

ASX Code: BGL

www.bellevuegold.com.au

High-Grade Gold Drill Results & Exploration Update, Bellevue Gold Project

Continued high-grade gold drill results from ongoing diamond core drilling received from infill drilling at the Tribune and Viago Lodes. Results have now been received for the first 30,000 metres of the initial 80,000 metre infill program.

An additional 2 x diamond core drill rigs are being added taking the total to 8 x diamond core drill rigs onsite for the continuation of the infill program (2 x rigs) as well as the expansion step-out programme currently (6 x rigs) targeting the large scale high-grade Deacon & Mavis Discovery.

Infill Drilling Highlights:

- Shallow infill drilling completed at Tribune Lode in the top 200 metres from surface has consistently intersected the Lode as expected with numerous high-grade gold results reinforcing the current inferred resource model.
- A large portion of the current Tribune Lode inferred resource has now been infilled to 40 m x 20 m aimed at increasing the confidence level of the resource to be updated in 2020. Results include:
 - 9.6 m @ 14.1 g/t gold from 107.9 m in DRDD257
 - 3.0 m @ 33.0 g/t gold from 162.0 m in DRDD247
 - 1.9 m @ 29.3 g/t gold from 58 m in DRDD200
 - 5.2 m @ 5.4 g/t gold from 203 m in DRDD202
 - 0.6 m @ 273.5 g/t gold from 155.0 m in DRDD220
- Infill drilling has commenced at the Viago Lode with drilling to continue over the coming months ready for conversion to a higher resource confidence level in 2020. Results include:
 - 0.7 m @ 74.8 g/t gold from 590.4 m in DRDD227
 - 5.0 m @ 11.1 g/t gold from 606.0 m in DRDD222
 - 3.0 m @ 19.8 g/t gold from 580.5 m in DRDD233
- The infill diamond core drilling programme is now underway at the Viago, Bellevue South and Vlad Lodes with two rigs currently operating.

New Deacon & Mavis High-Grade Gold Discovery Highlights:

- Additional resources allocated to the Deacon and Mavis discovery with six rigs targeting step out expansion drilling as well as targeting a number of significant high-priority off-hole DHEM conductors during the remainder of Q4 2019.
- A number of new significant visual drill core intersections reported with visible gold from Deacon & Mavis Lodes drilling. Results expected to be received in the coming weeks.
- Results pending for a further 15,000 metres of completed diamond core infill and step out drilling ready for resource updates in 2020.

1. All material assumptions and technical parameters underpinning the Mineral Resource estimate in the ASX announcement dated 11 July 2019 continue to apply and have not materially changed since last reported.

Managing Director Mr Steve Parsons commented:

"We are pleased to update the market on the progress of the infill drilling of the current resource areas at the Bellevue Gold Project. Around 35% of the infill drill programme has now been completed and we anticipate making significant progress by the end of Qtr1 2020. Infill drill results continue to demonstrate the quality and high-grade of the Bellevue mineralised gold system.

The company has also sourced a further two diamond core drill rigs to operate through until the end of 2019 to allow the assessment of what looks like a very large and significant target at the Deacon and Mavis Lodes discovery. We now have six drill rigs operating over 1.8 kilometres of strike on this new discovery taking the total rigs to eight on site.

We are very excited by what we are seeing at the Deacon & Mavis discovery and intend to update the market as further results become available."

Drilling Update from the Bellevue Gold Project

Bellevue Gold Limited (ASX: BGL) is pleased to announce an exploration update from recent work completed at the Bellevue Gold Project, Western Australia. A total of eight rigs are currently operating with an additional two further rigs added to the fleet to drill through to the end of the year. Drilling is targeting exploration step out at the new Deacon & Mavis Discoveries and to infill areas to upgrade the resource category at the other target areas which currently form the current resource of 1.8 Million oz @ 11.1 g/t gold of Inferred category resources¹.

Excellent progress is being made with approximately 30,000 metres of infill completed of the current budgeted programme of 80,000 metres. Assays are currently pending for a further 15,000 metres of drilling from the Deacon Discovery and the Viago North infill.

Due to the significant potential scale of the Deacon & Mavis discoveries and based on visual indications of gold mineralisation associated with the step out DHEM plates (conductors) at Deacon, further resources have been allocated to the target during the remainder of the 2019 drill programme. A total of six diamond core drill rigs are currently drilling the Deacon corridor.

The Deacon mineralised shear zone represents the fourth known significant mineralised shear zone to host high grade gold mineralisation in the Bellevue lode system after the (1) Bellevue Shear (0.7 Moz produced and current inferred resources of 0.7 Moz @ 9.6 g/t), (2) Viago Shear (current inferred resource of 0.7 Moz @ 16.1 g/t) and the (3) Tribune Shear (current inferred resource of 0.3 Moz @ 8.1 g/t)¹. **All four mineralised shear zones and lodes are located within 400 metres of existing underground development and are of similar strike extent.**

Infill drilling at the Tribune and Viago Lodes is ongoing with two rigs currently continuing the infill drill programme.

Tribune Lode Infill Drilling

Drilling has been completed over the main portion of the Tribune Lode in the top 200 metres to drill out the lode to 40 metre x 20 metre centres. Received drill results from Tribune are in line with the current interpretation and have supported the gentle plunge of the bonanza grade mineralised shoots, similar to what was seen and mined at the parallel Bellevue underground mine. A total of 42 holes have been completed as part of the Tribune infill programme.

DRDD220	0.6 m @ 273.5 g/t gold	from 155 m
DRDD224	2.3m @ 8.2 g/t gold	from 158 m and 0.6 m @ 26.4 g/t gold from 179 m
DRDD227	2.2 m @ 12.3 g/t gold	from 262 m
DRDD230	2.4 m @ 5.3 g/t gold	from 80 m
DRDD241	5.8 m @ 1.9 g/t gold	from 69 m
DRDD246	0.9 m @ 36.0 g/t gold	from 148 m
DRDD247	1.3 m @ 13.6 g/t gold	from 137 m and 3.0 m @ 32.2 g/t gold from 162 m
DRDD249	3.3 m @ 3.8 g/t gold	from 80 m

DRDD253 **5.6 m @ 3.1 g/t gold** from 201 m
 DRDD257 **9.6 m @ 14.1 g/t gold** from 107 m
 DRDD261 **3.8 m @ 3.1 g/t gold** from 262 m
 DRDD270 **1.3 m @ 25.0 g/t gold** from 23.4 m
 DRDD200 **1.9 m @ 29.2 g/t gold** from 58 m (refer asx 05/08/19)
 DRDD202 **5.2 m @ 5.4 g/t gold** from 203 m (refer asx 05/08/19)

Key points related to the Tribune Lode are:

- The Tribune Lode, including Tribune North, has a current Inferred resource of 1.0 Mt @ 8.1 g/t gold for 0.3 Million ounces of contained gold.¹
- The Tribune Shear strike length has a total of 1,300 metres strike length and remains open to the north and south.
- DHEM indicates the continuation of the **significant untested DHEM conductive plates** to the south of the high-grade plunge as well as a number of newly identified, untested, EM conductive plates to the north of current resources.
- Mineralization is located only 300 metres west of the existing historic underground mine development.
- Drilling has confirmed a well-defined gentle southeast plunge to the mineralised shoots as anticipated with the updated structural model and supported by observations at the Bellevue Mine.
- Mineralised shoots remain **completely open both to the north, south and at depth**.

Recent drilling from Tribune support previously released intersections including:²

DRCD004	5 m @ 22.9 g/t gold from 25 m (asx 11/12/17)
DRRC1024	7 m @ 27.4 g/t gold from 93 m (asx 20/11/17)
DRDD006	15 m @ 5.8 g/t gold from 79.5 m (including 0.3m @ 242g/t gold from 79.5 m) (asx 07/02/18)
DRDD010	12 m @ 12.0 g/t gold from 68 m (asx 07/02/18)
DRDD013	2.4 m @ 21.9 g/t gold from 162.8 m (asx 07/02/18)
DRCD020	3.8 m @ 5.2 g/t gold from 133 m and 2.5 m @ 29 g/t gold from 147.5 m (asx 22/03/18)
DRDD036	2.4 m @ 16.6 g/t gold from 102.4 m (asx 22/03/18)
DRCC033	8 m @ 5.0 g/t gold from 53 m including 4m @ 9.0 g/t gold from 57 m (asx 22/03/18)
DRDD034	7 m @ 7.2 g/t gold including 2 m @ 17.8 g/t from 289 m (asx 22/03/18)
DRDD057	4.5 m @ 13.3 g/t gold from 305.5 m (asx 23/05/18)
DRDD069	10.1 m @ 29.0 g/t gold from 188.5 m (asx 26/09/18)
DRRC143	5 m @ 27.3 g/t gold from 41 m (asx 26/08/18)
DRRC146	7 m @ 8.2 g/t gold from 34 m (asx 26/08/18)
DRDD111	6 m @ 24.9 g/t gold from 188 m (asx 14/03/19)
DRDD112	6.5 m @ 22.2 g/t gold from 96 m (asx 14/03/19)
DRDD153	3.2 m @ 17.2 g/t gold from 75.2 m (asx 21/05/19)
DRDD171	4.5 m @ 4.8 g/t gold from 172.5 m (asx 21/05/19)
DRDD157	7.0 m @ 2.8 g/t gold from 192.5 m (asx 21/05/19)
DRDD168	1.1 m @ 17.2 g/t gold from 221.2 m (asx 21/05/19)
DRDD158	2.2 m @ 6.8 g/t gold from 131 m (asx 21/05/19)
DRDD137	2.2 m @ 5.5 g/t gold from 190.5 m (asx 21/05/19)
DRCD020W1	2.7 m @ 22.6 g/t gold from 146.4 m (asx 21/05/19)
DRDD136	0.3 m @ 218.5 g/t gold from 210 m (asx 21/05/19)
DRDD127	3.6 m @ 12.2 g/t gold from 24.7 m (asx 21/05/19)
DRDD175A	3.5 m @ 15.1 g/t gold from 356 m (asx 15/07/19)
DRDD181	2.4 m @ 9.9 g/t gold from 257 m (asx 15/07/19)
DRDD166	2.6 m @ 11.4 g/t gold from 202 m (asx 15/07/19)
DRDD171	4.5 m @ 4.8 g/t gold from 172 m (asx 15/07/19)

Figure 1: Drill core from Tribune infill diamond core hole DRDD247 high-grade mineralization associated with ~30% semi massive pyrrhotite, trace disseminated chalcopyrite and fine-grained visible gold. Interval assayed 3m @ 32.2 g/t gold from 137 m.



Figure 2: Drill core from Tribune infill diamond core hole DRDD257 high-grade mineralization associated with ~15% semi massive pyrrhotite, trace disseminated chalcopyrite and fine-grained visible gold. Interval assayed 9.6m @ 14.1 g/t gold from 107m.





Figure 3: Long Section of Tribune Lode showing southerly plunge to the high-grade ore shoots. Mineralisation has been defined over 1,300 m and remains open to the north and south. View looking east. MGA 94 Zone 51



Further Drill Results from the Viago Lode

Since the majority of infill drilling has now been completed at the main portion of the Tribune Lode, infill drilling has commenced at the Viago Lode with the Viago North area currently being infilled to 40 metre x 40 metre centres with two diamond core drill rigs operating to complete the programme. A number of holes from the Tribune infill programme were also extended to intercept the Viago Main Lode.

New results from the Viago Main Lode include:

DRDD227	0.7 m @ 74.8 g/t gold from 590.4m
DRDD222	5.0 m @ 11.1 g/t gold from 606m
DRDD233	3.0 m @ 19.8 g/t gold from 580m
DRDD202	2.1 m @ 8.6 g/t gold from 607.5

And further recent results from Viago North Include:

DRDD204	3.5 m @ 3.1 g/t gold from 441.8m
DRDD205	0.7 m @ 15.9 g/t gold from 422m
DRDD215	5 m @ 5.5 g/t gold from 395m
DRDD217	2.2 m @ 6.1 g/t gold from 415.2m

Key points related to the Viago Lode are:

- The Viago lode, has a current Inferred resource of 1.3 Mt @ 16.1 g/t Au for 0.7 Million ounces of contained gold¹. The resource is made up of the Viago Main and the northern block known as Viago North.
- Recent drilling has confirmed the intersection of the Viago Shear and Bellevue Shear as an important shoot control with high grade mineralisation on both the gently dipping Viago Shear and also on the moderately west dipping Bellevue shear, south of the historic mine.


- The Viago North extensions come to **within 100 metres of existing historic development** and are within 400 metres of the surface. **Viago mineralisation continues to shallow to the north where it remains untested.**
- Primary mineralised shoot control is interpreted to be subparallel to the Tribune and Bellevue mineralised shoot orientations. **Mineralisation style is analogous to the Bellevue Lode.**

The current geological model predicts **significant potential for repetitions of Viago style lodes**. This is supported by the observation of a number of further, albeit uneconomic, sub-horizontal, gently south plunging mineralised shears already observed within the drilling area.

Previously released high grade drill results from Viago include²:

DRDD069	3 m @ 87.6 g/t gold from 597 m <i>including 0.5 m @ 445.0 g/t gold</i> from 598 m (refer asx 09/10/18)
DRDD073	6.4 m @ 27.9 g/t gold from 587.6 m <i>including 2.8 m @ 62.8 g/t gold</i> from 587.6 m (refer asx 09/10/18)
DRDD013	4.3 m @ 58.8 g/t gold from 575.5 m (refer asx 06/08/18) ¹
DRDD072	2.8 m @ 32.3 g/t gold from 606.8 m (refer asx 09/10/18)
DRDD070	3.35 m @ 37.4 g/t gold from 562.45 m (refer ASX 26/09/18)
DRCDW020	6.9 m @ 18.0 g/t gold from 535.9 m <i>including 0.35 m @ 203.3 g/t gold</i> from 540.8 m (refer asx 09/10/18)
DRDD065	2.8 m @ 19.0 g/t gold from 571.65 m (refer ASX 26/09/18)
DRCD022	2.5 m @ 13.1 g/t gold from 560.5 m (refer ASX 17/07/18)
DRDD066	1.5 m @ 23.9 g/t gold from 566.3 m (refer ASX 26/09/18)
DRDD059	4.3 m @ 8.8 g/t gold from 575.3 m (refer ASX 30/05/18)
DRDD144	3.2 m @ 13.8 g/t gold from 409.6m (refer asx 21/05/19)
DRDD156	4.1 m @ 6.0 g/t gold from 406.5 m (refer asx 21/05/19)
DRDD151	0.7 m @ 13.6 g/t gold from 465.5 m (refer asx 21/05/19)
DRDD142	0.8 m @ 16.2 g/t gold from 446.6 m (refer asx 21/05/19)
DRDD158	3.5 m @ 13.4 g/t gold from 528 m in (refer asx 21/05/19)

Figure 4: Plan view of Viago Lode showing recent northern discovery & southern extensions. New holes relating to this announcement are shown with a star symbol. MGA94 Zone 51



Update on the new Deacon & Mavis Lodes Discovery

Exploration at Deacon Discovery has been accelerated with six diamond core drill rigs currently targeting the discovery. Visual indications continue to define a large mineralisation system with recent drilling and DHEM indicating a number of high priority targets for immediate follow up. The company has made the decision to expedite drilling at the discovery due to the potential size of the target, analogies with the Bellevue Lode geometry and mineralisation style.

Most drilling to date has been on very broad spacings typically +180 metre drill spacings across 1,800 metres of strike and only testing a small portion of up & down dip continuations.

No new results from Deacon are reported in this announcement with results pending for a number of holes and a further update on drilling results at Deacon anticipated as soon as further results are made available.

Previously reported results from Deacon include:²

DRDD237	3.8 m @ 13.9 g/t gold and 1.7 m @ 5.9 g/t gold – Deacon Lode. (refer asx 02/10/19)
DRDD225	0.8 m @ 36.9 g/t gold – Deacon Lode. (refer asx 02/10/19)
DRDD218	4.4 m @ 62.4 g/t gold – Deacon Lode. (refer asx 10/09/19)
DRDD130	3.6 m @ 18.3 g/t gold including 2.2 m @ 27.8 g/t gold – Deacon Lode. (refer asx 05/08/19) and 2.2 m @ 38.0 g/t gold including 1.1 m @ 75.3 g/t gold – Mavis Lode.
DRDD088	1.8 m @ 5.9 g/t gold (refer asx 05/08/19)
DRDD086	2.0 m @ 4.2 g/t gold and 2.4 m @ 4.9 g/t gold (refer asx 05/08/19)
DRDD139	2.5 m @ 5.1 g/t gold (refer asx 05/08/19)
DRDD110	2.0 m @ 4.9 g/t gold (refer asx 05/08/19)
DRDD105	9.5 m @ 0.5 g/t gold (refer asx 05/08/19)

Summary logs of the recently completed holes are included in the appendix along with core photos from holes DRDD295 and DRDD273, refer to figures 5 and 6 below.

Drillhole DRDD273 is significant as it is the first follow up hole into the substantial previously untested southern DHEM plate. The hole confirms the potential for significant possible strike extensions related to the other previously defined DHEM plates at the target.

DRDD295 is a 140 metre north step out on previously announced DRDD237 (3.8m @ 13.9 g/t gold).

A total of nine holes have been completed since the previous release.

Key points related to the Deacon Lode are:

- The Deacon Lode is a new discovery located in the footwall to the Bellevue Lode. Most new drill holes pass through the Bellevue Lode on the way to the Deacon Shear.
- A second parallel lode named the Mavis Lode is located approximately 40 metres away in the Deacon footwall.
- **Mineralisation style, shear geometry and lithology is analogous to the Bellevue Mine.**
- The Deacon Shear has been defined for 1,800 metres on broad spaced scout drilling with a number of significant DHEM plates currently being tested by follow up drilling.

Figure 5: Drill core from Deacon diamond core hole DRDD295 mineralization associated with ~35% semi massive pyrrhotite, trace disseminated chalcopyrite and fine-grained visible gold. The hole is collared 140 metres north of DRDD237 that assayed 3.8m @ 13.9 g/t from 667m. Assays Pending.




Figure 6: Drill core from Deacon diamond core hole DRDD273 un-assayed mineralization associated with ~15% semi massive pyrrhotite, trace disseminated chalcopyrite and fine-grained visible gold. The hole is the first follow up of the southern DHEM plate. Assays Pending




Figure 7: Plan View showing recent drilling at the Deacon and Mavis Discoveries. Assays are pending for all holes shown in blue. MGA 94 Zone 51




Figure 8: Cross-section through the Bellevue Lode system. The new Deacon/Mavis discovery is situated 500m into the footwall of the historic Bellevue Mine. MGA94 Zone 51




Table 1: Drill holes recently completed at the Bellevue Gold Project. MGA 94 Zone 51

Hole	East	North	RI	Azi	Dip	Depth	From	To	Interval	Au	gram metres	Lode	Refer
DRDD200	258903	6938864	461	90	-58	612	58.7	60.5	1.9	29.3	54.2	Tribune	asx 05/08/2019
DRDD201	258615	6939680	462	91	-60	464	181.0	182.0	1.0	1.3	1.3		asx 05/08/2019
DRDD201							241.0	241.6	0.6	2.0	1.2		
DRDD201							456.0	457.0	1.0	1.7	1.7	Viago North	
DRDD202	258844	6938865	462	90	-60	738	203.2	208.4	5.2	5.4	28.2	Tribune	asx 05/08/2019
DRDD202							212.9	214.2	1.3	1.9	2.4		
DRDD202							260.0	260.5	0.5	10.5	5.2		
DRDD202							267.2	267.7	0.5	6.1	3.1		
DRDD202							607.5	613.0	5.5	3.8	20.9	Viago North	
DRDD202							665.8	666.4	0.6	1.9	1.2		
DRDD203	258779	6939159	464	88	-59	640	102.9	103.5	0.5	2.9	1.6		asx 05/08/2019
DRDD203							150.0	150.5	0.5	1.2	0.6		
DRDD203							228.0	228.6	0.6	1.1	0.7	Tribune	
DRDD203							354.0	355.0	1.0	1.0	1.0		
DRDD203							495.3	496.2	0.9	1.3	1.2		
DRDD203							564.7	569.5	4.8	1.8	8.7	Viago North	
DRDD203							636.0	637.0	1.0	1.8	1.8		
DRDD204	258576	6939676	462	90	-60	484	233.0	233.6	0.6	10.1	6.1		asx 05/08/2019
DRDD204							306.1	306.6	0.5	1.2	0.6		
DRDD204							428.4	429.1	0.7	1.5	1.1		
DRDD204							435.0	437.5	2.5	2.6	6.4		
DRDD204							441.8	445.3	3.5	3.1	10.7	Viago North	
DRDD205	258598	6939724	462	90	-61	556	258.6	259.3	0.7	1.1	0.8		asx 05/08/2019
DRDD205							422.0	422.7	0.7	15.9	10.5	Viago North	
DRDD206	258690	6939681	463	90	-63	521	166.7	167.7	1.0	6.8	6.7		asx 05/08/2019
DRDD206							386.0	386.5	0.5	5.7	2.8		
DRDD206							401.4	402.0	0.6	16.8	10.1	Viago North	
DRDD207	258604	6939920	465	89	-59	422	90.0	90.8	0.8	1.4	1.2		
DRDD207							165.0	165.5	0.5	2.2	1.1		
DRDD207							203.2	203.7	0.5	2.6	1.3		
DRDD207							385.6	389.8	4.2	2.0	8.3	Viago North	
DRDD208	258882	6939158	465	90	-56	526	63.3	67.0	3.7	1.4	5.0	Tribune	
DRDD209	258747	6939243	463	91	-66	600	134.5	135.0	0.5	5.7	2.9		asx 05/08/2019
DRDD209							267.6	269.1	1.5	10.5	16.0	Tribune	
DRDD209							437.6	438.1	0.5	51.1	25.6	Viago Hanging wall	
DRDD209							542.6	543.7	1.0	7.2	7.5	Viago North	

Hole	East	North	RI	Azi	Dip	Depth	From	To	Interval	Au	gram metres	Lode	Refer
DRDD209W1	258747	6939243	463	91	-66	600	552.7	553.7	0.9	12.5	11.9	Viago	
DRDD210	258633	6939764	462	91	-59	539	211.4	215.0	3.6	17.1	61.6	Vlad	
DRDD210							409.3	411.4	2.1	3.3	6.9	Viago North	
DRDD210							431.8	432.4	0.6	1.3	0.8		
DRDD211	258802	6939024	464	90	-59	683	228.9	235.0	6.1	1.4	8.5	Tribune	
DRDD211							256.1	256.6	0.5	3.2	1.6		
DRDD211							261.4	262.0	0.6	2.2	1.3		
DRDD211							593.7	594.8	1.1	10.9	12.6	Viago	
DRDD212	258606	6939762	463	90	-60	289	211.5	212.1	0.6	1.9	1.1		
DRDD212							247.2	251.2	4.0	8.4	33.8	Vlad	
DRDD213	258609	6939438	462	90	-60	500	374.0	376.0	2.0	2.2	4.5		
DRDD213							467.6	468.5	0.9	8.4	8.0	Viago North	
DRDD214	258600	6939845	463	91	-64	436	170.2	170.7	0.5	1.3	0.7		
DRDD214							174.5	177.6	3.1	1.1	3.6		
DRDD214							238.8	239.7	0.9	9.4	8.2	Vlad	
DRDD214							401.2	401.7	0.5	8.2	4.1	Viago North	
DRDD214							413.5	414.0	0.5	2.1	1.1		
DRDD215	258688	6939722	463	90	-62	502	395.0	400.0	5.0	5.5	27.3	Viago North	
DRDD215							403.3	403.9	0.6	1.1	0.7		
DRDD215							439.7	441.0	1.3	1.0	1.3		
DRDD216	258785	6938980	463	90	-59	722	263.6	264.1	0.5	1.1	0.6	Tribune	
DRDD216							642.3	643.2	0.9	7.2	6.8	Viago	
DRDD217	258688	6939640	462	90	-60	478	405.9	408.5	2.6	2.8	7.4		
DRDD217							415.2	417.3	2.2	6.1	13.2	Viago North	
DRDD218	258915	6939639	465	86	-55	853	272.5	273.0	0.5	1.7	0.8		asx 10/09/19
DRDD218							606.0	606.5	0.5	5.1	2.5		
DRDD218							650.0	651.0	1.0	1.0	1.0		
DRDD218							692.5	696.9	4.4	62.4	274.6	Deacon	
DRDD218							769.5	771.0	1.5	4.4	6.8		
DRDD219	258838	6938864	462	90	-64	654	252.9	253.4	0.5	2.0	1.0	Tribune	
DRDD219							601.2	601.7	0.5	5.1	2.5		
DRDD219							625.1	625.7	0.5	9.6	5.3	Viago	
DRDD220	258579	6939478	462	90	-60	496	62.0	62.7	0.7	1.4	1.0		
DRDD220							111.0	112.6	1.6	1.8	2.8	Tribune	
DRDD220							155.0	155.6	0.6	273.5	164.1		
DRDD221	258640	6939205	462	90	-56	619	592.0	592.7	0.6	1.4	0.9		
DRDD221							604.6	605.2	0.6	2.5	1.5	Viago	
DRDD222	258766	6939022	463	91	-60	736	292.0	293.2	1.1	4.4	5.1	Tribune	
DRDD222							485.6	486.8	1.2	1.9	2.2		
DRDD222							598.1	598.6	0.5	2.9	1.5		
DRDD222							606.0	611.0	5.0	11.1	57.2	Viago	
DRDD223	258999	6939921	474	90	-60	865	624.5	624.8	0.3	3.2	1.0	Deacon	asx 02/10/19
DRDD224	258847	6939026	464	90	-56	571	158.9	161.2	2.3	8.2	18.4	Tribune	
DRDD224							179.7	180.3	0.6	26.4	15.8	Tribune	

Hole	East	North	RI	Azi	Dip	Depth	From	To	Interval	Au	gram metres	Lode	Refer
DRDD224							205.6	206.4	0.8	3.1	2.5		
DRDD225	259085	6939756	476	89	-61	868	233.4	234.0	0.6	1.2	0.7		asx 02/10/19
DRDD225							325.0	326.0	1.0	1.7	1.7		
DRDD225							487.0	487.5	0.5	1.3	0.7		
DRDD225							513.3	514.0	0.7	1.2	0.9		
DRDD225							535.7	536.5	0.8	36.9	29.9	Deacon	
DRDD225							597.1	597.8	0.7	1.5	1.0		
DRDD225							778.0	779.0	1.0	2.2	2.2		
DRDD225							798.0	799.0	1.0	5.0	5.0		
DRDD226	258879	6939106	465	91	-60	573	70.3	70.8	0.5	12.5	6.2		
DRDD226							98.0	104.5	6.5	1.1	6.8	Tribune	
DRDD226							523.2	523.8	0.6	1.1	0.6	Bellevue	
DRDD227	258765	6939102	464	90	-60	631	262.4	264.6	2.2	12.3	27.5	Tribune	
DRDD227							267.9	269.0	1.1	2.3	2.5		
DRDD227							590.4	591.1	0.7	74.8	53.8	Viago	
DRDD228	258884	6938866	462	91	-60	667	119.0	122.4	3.4	2.5	8.4	Tribune	
DRDD229	259030	6939838	476	89	-60	853	84.1	86.2	2.1	7.0	14.7	Bellevue	asx 02/10/19
DRDD229							496.3	497.0	0.7	1.2	0.8		
DRDD229							616.0	623.1	7.1	1.3	9.4	Deacon	
DRDD229							641.4	645.0	3.6	1.9	7.0	Mavis	
DRDD230	258888	6938990	464	89	-61	592	75.0	76.6	1.6	4.1	6.3		
DRDD230							80.8	83.2	2.4	5.3	12.8	Tribune	
DRDD230							445.5	448.0	2.5	1.1	2.8	Bellevue	
DRDD231	258861	6939060	464	89	-59	191					NSR		
DRDD232	259008	6938788	461	112	-69	646					NSR		
DRDD233W1	258828	6939060	464	91	-60	622	573.1	574.5	1.4	1.6	2.3		
DRDD233W1							580.5	583.5	3.0	19.8	59.5	Viago	
DRDD234A	259059	6939638	469	90	-60	751	238.2	238.8	0.6	2.9	1.7		
DRDD234A							580.0	580.9	0.8	10.3	8.6		
DRDD234A							601.0	602.0	1.0	1.0	1.0		
DRDD234A							605.8	606.3	0.5	2.6	1.4		
DRDD234A							609.6	612.4	2.8	3.3	9.2	Deacon	
DRDD234A							656.2	657.1	0.9	5.7	5.1		
DRDD235	258919	6938821	462	90	-60	74					NSR		
DRDD236	258838	6938982	464	90	-60	220					NSR		
DRDD237	258947	6939869	472	82	-60	781	81.0	82.0	1.0	1.2	1.2		asx 02/10/19
DRDD237							425.0	425.8	0.8	1.2	0.9		
DRDD237							627.9	629.5	1.6	1.3	2.2		
DRDD237							667.1	670.9	3.8	13.9	52.4	Deacon	
DRDD237							757.8	759.5	1.7	5.9	10.2	Mavis	
DRDD238	259013	6938782	461	94	-81	640	218.3	219.1	0.8	1.1	0.9	Tribune	
DRDD239	258790	6939059	464	91	-61	320	109.0	109.7	0.7	2.2	1.6		
DRDD239							240.5	241.0	0.6	11.1	6.1	Tribune	
DRDD239							244.5	245.1	0.6	2.4	1.4		
DRDD240	258822	6938938	463	89	-60	260	231.4	234.0	2.5	1.2	3.1	Tribune	
DRDD241	258907	6938819	462	91	-62	136	69.5	75.3	5.8	1.9	11.2	Tribune	

Hole	East	North	RI	Azi	Dip	Depth	From	To	Interval	Au	gram metres	Lode	Refer
DRDD242	258849	6940297	472	90	-60	850	24.1	25.4	1.2	2.1	2.6		asx 02/10/19
DRDD242							153.5	154.0	0.5	1.6	0.8		
DRDD242							175.5	178.3	2.8	46.9	132.1	Bellevue	
DRDD242							193.8	196.5	2.7	1.2	3.2		
DRDD242							233.5	235.0	1.5	36.4	54.6	Deacon	
DRDD242							629.0	630.7	1.7	2.7	4.6		
DRDD242							648.4	652.0	3.6	1.0	3.7		
DRDD242							656.0	656.5	0.5	4.2	2.1		
DRDD243	259556	6942564	481	224	-52	110	77.0	81.0	4.0	6.2	24.9	Vanguard	
DRDD244	259584	6942530	480	230	-51	109	61.1	64.0	2.9	5.5	15.9	Vanguard	
DRDD245	259588	6942455	478	269	-51	91					NSR		
DRDD246	258897	6938900	463	90	-60	140	70.0	70.6	0.6	1.1	0.7		
DRDD246							126.1	127.0	0.9	36.0	31.7	Tribune	
DRDD247	258866	6938940	463	89	-60	192	136.9	138.2	1.3	13.6	17.1	Tribune	
DRDD247							148.0	151.9	3.9	2.9	11.1	Tribune	
DRDD247							162.0	165.0	3.0	33.0	98.0	Tribune	
DRDD248	259172	6939877	478	87	-60	733	162.9	163.6	0.8	1.0	0.8		
DRDD248							418.5	419.1	0.6	2.1	1.3	Deacon	
DRDD249	258888	6938939	463	91	-60	170	80.8	84.1	3.3	3.8	12.5	Tribune	
DRDD250	258942	6939573	465	82	-61	862	274.5	277.2	2.7	9.3	24.9	Tribune	
DRDD251	258900	6939060	465	90	-56	100	41.5	42.0	0.5	7.9	3.9	Tribune	
DRDD252	258850	6939098	464	90	-59	181	135.6	136.6	1.0	1.2	1.2	Tribune	
DRDD253	258805	6939119	464	90	-60	240	87.4	88.0	0.6	1.4	0.8		
DRDD253							133.5	134.5	1.0	1.9	1.9		
DRDD253							201.4	207.0	5.6	3.1	17.3	Tribune	
DRDD254	258618	6940037	466	270	-90	226	103.0	103.6	0.6	1.0	0.6	Tribune	
DRDD255	258828	6939097	464	90	-60	238	80.5	81.0	0.5	1.2	0.6		
DRDD255							176.5	179.0	2.5	1.4	3.5	Tribune	
DRDD255							189.8	190.3	0.5	3.1	1.6		
DRDD256	258852	6939119	465	90	-60	160	89.6	90.3	0.8	9.3	7.0		
DRDD256							135.6	137.0	1.4	1.3	2.0		
DRDD256							147.0	147.7	0.7	10.0	7.0	Tribune	
DRDD257	258864	6939160	465	90	-60	163	107.9	117.5	9.6	14.1	135.6	Tribune	
DRDD258	258794	6939201	464	90	-60	236	196.0	196.5	0.5	2.9	1.5		
DRDD258							199.4	200.0	0.7	2.1	1.4	Tribune	
DRDD259	258814	6939200	464	90	-60	212	176.7	177.2	0.5	2.4	1.2		
DRDD259							211.5	212.1	0.6	1.1	0.6	Tribune	
DRDD260	258618	6940038	466	90	-79	424						Viago North	assays pending
DRDD261	258801	6939241	464	90	-60	211	180.5	184.4	3.8	3.1	12.0	Tribune	
DRDD262	258843	6939240	464	89	-60	169	28.7	29.8	1.1	20.4	22.3	Tribune	
DRDD262							122.4	124.9	2.6	1.3	3.4	Tribune	
DRDD262							128.1	129.0	0.9	1.2	1.0		
DRDD263	258862	6939200	465	90	-60	156	98.0	99.0	1.0	1.3	1.3		
DRDD263							102.5	105.0	2.5	3.2	7.9	Tribune	
DRDD263							108.5	109.0	0.5	1.3	0.7		
DRDD264	258757	6939319	463	91	-60	240	214.6	217.1	2.5	1.9	4.8	Tribune	
DRDD265	258775	6939359	464	89	-61	220					NSR		
DRDD266	258815	6939322	464	89	-60	505					NSR		

<i>Hole</i>	<i>East</i>	<i>North</i>	<i>RI</i>	<i>Azi</i>	<i>Dip</i>	<i>Depth</i>	<i>From</i>	<i>To</i>	<i>Interval</i>	<i>Au</i>	<i>gram metres</i>	<i>Lode</i>	<i>Refer</i>
<i>DRDD267</i>	258815	6939322	464	89	-60	160	137.0	137.5	0.5	3.4	1.7		
<i>DRDD267</i>							140.5	144.7	4.2	1.8	7.6	Tribune	
<i>DRDD268</i>	258817	6939282	464	90	-60	190	142.2	142.7	0.5	2.1	1.1		
<i>DRDD268</i>							146.7	147.2	0.5	2.2	1.1	Tribune	
<i>DRDD269</i>	258619	6940038	466	91	-69	385	366.9	367.3	0.4	18.8	7.9	Viago North	
<i>DRDD270</i>	258851	6939281	465	90	-60	112	23.4	24.7	1.3	25.0	32.5	Tribune	
<i>DRDD270</i>							88.3	95.8	7.5	1.7	12.8	Tribune	
<i>DRDD271</i>	258776	6939324	463	89	-60	210	185.6	186.1	0.5	12.2	6.1	Tribune	
<i>DRDD271</i>							189.5	190.0	0.5	2.9	1.5		
<i>DRDD272</i>	258790	6939362	464	90	-60	190	158.0	161.0	3.0	1.2	3.7	Tribune	
<i>DRDD272</i>							163.0	163.5	0.5	1.1	0.6		
<i>DRDD273</i>	258907	6939238	467	90	-59	854						Deacon	assays pending
<i>DRDD274</i>	258610	6939996	466	90	-86	426						Vlad	assays pending
<i>DRDD275</i>	258834	6939360	465	89	-61	134	98.1	100.1	2.0	8.5	16.8	Tribune	
<i>DRDD276</i>	258810	6939361	464	90	-60	160	125.2	126.1	0.9	2.9	2.6		
<i>DRDD276</i>							140.2	142.2	2.0	6.0	11.6	Tribune	
<i>DRDD277</i>	258735	6939396	463	90	-60		218.6	223.0	4.4	1.4	6.3		
<i>DRDD278</i>	258825	6939399	465	90	-60	130	92.9	94.5	1.7	2.2	3.6		
<i>DRDD278</i>							101.6	103.2	1.6	2.7	4.3		
<i>DRDD279</i>	258804	6939279	463	90	-61	210						Viago North	assays pending
<i>DRDD280</i>	258686	6939760	463	90	-61	490						Viago North	assays pending
<i>DRDD281</i>	258781	6939271	463	89	-60	240						Viago North	assays pending
<i>DRDD282</i>	258606	6939996	466	90	-72	394						Viago North	assays pending
<i>DRDD283</i>	258578	6939717	462	90	-67	445						Viago North	assays pending
<i>DRDD284</i>	258578	6939756	463	90	-66	441						Viago North	assays pending
<i>DRDD285</i>	258694	6939520	463	90	-60	528						Viago North	assays pending
<i>DRDD286</i>	258575	6939880	464	90	-60	440						Viago North	assays pending
<i>DRDD287</i>	258940	6940280	474	79	-66	751						Deacon	assays pending
<i>DRDD288</i>	258600	6939960	465	90	-66	410						Viago North	assays pending
<i>DRDD289</i>	258634	6940120	467	88	-76	390						Viago North	assays pending
<i>DRDD290</i>	259085	6939878	478	90	-60	673						Deacon	assays pending
<i>DRDD291</i>	258578	6939717	462	90	-75	300						Viago North	assays pending
<i>DRDD292</i>	259008	6939958	475	90	-60	720						Deacon	assays pending
<i>DRDD293</i>	258594	6939917	465	90	-73	431						Viago North	assays pending
<i>DRDD294</i>	258690	6939802	464	90	-62	390						Viago North	assays pending
<i>DRDD295</i>	259040	6940050	474	90	-60	775						Deacon	assays pending

Hole	East	North	RI	Azi	Dip	Depth	From	To	Interval	Au	gram metres	Lode	Refer
DRDD296	259040	6940116	477	90	-60	671						Deacon	assays pending
DRDD297	259113	6940004	478	89	-61	595						Deacon	assays pending
DRDD298	259090	6939958	479	90	-60	600						Deacon	assays pending
DRDD299	258598	6939847	463	90	-69	412						Viago North	assays pending

Appendix 1: Summary drill logs from recent Deacon core drilling as recorded by the logging geologist.

DRDD273 - Mineralisation/Structure Summary		
From:	To:	Comments
25.4	26.4	Tribune: highly weathered, 30% smoky quartz, chlorite amphibole shear, sulphide content heavily oxidized but additional 3% unaltered pyrrhotite, (blebby fracture fill). Clay infill on fracture surfaces. Vuggy in places due to both carbonate weathering and pyrite replacement.
473.5	475	Bellevue lode. Moderate intensity chlorite/biotite shear with 90% quartz vein (both opaque and smoky) with wispy texture to quartz vein resulting from inclusions from surrounding shear. 10% sulphide overall with pyrrhotite and chalcopyrite plus trace arsenopyrite. Sulphide with fracture fill texture in opaque quartz vein becoming more disseminated in smoky quartz. Diffuse strain gradient with minor mineralisation in HW and FW. +15 flecks of visible gold observed over first 0.75m.
809.6	810.6	Deacon: chlorite biotite shear with 40% opaque quartz veining, 10% smoky quartz veining and 5% sulphides. Sulphides occur as fine fracture fill within smoky quartz veining and more blebby within opaque veining, pyrrhotite and chalcopyrite. Fine carbonate veining throughout.
819	821.5	Mavis: biotite chlorite shear with strong carbonate alteration. 10% opaque quartz veining, 6% smoky quartz veining, 15% sulphides, mostly cataclastic texture with some larger blebs. Pyrrhotite, chalcopyrite and some pyrite replacement. 20+ flecks of gold throughout.

DRDD287 - Mineralisation/Structure Summary		
From:	To:	Comments
100.8	103.1	Bellevue (intersected after stope): biotite chlorite shear with 30% smoky quartz veining, 4% sulphides as blebby fracture fill (pyrrhotite and chalcopyrite with some pyrite replacement). Vuggy in places due to pyrite replacement. Weak carbonate alteration throughout. +5 flecks of visible gold
287.6	288	Structure: chlorite amphibole (randomly orientated) biotite shear (weak shearing), 6% opaque quartz veining, 5% cataclastic sulphides (mostly pyrrhotite with minor chalcopyrite), weak carbonate alteration.
540.8	541.3	Shear and vein mineralisation intersected over 0.5m from 540.8m to 541.3m hosted in pillow basalt. Moderate to intense biotite shearing plus minor amphibole with c.10cm smokey quartz vein. 5% sulphide over interval up to 15% locally with fracture fill sulphide in the vein and stringer sulphide aligned with shear fabric. One fleck of visible gold observed in quartz vein associated with epidote inclusions. Sharp strain gradient in both HW and FW.
584.4	586.4	Shear and mineralisation over 2m from 584.4m to 586.4m hosted in pillow basalt. Intense shear deformation with variable alteration dominated by biotite/chlorite/epidote/amphibole plus lesser sericite and carbonate. Trace quartz vein with 1% carbonate veining deformed within shear fabric. 3% sulphide mineralisation disseminated over interval with minor stringer veins associated with carbonate. 2 flecks of visible gold observed both in wall rock alteration not vein. Minor shear and mineralisation observed in HW and FW.
671.2	672.6	Mineralised quartz vein with FW shear over 1.4m from 671.2m to 672.6m hosted in massive dolerite. Large c.25cm laminated opaque quartz vein with 20% stringer sulphide with +4 flecks of visible gold . Weak chlorite shear with smokey quartz veinlets continuous into FW.

DRDD292 - Mineralisation/Structure Summary		
From:	To:	Comments
111	112.2	Bellevue: biotite chlorite shear, little quartz veining (3% smoky), 7% sulphides (3% arsenopyrite), cataclastic, no carbonate alteration.
359.1	360.15	Structure: biotite chlorite amphibole shear, weak carbonate alteration throughout, coarse random amphiboles, 10% smoky quartz, 2% fracture fill pyrrhotite, arsenopyrite and minor chalcopyrite.
615.9	617.4	Mineralised vein and shear over 1.5m from 615.9m to 617.4m hosted in pillow basalt. Moderate shear intensity with chlorite/amphibole alteration in FW and HW of c.40cm hydrothermally brecciated quartz vein. Fragments of smokey quartz and sulphide in opaque quartz matrix showing fluid paragenesis with 20% fracture fill sulphide locally. +4 flecks of visible gold observed in brecciated vein. Minor mineralisation continuous into HW and FW with stringer sulphide plus epidote.
673.2	684.5	Large shear zone intersected over 11.3m from 673.2m to 684.5m hosted in pillow basalt. Intense shear fabric with evidence of folding. Variable alteration dominated by biotite/amphibole with patchy to pervasive epidote/chlorite overprint. 3% smokey quartz veins with minor carbonate fill. Sulphide 3% disseminated through interval with some stringer veins. No visible gold observed

DRDD295 - Mineralisation/Structure Summary		
From:	To:	Comments
53.4	55.5	Bellevue Lode intersected over 2.1m from 53.4m to 55.5m hosted in massive dolerite. Massive pyrite with vuggy texture plus quartz vein associated with weak chlorite shear in HW and FW. One fleck of visible gold observed. Multiple smaller zones of mineralisation in HW some with visible gold .
109.9	111	Shear and quartz lode mineralisation intersected over 1.1m from 109.9m to 111m forming on contact of pillow basalt to mafic quartz feldspar porphyry. Strong shear fabric at low angle to the core axis with chlorite/amphibole alteration plus disseminated pyrrhotite. 0.5m opaque quartz vein with fracture fill pyrrhotite replaced by pyrite in places. No visible gold. Weak shear and mineralisation in FW porphyry.
317.9	319.4	Moderate shear and mineralisation intersected over 1.5m from 317.9m to 319.4m in pillow basalt. Shear with weak biotite alteration plus one 5cm smokey quartz vein with fracture fill pyrrhotite mineralisation. Overall 2% sulphide mainly as disseminations within shear fabric with weak stringer textures. Minor shear and mineralised veins observed in HW and FW to reported zone.
587.5	590.7	Deacon Lode intersected over 3.2m from 587.5m to 590.7m hosted in pillow basalt. Strong mineralisation with 70% quartz vein (smokey and opaque) bordered by amphibole/chlorite/epidote altered shearing with sharp strain gradients to surrounding undeformed pillow basalt. 35% sulphide associate with quartz lode with dominant fracture fill texture becoming cataclastic in places. Relative high proportion of chalcopyrite to pyrrhotite. +15 flecks of visible gold observed associated with quartz.
628.5	630.5	Mavis: chlorite, biotite, amphibole shear, 5% opaque quartz veining, strong carbonate alteration throughout, 1% blebby fracture fill sulphides (mostly pyrrhotite), plus sulphides finely disseminated throughout shear.

DRDD296 - Mineralisation/Structure Summary		
From:	To:	Comments
32	33.1	Bellevue Shear intersected over 1.1m from 32m to 33.1m forming on contact of mafic quartz feldspar porphyry to pillow basalt with 1.6m cavity intersected at 27m. Weak/moderate shear fabric with weak biotite plus albite alteration. 10% smokey quartz vein with fracture fill vuggy pyrite replacing pyrrhotite. +6 flecks of visible gold observed.
145.2	150.2	Strong shear and mineralisation intersected over c.5m from 145.2m to 150.2m forming on FW contact of mafic quartz-feldspar porphyry to pillow basalt. Strong amphibole/chlorite shearing at low angle to core axis with 15% smoky quartz vein deformed within shear fabric. Overall 7% sulphide, locally up to 20%, mainly as pyrite replacing pyrrhotite with vuggy texture. No visible gold observed.
543.9	545.5	Deacon: chlorite amphibole biotite shear, weak carbonate alteration throughout, 5% sulphides (pyrrhotite), cataclastic and shear parallel veinlets, 1% quartz veining, one 5cm section of massive sulphides, shear aligned amphiboles.

DRDD297 - Mineralisation/Structure Summary		
From:	To:	Comments

204.5	225	Large structure (unmineralized), chlorite shear with strong carbonate and albite alteration, 15% opaque quartz veining. Alteration progresses from more chlorite carbonate dominant, to biotite dominant with depth.
479.5	488.5	Weakly sheared vein structure, 30% opaque quartz veining. Strong chlorite amphibole (coarse and randomly orientated) alteration, lesser biotite alteration throughout, but very strong biotite alteration in footwall. Weak carbonate alteration in hanging wall. 1% sulphides (mostly pyrrhotite), fracture fill and cataclastic textures throughout.
495.6	504	Biotite chlorite amphibole shear with 5% opaque quartz, 5% smoky quartz veining, 2% blebby sulphides, cataclastic in places (mostly pyrrhotite), sulphides appear brecciated in some areas, randomly aligned amphiboles, weak carbonate alteration throughout.
545.6	547.3	Deacon: chlorite amphibole shear with 10% smoky quartz, 5% opaque quartz, 15% sulphides (cataclastic pyrrhotite and minor chalcopyrite), no carbonate alteration, very high strain gradient.

DRDD298 - Mineralisation/Structure Summary		
From:	To:	Comments
26	38	Bellevue shear intersected over c.12m from 26m to 38m hosted in pillow basalt. Wide zone of moderate chlorite/amphibole shearing in pillows with trace stringer pyrite observed associated with biotite alteration and minor quartz vein.
547.4	549	Deacon Biotite, chlorite, amphibole shear, one zone of 5cm smoky quartz vein with cataclastic pyrrhotite and one fleck of visible gold . Otherwise, biotite dominant shear with sulphides (pyrrhotite) disseminated throughout, few <1cm smoky quartz veins, randomly aligned amphiboles. Over entire interval, 3% pyrrhotite, 5% smoky quartz.
587.2	588.0	Mavis chlorite amphibole biotite shear, sulphide veinlets throughout shear plus cataclastic sulphides throughout smoky quartz veins. 7% sulphides (mostly pyrrhotite with minor chalcopyrite), 5% smoky quartz veining. Strong carbonate alteration in footwall. Amphiboles are shear aligned.

Notes

1. All material assumptions and technical parameters underpinning the Mineral Resource estimate in the ASX announcement dated 11 July 2019 continue to apply and have not materially changed since last reported.
2. For full details of these Exploration results, refer to the said Announcement or Release on the said date. Bellevue Gold is not aware of any new information or data that materially affects the information included in the said announcement.

Table 1 - JORC Code, 2012 Edition.

Section 1 Sampling Techniques and Data (Criteria in this section apply to all succeeding sections.)

Criteria	JORC Code explanation	Commentary
Sampling techniques	<ul style="list-style-type: none"> Nature and quality of sampling (eg cut channels, random chips, or specific specialized industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling. Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used. Aspects of the determination of mineralisation that are Material to the Public Report. In cases where ‘industry standard’ work has been done this would be relatively simple (eg ‘reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay’). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information. 	<ul style="list-style-type: none"> The holes were sampled by NQ Diamond Core drilling. Sampling was nominally at 1 m intervals however over narrow zones of mineralisation it was as short as 0.2 m. QAQC samples were inserted in the sample runs, comprising gold standards (CRM’s or Certified Reference Materials) and commercially sourced blank material (barren basalt). Sampling practice is appropriate to the geology and mineralisation of the deposit and complies with industry best practice.
Drilling techniques	<ul style="list-style-type: none"> Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc). 	<ul style="list-style-type: none"> Diamond coring was undertaken with a modern truck mounted rig and industry recognized quality contractor. Core (standard tube), was drilled at HQ3 size (61.1mm) from surface until competent ground was reached. The hole was then continued with NQ size (45.1mm) to total depth. The core was orientated using a Reflex Ez-Ori tool.
Drill sample recovery	<ul style="list-style-type: none"> Method of recording and assessing core and chip sample recoveries and results assessed. Measures taken to maximise sample recovery and ensure representative nature of the samples. Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material. 	<ul style="list-style-type: none"> Diamond core recovery was measured for each run and calculated as a percentage of the drilled interval, in weathered material, core recoveries were generally 80 to 90%, in fresh rock, the core recovery was excellent at 100%. There has been no assessment of core sample recovery and gold grade relationship.
Logging	<ul style="list-style-type: none"> Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies. Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography. The total length and percentage of the relevant intersections logged. 	<ul style="list-style-type: none"> All core was geologically logged. Lithology, veining, alteration, mineralisation and weathering are recorded in the geology table of the drill hole database. Final and detailed geological logs were forwarded from the field following cutting and sampling. Geological logging of core is qualitative and descriptive in nature.
Sub-sampling techniques and sample preparation	<ul style="list-style-type: none"> If core, whether cut or sawn and whether quarter, half or all core taken. If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry. For all sample types, the nature, quality and appropriateness of the sample preparation technique. Quality control procedures adopted for all sub-sampling stages to maximize representivity of samples. Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling. Whether sample sizes are appropriate to the grain size of the material being sampled. 	<ul style="list-style-type: none"> Core was cut in half, one half retained as a reference and the other sent for assay. Sample size assessment was not conducted but used sampling size typical for WA gold deposits.
Quality of assay data and	<ul style="list-style-type: none"> The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total. 	<ul style="list-style-type: none"> Assaying and laboratory procedures used are NATA certified techniques for gold. Samples were prepared and assayed at NATA accredited Minanalytical Laboratory Services in Perth.

Criteria	JORC Code explanation	Commentary
laboratory tests	<ul style="list-style-type: none"> For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc. Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established. 	<ul style="list-style-type: none"> All samples are initially sent to Minanalytical sample Preparation facility in Kalgoorlie. Samples submitted for fire assay are weighed, dried, coarse crushed and pulverized in total to a nominal 85% passing 75 microns (method code SP3010) and a 50 g subsample is assayed for gold by fire assay with an AAS finish (method code FA50/AAS). Lower Detection limit 0.005 ppm and upper detection limit 100 ppm gold. Samples reporting above 100 ppm gold are re-assayed by 50 gram fire assay method FA50HAAS which has a lower detection of 50 ppm and an upper detection limit of 800 ppm. This method is used for very high grade samples. Both fire assay methods are considered to be total analytical techniques. Samples submitted for analysis via Photon assay technique were dried, crushed to nominal 85% passing 2mm, linear split and a nominal 500g sub sample taken (method code PAP3512R) The 500g sample is assayed for gold by PhotonAssay (method code PAU2) along with quality control samples including certified reference materials, blanks and sample duplicates. About the MinAnalytical PhotonAssay Analysis Technique:- <ul style="list-style-type: none"> Developed by CSIRO and the Chrysos Corporation, the PhotonAssay technique is a fast and chemical free alternative to the traditional fire assay process and utilizes high energy x-rays. The process is non-destructive on and utilises a significantly larger sample than the conventional 50g fire assay. MinAnalytical has thoroughly tested and validated the PhotonAssay process with results benchmarked against conventional fire assay. The National Association of Testing Authorities (NATA), Australia's national accreditation body for laboratories, has issued MinAnalytical with accreditation for the technique in compliance with ISO/IEC 17025:2018-Testing. In addition to the Company QAQC samples (described earlier) included within the batch the laboratory included its own CRM's, blanks and duplicates.
Verification of sampling and assaying	<ul style="list-style-type: none"> The verification of significant intersections by either independent or alternative company personnel. The use of twinned holes. Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols. Discuss any adjustment to assay data. 	<ul style="list-style-type: none"> Intersection assays were documented by Bellevue's professional exploration geologists and verified by Bellevue's Exploration Manager. No drill holes were twinned. All assay data were received in electronic format from Minanalytical, checked, verified and merged into Bellevue's database. Original laboratory data files in CSV and locked PDF formats are stored together with the merged data. There were no adjustments to the assay data.
Location of data points	<ul style="list-style-type: none"> Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation. Specification of the grid system used. Quality and adequacy of topographic control. 	<ul style="list-style-type: none"> All drill collars are located with hand held GPS. These positions are considered to be within 5 metres accuracy in the horizontal plane and less so in the vertical. The positions were subsequently surveyed with a differential GPS system to achieve x – y accuracy of 2 cm and height (z) to +/- 10 cm. All collar location data is in UTM grid (MGA94 Zone 51). Down hole surveys were by a north seeking gyroscope.
Data spacing and distribution	<ul style="list-style-type: none"> Data spacing for reporting of Exploration Results. Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied. Whether sample compositing has been applied. 	<ul style="list-style-type: none"> The drill hole intersections are between 40 and 80 m apart which is adequate for a mineral resource estimation at the inferred category. No sample compositing has been applied.

Criteria	JORC Code explanation	Commentary
Orientation of data in relation to geological structure	<ul style="list-style-type: none"> Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type. If the relationship between the drilling orientation and the orientation of key mineralized structures is considered to have introduced a sampling bias, this should be assessed and reported if material. 	<ul style="list-style-type: none"> Drill lines are orientated approximately at right angles to the currently interpreted strike of the known mineralization. No bias is considered to have been introduced by the existing sampling orientation.
Sample security	<ul style="list-style-type: none"> The measures taken to ensure sample security. 	<ul style="list-style-type: none"> Samples were secured in closed polyweave sacks for delivery to the laboratory sample receipt yard in Kalgoorlie by Bellevue personnel.
Audits or reviews	<ul style="list-style-type: none"> The results of any audits or reviews of sampling techniques and data. 	No audits or reviews completed.

Section 2 Reporting of Exploration Results (Criteria listed in the preceding section also apply to this section.)

Criteria	JORC Code explanation	Commentary
Mineral tenement and land tenure status	<ul style="list-style-type: none"> Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings. The security of the tenure held at the time of reporting along with any known impediments to obtaining a license to operate in the area. 	<ul style="list-style-type: none"> The Bellevue Gold Project consists of three granted mining licenses M36/24, M36/25, M36/299 and one granted exploration license E36/535. Golden Spur Resources, a wholly owned subsidiary of Bellevue Gold Limited (Formerly Draig Resources Limited) owns the tenements 100%. There are no known issues affecting the security of title or impediments to operating in the area.
Exploration done by other parties	<ul style="list-style-type: none"> Acknowledgment and appraisal of exploration by other parties. 	<ul style="list-style-type: none"> Historical work reviewed was completed by a number of previous workers spanning a period of over 100 years. More recently and particularly in terms of the geophysical work reviewed the companies involved were Plutonic Operations Limited, Barrick Gold Corporation and Jubilee Mines NL.
Geology	<ul style="list-style-type: none"> Deposit type, geological setting and style of mineralisation. 	<ul style="list-style-type: none"> The Bellevue Project is located within the Agnew-Wiluna portion of the Norseman-Wiluna Greenstone belt, approximately 40 km NNW of Leinster. The project area comprises felsic to intermediate volcanic sequences, meta-sediments, ultramafic komatiite flows, Jones Creek Conglomerates and tholeiitic meta basalts (Mt Goode Basalt) which hosts the known gold deposits. The major gold deposits in the area lie on or adjacent to north-northwest trending fault zones. The Bellevue gold deposit is hosted by the partly tholeiitic meta-basalts of the Mount Goode Basalts in an area of faulting, shearing and dilation to form a shear hosted lode style quartz/basalt breccia.
Drill hole Information	<ul style="list-style-type: none"> A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes: <ul style="list-style-type: none"> easting and northing of the drill hole collar elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar dip and azimuth of the hole down hole length and interception depth hole length. If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case. 	<ul style="list-style-type: none"> All requisite drill hole information is tabulated elsewhere in this release.
Data aggregation methods	<ul style="list-style-type: none"> In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (eg cutting of high grades) and cut-off grades are usually Material and should be stated. Where aggregate intercepts incorporate short lengths of high grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail. The assumptions used for any reporting of metal equivalent values should be clearly stated. 	<ul style="list-style-type: none"> Drill hole intersections are reported above a lower cut-off grade of 1 g/t Au and no upper cut off grade has been applied. A minimum intercept length of 0.2 m applies to the sampling in the tabulated results presented in the main body of this release. Up to 2 m of internal dilution have been included. No metal equivalent reporting has been applied.
Relationship between mineralisation widths and intercept lengths	<ul style="list-style-type: none"> These relationships are particularly important in the reporting of Exploration Results. If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (eg 'down hole length, true width not known'). 	<ul style="list-style-type: none"> Drill intersections of the Viago mineralisation is considered very close to true width. For Tribune drill intersections, true width is approximately 70% that of the quoted intersections.

Diagrams	<ul style="list-style-type: none"> Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views. 	<ul style="list-style-type: none"> Included elsewhere in this release.
Balanced reporting	<ul style="list-style-type: none"> Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results. 	<p>All results above 0.2 m at 1.0 g/t lower cut have been reported.</p>
Other substantive exploration data	<ul style="list-style-type: none"> Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances. 	<ul style="list-style-type: none"> Down hole electromagnetic surveys support the in hole geological observations and will continue to be used to vector drill targeting.
Further work	<ul style="list-style-type: none"> The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale step-out drilling). Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive. 	<ul style="list-style-type: none"> Bellevue Gold Limited is continuing to drill test this new lode with step out and infill drilling in conjunction with shallow infill work at the Tribune Lode, more information is presented in the body of this report. Diagrams in the main body of this document show the areas possible extensions of the lodes. Other targets exist in the project and the company continues to assess these.