

## TRENCH SAMPLING CONFIRMS GOLD IN ADDITIONAL STOCKPILES AT HAWKINS HILL, IMPROVING PRODUCTION PATHWAY

Advanced Hill End Gold Project (NSW)  
34km strike length high grade gold system – to be developed on a large scale - 1.6m ozs historically mined.

Advanced Hargraves Gold Project (NSW) moving to a PFS.

Combined existing 2012 JORC 484K oz @ 3.28 g/t. Significant exploration upside.

Highly prospective Pride of Elvire Gold Project (WA) & Taylors Rock Nickel Gold Project (WA).

Hill End is home to the largest gold reef nugget ever found – world record.



W. [www.Vertexminerals.com](http://www.Vertexminerals.com)  
E. [info@vertexminerals.com.au](mailto:info@vertexminerals.com.au)



ASX ANNOUNCEMENT 27<sup>TH</sup> APRIL 2023

### HIGHLIGHTS:

- Vertex has been actively assessing all potential ore sources for processing feed stock. Further to Vertex’s ASX release dated 22<sup>nd</sup> Feb. 2023, the Company is pleased to announce trench sampling of the Process Plant Stockpile, Tails Dam Road Stockpile & Consolidated Pad revealed each contains gold.
- The Process Plant Stockpile & Tails Dam Road Stockpile are located within 70m-90m of the Company’s Gold Gravity Plant while the Consolidated Pad is located <1km further up the valley.
- Domains of waste versus mineralisation are evident resulting in higher grade zones;
  - Process Plant Stockpile averages 1.26g/t Au across 24 samples with a max gold value of 5.50g/t Au,
  - Tails Dam Road Stockpile averages 2.10g/t Au across 15 samples with a max gold value of 12.20g/t Au &
  - Consolidated Pad averages 0.89g/t Au across 20 samples with a max gold value of 6.74g/t Au.
- Grade estimation of stockpiles can be difficult due to their random nature and can only truly be determined by processing a bulk sample. Vertex plans to run a bulk sample through the Hill End Gravity Plant, where previous recoveries exceeded 95%.
- Refurbishment of the Plant continues with the testing and rewinding of electrical motors on crushing and processing equipment. The Company anticipates that within the next month this refurbishment work will have been completed such that the plant will be ready for wet commissioning
- Vertex has prioritised the assessment of open pit and Underground gold mineralisation on the Company’s Mining Leases, to provide follow-on feed for the plant.

### Cautionary Statement

It must be noted that only the surface of the stockpile was sampled and that the sample grades may not be representative of the entire stockpile which is up to 25m thick.

***Vertex Minerals Limited (ASX: VTX) (“Vertex” or the “Company”) is pleased to advise they have sampled stockpiles immediately adjacent their Hill End gravity processing plant and received robust gold grades.***

### Director Tully Richards commented:

*“Vertex are very pleased that, ongoing and additional sampling continues to add substance to the planned treatment of mineralised stockpiles through the Company’s plant.”*

### Sampling Technique

A backhoe was used to dig trenches across three stockpile locations, namely, the Process Plant Stockpile (“PPS”), Tails Dam Road Stockpile (“TDRS”) and Consolidated Pad (“CP”). Approx 5kg of sample, inclusive of all size fractions, was collected from each metre and submitted to ALS Orange for assay by Fire Assay (50g charge)



**Plate 1. Showing trench excavation.**

**Plate 2. Showing sampling from bucket.**

**Table 1A Trench samples, weights and Au grades.**

Location	Trench	Interval (m)	Weight (kg)	Au-AA26 (ppm)	Weighted Average Interval
Process Plant SP	Trench A	0-1	5.34	5.50	
Process Plant SP	Trench A	1-2	5.16	0.30	
Process Plant SP	Trench A	2-3	5.32	0.10	
Process Plant SP	Trench A	3-4	6.02	0.90	
				<b>1.69</b>	4m @ 1.69g/t gold
Process Plant SP	Trench B	0-1	5.58	0.70	
Process Plant SP	Trench B	1-2	5.28	3.30	
Process Plant SP	Trench B	2-3	5.32	1.90	
Process Plant SP	Trench B	3-4	5.48	0.30	
				<b>1.53</b>	4m @ 1.53g/t gold
Process Plant SP	Trench C	0-1	4.72	1.90	
Process Plant SP	Trench C	1-2	4.94	0.20	
Process Plant SP	Trench C	2-3	5.54	1.30	
Process Plant SP	Trench C	3-4	5.82	0.80	
				<b>1.04</b>	4m @ 1.04g/t gold
Process Plant SP	Trench D	0-1	5.46	3.10	
Process Plant SP	Trench D	1-2	5.26	3.40	
Process Plant SP	Trench D	2-3	5.36	0.10	
Process Plant SP	Trench D	3-4	6.04	0.70	
				<b>1.79</b>	4m @ 1.79g/t gold
Process Plant SP	Trench E	0-1	4.82	0.30	
Process Plant SP	Trench E	1-2	5.06	0.00	
Process Plant SP	Trench E	2-3	5.16	0.00	
Process Plant SP	Trench E	3-4	4.92	0.01	
				<b>0.07</b>	4m @ 0.07g/t gold
Process Plant SP	Trench F	0-1	5.52	0.00	
Process Plant SP	Trench F	1-2	5.18	0.00	
Process Plant SP	Trench F	2-3	5.18	0.00	
Process Plant SP	Trench F	3-4	5.10	0.10	
				<b>0.02</b>	4m @ 0.02g/t gold
Process Plant SP	Trench G	0-1	5.18	0.10	
Process Plant SP	Trench G	1-2	4.86	2.30	
Process Plant SP	Trench G	2-3	5.40	0.90	
Process Plant SP	Trench G	3-4	5.38	0.00	
				<b>0.80</b>	4m @ 0.80g/t gold
Process Plant SP	Trench H	0-1	4.98	0.10	
Process Plant SP	Trench H	1-2	4.96	0.00	
Process Plant SP	Trench H	2-3	4.84	0.00	
Process Plant SP	Trench H	3-4	5.00	0.20	
				<b>0.08</b>	4m @ 0.08g/t gold
Process Plant SP	Trench I	0-1	5.32	1.50	

Process Plant SP	Trench I	1-2	5.22	0.00	
Process Plant SP	Trench I	2-3	5.56	0.10	
Process Plant SP	Trench I	3-4	4.86	0.90	
				<b>0.62</b>	4m @ 0.62g/t gold
TAILS DAM RD	Trench J	0-1	5.36	0.00	
TAILS DAM RD	Trench J	1-2	5.56	1.00	
TAILS DAM RD	Trench J	2-3	5.34	0.00	
TAILS DAM RD	Trench J	3-4	5.02	0.00	
				<b>0.26</b>	4m @ 0.26g/t gold
TAILS DAM RD	Trench K	0-1	4.58	1.50	
TAILS DAM RD	Trench K	1-2	5.08	7.50	
TAILS DAM RD	Trench K	2-3	4.76	2.70	
				<b>4.01</b>	3m @ 4.01g/t gold
TAILS DAM RD	Trench L	0-1	5.10	0.00	
TAILS DAM RD	Trench L	1-2	5.22	0.02	
TAILS DAM RD	Trench L	2-3	5.08	0.01	
TAILS DAM RD	Trench L	3-4	5.80	0.00	
				<b>0.01</b>	4m @ 0.01g/t gold
TAILS DAM RD	Trench M	0-1	5.30	0.01	
TAILS DAM RD	Trench M	1-2	5.94	0.00	
TAILS DAM RD	Trench M	2-3	5.46	0.01	
TAILS DAM RD	Trench M	3-4	6.26	0.02	
				<b>0.01</b>	4m @ 0.01g/t gold
TAILS DAM RD	Trench N	0-1	5.04	0.01	
TAILS DAM RD	Trench N	1-2	5.00	0.03	
TAILS DAM RD	Trench N	2-3	5.00	1.72	
TAILS DAM RD	Trench N	3-4	5.06	0.93	
				<b>0.67</b>	4m @ 0.67g/t gold
TAILS DAM RD	Trench O	0-1	5.50	0.01	
TAILS DAM RD	Trench O	1-2	6.44	0.02	
TAILS DAM RD	Trench O	2-3	5.48	12.20	
				<b>3.85</b>	3m @ 3.85g/t gold
TAILS DAM RD	Trench P	0-1	4.94	0.06	
TAILS DAM RD	Trench P	1-2	5.26	0.07	
TAILS DAM RD	Trench P	2-3	4.96	0.10	
TAILS DAM RD	Trench P	3-4	5.22	3.35	
				<b>0.91</b>	4m @ 0.91g/t gold
TAILS DAM RD	Trench Q	0-1	5.00	1.29	
				<b>1.29</b>	Grab sample
Consolidated Pad	Trench A	0-1	4.90	0.00	
Consolidated Pad	Trench A	1-2	5.02	0.00	
Consolidated Pad	Trench A	2-3	4.94	0.04	
Consolidated Pad	Trench A	3-4	4.96	0.02	
				<b>0.01</b>	4m @ 0.01g/t gold
Consolidated Pad	Trench B	0-1	4.82	0.03	
Consolidated Pad	Trench B	1-2	5.46	0.02	

Consolidated Pad	Trench B	2-3	5.04	0.05	
Consolidated Pad	Trench B	3-4	4.88	6.74	
				<b>1.65</b>	4m @ 1.65g/t gold
Consolidated Pad	Trench C	0-1	5.08	0.01	
Consolidated Pad	Trench C	1-2	5.20	0.83	
Consolidated Pad	Trench C	2-3	5.00	0.17	
Consolidated Pad	Trench C	3-4	4.96	0.54	
				<b>0.39</b>	4m @ 0.39g/t gold
Consolidated Pad	Trench D	0-1	5.12	0.68	
Consolidated Pad	Trench D	1-2	5.04	0.46	
Consolidated Pad	Trench D	2-3	4.94	0.06	
Consolidated Pad	Trench D	3-4	5.16	0.17	
				<b>0.34</b>	4m @ 0.34g/t gold
Consolidated Pad	Trench E	0-1	5.36	0.06	
Consolidated Pad	Trench E	1-2	4.80	1.38	
Consolidated Pad	Trench E	2-3	4.98	0.15	
Consolidated Pad	Trench E	3-4	4.92	0.18	
				<b>0.43</b>	4m @ 0.43g/t gold
Consolidated Pad	Trench F	0-1	4.86	0.12	
Consolidated Pad	Trench F	1-2	4.82	5.42	
Consolidated Pad	Trench F	2-3	4.88	0.10	
Consolidated Pad	Trench F	3-4	4.94	0.63	
				<b>1.55</b>	4m @ 1.55g/t gold
Consolidated Pad	Trench G	0-1	5.26	0.03	
Consolidated Pad	Trench G	1-2	5.00	0.29	
Consolidated Pad	Trench G	2-3	4.94	0.01	
Consolidated Pad	Trench G	3-4	4.90	0.00	
				<b>0.08</b>	4m @ 0.08g/t gold

**Table 2B Sample Locations**

<b>LOCATION</b>	<b>TRENCH</b>	<b>EASTING</b>	<b>NORTHING</b>	<b>Z_LIDAR</b>	<b>Z_GPS</b>
Process Plan Stockpile	A	724862	6340660	627	
Process Plan Stockpile	B	724868	6340647	626.2	
Process Plan Stockpile	C	724884	6340650	626.7	
Process Plan Stockpile	D	724904	6340650	627.2	
Process Plan Stockpile	E	724874	6340670	626.9	
Process Plan Stockpile	F	724885	6340668	626.6	
Process Plan Stockpile	G	724894	6340668	626.6	
Process Plan Stockpile	H	724912	6340658	628.8	
Process Plan Stockpile	I	724885	6340682	627.4	
Consolidated Pad	A	725042	6340939	722.2	
Consolidated Pad	B	725033	6340946	721.1	

Consolidated Pad	C	725024	6340952	720.9	741
Consolidated Pad	D	725026	6340966	721.4	739
Consolidated Pad	E	725029	6340984	721.9	737
Consolidated Pad	F	725043	6340969	722.2	
Consolidated Pad	G	725040	6340956	721.7	733
Tails Dam Rd	J	724923	6340635	636.7	
Tails Dam Rd	K	724921	6340602	636.9	
Tails Dam Rd	L	724926	6340651	634.6	643
Tails Dam Rd	M	724922	6340628	637	645
Tails Dam Rd	N	724922	6340620	637.3	646
Tails Dam Rd	O	724922	6340611	637.3	645
Tails Dam Rd	P	724918	6340594	636.2	646
Tails Dam Rd	Q	724922	6340589	635.9	646

The raw data re the above is summarised below;

- **9 trenches, for 36 samples, were dug across the Process Plant Stockpile averaging 0.86g/t Au incl. a high of 5.50g/t Au while,**
- **7 trenches & 1 grab, for 27 samples, were dug across the Tails Dam Road Stockpile averaging 1.21g/t Au incl. a high of 12.20g/t Au**
- **A further 7 trenches, for 28 samples, were dug across the Consolidated Pad averaging 0.65g/t Au incl. a high of 6.74g/t Au**

Figure 1 illustrates trench locations at PPS and TDRS. Said stockpiles comprises material mined between 2008 and 2010 and are considered to be low grade stockpiles rather than waste dumps (development completed during this period was either on the 'line of lode' or within the mine sequence of rocks (about 25m wide) that comprise all of the vein sets historically mined at Hawkin's Hill. This means that all the material that comprises the stockpile has a high probability of being mineralised.

In 2009 the price of gold was around AUD1156 per ounce (source <https://abcbullion.com.au/products-pricing/eofy-price-history>). Back analysis of mine expenditure information in the Company's data archive indicates that this would have related to a break-even grade of around 12g/t Au. Material below this break-even grade would have likely been directed to the mine stockpile by the production geologists at the time. Vertex considers the stockpile to contain material that is economically viable to process and plans to restart the existing processing plant and process enough of the stockpiled material (+100 tonnes) to determine the average grade of the stockpile. If the grade of this initial bulk sample is sufficient to provide an economic benefit, the Company will continue to process the stockpile.



Figure 1 – showing trench locations A-I for PPS & J-Q for TDRS (samples M1-M5 & previously reported, are also shown).

Figure 2 illustrates trench locations at the Consolidated Pad/laydown area. Less is known about the construction of the Consolidated Pad. Vertex will look to process parcels of said pad through its gravity circuit to determine if reclaiming this pad will be worthwhile.



This announcement has been approved by the Board of Vertex Minerals Limited.

**Further Information:**

**Roger Jackson**  
**Executive Chairman**  
**roger@vertexminerals.com.au**

**Tully Richards**  
**Technical Director**  
**tully@vertexminerals.com.au**

**About Vertex Minerals Limited**

Vertex Minerals Limited (ASX: VTX) is an Australian based gold exploration company developing its advanced Hargraves and Hill End gold projects located in the highly prospective Eastern Lachlan Fold Belt of Central West NSW. Other Company assets include the Pride of Elvire gold project and Taylors Rock gold/nickel/lithium project both located in the Eastern Goldfields of WA. The focus of Vertex Minerals is to advance the commercial production of gold from its NSW projects embracing an ethical and environmentally sustainable approach:

- **Gravity Separation:** The deportment of gold at the Hill End Project allows high recovery to a concentrate produced using gravity separation techniques.
- **Direct Smelting:** The use of direct smelting of a gold concentrate that eliminates the need to use cyanide as a solvent.
- **Contrast in Density:** These separation techniques take advantage of the contrast in density of gold ( $\rho=19.3$ ) relative to quartz ( $\rho=2.65$ ).
- **Renewable Energy Potential:** The unique landscape and infrastructure makes Hill End ideal for the establishment of renewable sources of power. The Crudine Ridge Windfarm is only 30km from the project site and Vertex plans to examine a pumped hydro-electricity scheme as an integral part of any proposed development. The topography and existing mine workings including shafts and adits make the establishment of a pumped hydro scheme achievable at modest expense.
- **Benign Tailings:** The tailings will essentially be quartz with little to no sulphide minerals.

**Hargraves Gold Project (NSW)**

- Hargraves Gold project is located approximately 2.5 km south of the town of Mudgee.
- The goldfield is 4 x 10 km with numerous mineralised structures with little modern exploration.
- An updated mineral resource in accordance with JORC 2012 Code was completed by SRK Consulting (Australasia) Pty Ltd (SRK) – total of **2.3Mt at 2.38g/t Au for 177koz Au.**

**Hill End Gold Project (NSW)**

- Consists of 10 mining leases and three Exploration Licences located in the core of the Hill End Trough on the eastern Lachlan Fold Belt.
- 14km of continuous gold lode with gold recovery rate to gravity at +90%.
- Work undertaken in 2015 by Hill End Gold Limited (HEG) culminated in a JORC 2012 resource estimate of **80,000 oz Au @ 1.7 g/t to 150m depth.**

<b>Hill End Project Mineral Resource Estimate</b>				
<b>Deposit</b>	<b>Classification</b>	<b>Tonnes (kt)</b>	<b>Grade Au (g/t)</b>	<b>Contained Au (koz)</b>
<b>Reward Gold Mine</b>	Indicated	55	12.4	22
	Inferred	782	8.1	205
<b>Sub Total</b>		<b>837</b>	<b>8.5</b>	<b>227</b>
<b>Hargraves Project</b>	Indicated	1,109	2.7	97
	Inferred	1,210	2.1	80
<b>Sub Total</b>		<b>2,319</b>	<b>2.4</b>	<b>178</b>
<b>Red Hill Project</b>	Indicated	413	1.4	19
	Inferred	1,063	1.8	61
<b>Sub Total</b>		<b>1,476</b>	<b>1.7</b>	<b>80</b>
<b>Project Total</b>	Indicated	1,577	2.7	138
	Inferred	3,055	3.5	347
<b>Grand Total</b>		<b>4,632</b>	<b>3.3</b>	<b>485</b>

#### **Pride of Elvire Gold Project (WA)**

- Tenements surround the Mt. Elvire homestead approximately 210km north of Southern Cross in Western Australia
- The project has seen historical drilling with encouraging gold results achieved.

#### **Taylor's Rock Project (WA)**

- Located 80km WSW of Norseman in the Southern Goldfields region of Western Australia.
- The project has both Gold and Nickel potential, interesting historical intercepts have recorded encouraging mineralisation.

#### **Competent Persons Statement**

The information in this report that relates to Exploration Results and Exploration Targets is based on information compiled by Mr. Roger Jackson, a Director and Shareholder of the Company, who is a 25+ year Fellow of the Australasian Institute of Mining and Metallurgy (FAusIMM), Fellow of the Australian Institute of Geoscientists (FAIG) and a Member of Australian Institute of Company Directors. Mr. Jackson has sufficient experience which is relevant to the style of mineralisation and type of deposits under consideration and to the activity which he is undertaking to qualify as a Competent Person as defined in the 2012 Edition of the "Australasian Code for Reporting of Exploration results, Mineral Resources and Ore Reserves". Mr. Jackson consents to the inclusion of the data contained in relevant resource reports used for this announcement as well as the matters, form and context in which the relevant data appears.

### Forward Looking Statements and Important Notice

This report contains forecasts, projections and forward-looking information. Although the Company believes that its expectations, estimates and forecast outcomes are based on reasonable assumptions it can give no assurance that these will be achieved. Expectations and estimates and projections and information provided by the Company are not a guarantee of future performance and involve unknown risks and uncertainties, many of which are out of Vertex Minerals' control.

Actual results and developments will almost certainly differ materially from those expressed or implied. Vertex Minerals has not audited or investigated the accuracy or completeness of the information, statements and opinions contained in this announcement. To the maximum extent permitted by applicable laws, Vertex Minerals makes no representation and can give no assurance, guarantee or warranty, express or implied, as to, and takes no responsibility and assumes no liability for the authenticity, validity, accuracy, suitability or completeness of, or any errors in or omission from, any information, statement or opinion contained in this report and without prejudice, to the generality of the foregoing, the achievement or accuracy of any forecasts, projections or other forward looking information contained or referred to in this report.

Investors should make and rely upon their own enquiries before deciding to acquire or deal in the Company's securities.

---

#### Vertex Minerals Ltd ABN 68 650 116 153

Unit 38, 460 Stirling Highway  
Peppermint Grove  
WA 6011

PO Box 8770  
Orange  
NSW 2800

Phone +61 (0) 8 6383 7828

Email: [info@vertexminerals.com.au](mailto:info@vertexminerals.com.au)

## Appendix 1 – Hill End Stockpile– JORC Code 2012 Table 1 Criteria

The table below summarises the assessment and reporting criteria used for the Hill End Gold Gravity Stockpile and reflects the guidelines in Table 1 of *The Australasian Code for the Reporting of Exploration Results, Mineral Resources and Ore Reserves* (the JORC Code, 2012).

### Section 1 Sampling Techniques and Data

Criteria	JORC Code explanation	Commentary
<b>Sampling techniques</b>	<i>Nature and quality of sampling (eg cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling.</i>	Rock chip samples were taken from 5 areas on the stockpile. Each set of samples was taken from random areas within an area of circa 3m by 3m. Each sample filled a 20l bucket. Trenches were taken with an Excavator Bucket. 750mm wide. Trenches were circa 3m long and up to 3m deep.
	<i>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</i>	No standards or duplicates were used for rock chip sampling.
	<i>Aspects of the determination of mineralisation that are Material to the Public Report.</i>	
	<i>In cases where 'industry standard' work has been done this would be relatively simple (eg 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information.</i>	The samples were bulked up to about 25kg each to account for the nugget affect. Trench samples were taken with the bucket across the base of the trench and composited.
<b>Drilling techniques</b>	<i>Drill type (eg core, reverse circulation, open- hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face- sampling bit or other type, whether core is oriented and if so, by what method, etc).</i>	No drilling is being reported.
<b>Drill sample recovery</b>	<i>Method of recording and assessing core and chip sample recoveries and results assessed.</i>	No drilling is being reported.
	<i>Measures taken to maximise sample recovery and ensure representative nature of the samples.</i>	No drilling is being reported.
	<i>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</i>	No drilling is being reported.
<b>Logging</b>	<i>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</i>	Samples are surface rock chip and geological interpretation is based on field observation
	<i>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography.</i>	
	<i>The total length and percentage of the relevant intersections logged.</i>	
<b>Sub-sampling techniques and</b>	<i>If core, whether cut or sawn and whether quarter, half or all core taken.</i>	No sub-sampling has been undertaken.

Criteria	JORC Code explanation	Commentary														
<b>sample preparation</b>	<i>If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry.</i>															
	<i>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</i>															
	<i>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</i>															
	<i>Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling.</i>															
	<i>Whether sample sizes are appropriate to the grain size of the material being sampled.</i>															
<b>Quality of assay data and laboratory tests</b>	<i>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</i>	<p>Each sample was submitted to the laboratory, and sorted into the size fractions shown below in the table. Each sized fraction was weighed, dried, and then pulverised. The samples were weighed and wet screened. Sized and pulverised fractions were received at OR lab and assayed via Au-AA26 – Fire-assay fusion with AAS finish. A nominal 50g sample was weighed for each size fraction, fused with a mixture of lead oxide, sodium carbonate, borax, silica and other reagents as required, inquarted with 6 mg of gold-free silver and then cupelled to yield a precious metal bead.</p> <p>The bead was digested in 0.5 mL dilute nitric acid in the microwave oven. 0.5 mL concentrated hydrochloric acid was then added and the bead further digested in the microwave at a lower power setting. The digested solution was cooled, diluted to a total volume of 10 mL with de-mineralized water, and analyzed by atomic absorption spectroscopy against matrix-matched standards.</p> <p>Samples were assayed with a blank, two internal CRMs and a duplicate in the same fusion run. Each sample was assayed in single with M5&gt;45&lt;106mm selected randomly for a run duplicate.</p> <p>The result reported is the grade of the analysed fraction and is not weight corrected for the sizing weight</p> <table border="1" data-bbox="858 1308 1426 1655"> <thead> <tr> <th>Method Code</th> <th>Element</th> <th>Symbol</th> <th>Units</th> <th>Sample Weight (g)</th> <th>Lower Limit</th> <th>Upper Limit</th> </tr> </thead> <tbody> <tr> <td>Au-AA26</td> <td>Gold</td> <td>Au</td> <td>ppm</td> <td>50</td> <td>0.01</td> <td>100</td> </tr> </tbody> </table> <p>The +75 micron fraction was dried in aluminium trays, weighed and fire assayed to extinction. The -75 micron fraction was collected using flocculant, the liquor then decanted and the fines sample dried in an oven. This was homogenised in the LM2, weighed and fire assayed in duplicate using a 50 g charge. The assays for the -75 micron fraction were averaged and a weighted average is calculated with the +75 micron fraction.</p>	Method Code	Element	Symbol	Units	Sample Weight (g)	Lower Limit	Upper Limit	Au-AA26	Gold	Au	ppm	50	0.01	100
Method Code	Element	Symbol	Units	Sample Weight (g)	Lower Limit	Upper Limit										
Au-AA26	Gold	Au	ppm	50	0.01	100										

Sample Description	<45mm		45 - 106 mm		>106mm		Total	
	Weight (kg)	Au-(g/t)	Weight (kg)	Au (g/t)	Weight (kg)	Au (g/t)	Weight (Kg)	Au (g/t)
M1	15.28	2.34	7.70	33.50	1.86	2.70	24.84	12.03
M2	20.82	8.45	3.80	0.38			24.62	7.20
M3	24.08	0.39	7.40	3.81			31.48	1.19
M4	23.96	0.06	3.90	0.13			27.86	0.07
M5	16.60	1.06	7.38	0.02			23.98	0.74
Average	100.74	2.38	30.18	9.55	1.86	2.70	132.78	4.02

  

	<i>For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.</i>	Not used for reporting
	<i>Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established</i>	Not applicable
<b>Verification of sampling and assaying</b>	<i>The verification of significant intersections by either independent or alternative company personnel.</i>	Rock chip sampling reported with no independent verification
	<i>The use of twinned holes.</i>	Rock chip sampling only with no drill repeats
	<i>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</i>	Field reconnaissance data is manually collected in field including photograph and location. Data is recorded in geological database
	<i>Discuss any adjustment to assay data.</i>	None required
<b>Location of data points</b>	<i>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</i>	All samples collected are located using a hand held GPS.
	<i>Specification of the grid system used</i>	The grid system used is GDA94 Zone 50
	<i>Quality and adequacy of topographic control.</i>	Nominal RLs based on regional topographic datasets are used initially; however, these will be updated if DGPS coordinates are collected.
<b>Data spacing and distribution</b>	<i>Data spacing for reporting of Exploration Results.</i>	Rock chip samples were randomly collected and were appropriate given the objectives of the program. Trench samples were randomly collected and collated.
	<i>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</i>	MRE not being prepared.
	<i>Whether sample compositing has been applied.</i>	None undertaken.
<b>Orientation of data in relation to geological structure</b>	<i>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</i>	Rock chip sampling was undertaken at the surface only. This does not represent the full stockpile volume.
	<i>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</i>	
<b>Sample security</b>	<i>The measures taken to ensure sample security.</i>	Senior company personnel supervise all sampling and transport to assay laboratory in Perth.
<b>Audits or reviews</b>	<i>The results of any audits or reviews of sampling techniques and data.</i>	No Audits or reviews were undertaken

**Section 2 Reporting of Exploration Results**

Criteria	JORC Code explanation	Commentary
<b>Mineral tenement and land tenure status</b>	<ul style="list-style-type: none"> <li>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</li> </ul>	<ul style="list-style-type: none"> <li>The project is located within granted Exploration Licence EL5868 Mining leases ML1541, ML1116, ML315, ML316, ML317, ML49, ML50, ML913, ML914, ML915 and GL5846 with the earliest expiry date of 19 January 2033. The leases are held by Vertex Minerals Pty Ltd.</li> <li>The site is covered by EPL 12008, scheduled activity is mining for minerals.</li> </ul> <p>As more fully disclosed in the Company's 2022 IPO Prospectus (see sections 5.1 and 7.2 of the Prospectus, and pages 83 and 84 of the Independent Geologist Report that is annexed to the Prospectus) First Tiffany Resources Corporation (FTRC) has a right to obtain a 15% contributing interest, which will only be triggered by the Company providing an 'economic feasibility study'. Failure to contribute will result in forfeiture of this right. The result is that the Company has a 100% beneficial interest in all its tenements at Hill End, subject to reduction to 85% in respect of certain tenements, if FTRC contributes at the 15% level.</p>
	<i>The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.</i>	All tenements are in good standing.
<b>Exploration done by other parties</b>	<i>Acknowledgment and appraisal of exploration by other parties.</i>	In relation to this stockpile no previous exploration or sampling has been undertaken.
<b>Geology</b>	<i>Deposit type, geological setting and style of mineralisation.</i>	<ul style="list-style-type: none"> <li>Mineralisation at the Reward deposit from which the stockpile is derived, occurs within a series of bedding parallel quartz veins occurring along the limbs of the Hill End Anticline which is located in the mid-Silurian to mid-Devonian Hill End Trough containing sedimentary and volcanic rocks. The deposit is best described as a brittle, thrust-dominated, competency-controlled orogenic gold low sulphide system developed post ductile deformation.</li> </ul>
<b>Drillhole Information</b>	<i>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drillholes:</i> <ul style="list-style-type: none"> <li><i>easting and northing of the drillhole collar</i></li> </ul>	No drilling undertaken

	<ul style="list-style-type: none"> <li>elevation or RL (elevation above sea level in metres) of the drillhole collar</li> <li>dip and azimuth of the hole</li> <li>down hole length and interception depth</li> <li>hole length.</li> </ul>	
<b>Data aggregation methods</b>	<i>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high grades) and cut-off grades are usually Material and should be stated.</i>	None completed.
<b>Relationship between mineralisation widths and intercept lengths</b>	<i>If the geometry of the mineralisation with respect to the drillhole angle is known, its nature should be reported. If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (e.g. 'down hole length, true width not known').</i>	No drilling completed by Lachlan Star
<b>Diagrams</b>	<i>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</i>	Appropriate figures are presented in the announcement
<b>Balanced reporting</b>	<i>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</i>	Recent exploration results reported and tabulated.
<b>Other substantive exploration data</b>	<i>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</i>	<ul style="list-style-type: none"> <li>The mineralogy of the Hill End gold mineralisation is relatively simple with most gold being of high fineness and hosted within quartz veins with low sulphide content.</li> <li>Preliminary metallurgical testing by Metcon Laboratories Brookvale NSW, indicated that the gold is coarse and free milling. Testing has determined that 98% of the contained gold is liberated and recoverable at a P80 grind size of 670 microns.</li> <li>The gravity separation plant on site achieved a 95% recovery rate. During 2009 a total of 12,591 tonnes of ore at a grade of 15.9g/t was processed producing 5,871 ounces of gold.</li> </ul>
<b>Further work</b>	<i>The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale step-out drilling).</i>	<ul style="list-style-type: none"> <li>Bulk sampling by way of gravity gold processing will be undertaken</li> </ul>